

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<p>(51) International Patent Classification 6: G02B 1/04</p>	<p>A1</p>	<p>(11) International Publication Number: WO 96/31792 (43) International Publication Date: 10 October 1996 (10.10.96)</p>
<p>(21) International Application Number: PCT/EP96/01265 (22) International Filing Date: 22 March 1996 (22.03.96) (30) Priority Data: 95810221.2 4 April 1995 (04.04.95) EP (34) Countries for which the regional or international application was filed: DE et al. 1496/95 19 May 1995 (19.05.95) CH 08/569,816 8 December 1995 (08.12.95) US (71) Applicants (for all designated States except US): CIBA-GEIGY AG [CH/CH]; Klybeckstrasse 141, CH-4002 Basle (CH). COMMONWEALTH SCIENTIFIC AND INDUSTRIAL RESEARCH ORGANISATION [AU/AU]; Limestone Avenue, Campbell, ACT 2602 (AU). (72) Inventors; and (75) Inventors/Applicants (for US only): NICOLSON, Paul, Clement [US/US]; 7765 Sagebrush Drive, Dunwoody, GA 30350 (US). BARON, Richard, Carlton [US/US]; 115 Kiltirman Court, Alpharetta, GA 30201 (US). CHABRECEK, Peter [SK/CH]; Friedrichstrasse 13, CH-4055 Basle (CH). COURT, John [AU/AU]; 34/333 Bulwara Road, Ultimo, NSW 2007 (AU). DOMSCHKE, Angelika [DE/DE]; Inzlinger Strasse 14, D-79540 Lorrach (DE). GRIESSER,</p>		<p>Hans, Jörg [CH/AU]; 20 View Road, The Patch, VIC 3792 (AU). HO, Arthur [AU/AU]; 12/50 Fern Street, Randwick, NSW 2031 (AU). HÖPKEN, Jens [DE/DE]; Inzlinger Strasse 33, D-79540 Lorrach (DE). LAYCOCK, Bronwyn, Glenice [AU/AU]; 4 Churchill Street, Heidelberg Heights, VIC 3081 (AU). LIU, Qin [CN/US]; 3250 River Summit Trail, Duluth, GA 30136 (US). LOHMANN, Dieter [CH/CH]; Mittelweg 56, CH-4142 Münchenstein (CH). MEIJS, Gordon, Francis [AU/AU]; 3 Henry Street, Murrumbena, VIC 3163 (AU). PAPASPILOTPOPOULOS, Eric [AU/AU]; 10/52 Goodhope Street, Paddington, NSW 2021 (AU). RIFFLE, Judy, Smith [US/US]; 608 Floyd Street, Blacksburg, VA 24060 (US). SCHINDHELM, Klaus [AU/AU]; 72 Francis Greenway Drive, Cherrybrook, NSW 2120 (AU). SWEENEY, Deborah [AU/AU]; 23 Malga Street, Roseville, NSW 2069 (AU). TERRY, Wilson, Leonard, Jr. [US/US]; 755 Citrus Drive, Alpharetta, GA 30202 (US). VOGT, Jürgen [CH/CH]; Kleinschönberg 34, CH-1700 Fribourg (CH). WINTERTON, Lynn, Cook [US/US]; 840 Locust Grove Court, Alpharetta, GA 30201 (US). (74) Common Representative: CIBA-GEIGY AG; Patentabteilung, Klybeckstrasse 141, CH-4002 Basle (CH). (81) Designated States: AL, AU, BB, BG, BR, CA, CN, CZ, EE, GE, HU, IS, JP, KP, KR, LK, LR, LT, LV, MG, MK, MN, MX, NO, NZ, PL, RO, SG, SI, SK, TR, TT, UA, US, UZ, VN, ARIPO patent (KE, LS, MW, SD, SZ, UG), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</p>
<p>(54) Title: EXTENDED WEAR OPHTHALMIC LENS (57) Abstract An ophthalmic lens is disclosed which is suited for extended-wear periods of at least one day on the eye without a clinically significant amount of corneal swelling and without substantial wearer discomfort. The lens has a balance of oxygen permeability and ion or water permeability, with the ion or water permeability being sufficient to provide good on-eye movement, such that a good tear exchange occurs between the lens and the eye. A preferred lens is a copolymerization product of an oxypem macromer and an ionopem monomer. The invention encompasses extended wear contact lenses, which include a core having oxygen transmission and ion transmission pathways extending from the inner surface to the outer surface.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AM	Armenia	GB	United Kingdom	MW	Malawi
AT	Austria	GE	Georgia	MX	Mexico
AU	Australia	GN	Guinea	NE	Niger
BB	Barbados	GR	Greece	NL	Netherlands
BE	Belgium	HU	Hungary	NO	Norway
BF	Burkina Faso	IE	Ireland	NZ	New Zealand
BG	Bulgaria	IT	Italy	PL	Poland
BJ	Benin	JP	Japan	PT	Portugal
BR	Brazil	KE	Kenya	RO	Romania
BY	Belarus	KG	Kyrgyzstan	RU	Russian Federation
CA	Canada	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic	KR	Republic of Korea	SE	Sweden
CG	Congo	KZ	Kazakhstan	SG	Singapore
CH	Switzerland	LI	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovakia
CM	Cameroon	LR	Liberia	SN	Senegal
CN	China	LT	Lithuania	SZ	Swaziland
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	LV	Latvia	TG	Togo
DE	Germany	MC	Monaco	TJ	Tajikistan
DK	Denmark	MD	Republic of Moldova	TT	Trinidad and Tobago
EE	Estonia	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	UG	Uganda
FI	Finland	MN	Mongolia	US	United States of America
FR	France	MR	Mauritania	UZ	Uzbekistan
GA	Gabon			VN	Viet Nam

EXTENDED WEAR OPHTHALMIC LENS

BACKGROUND OF THE INVENTION

1. FIELD OF THE INVENTION

This invention relates broadly to lenses and polymeric materials useful in optic and ophthalmic arts. More specifically, this invention relates to polymeric materials and treatment processes useful in the manufacture of contact lenses. Still more specifically, this invention relates to contact lenses useful as extended-wear contact lenses.

2. DESCRIPTION OF THE RELATED ART

A wide variety of research has been conducted in the field of biocompatible polymers. The definition of the term "biocompatible" depends on the particular application for which the polymer is designed. In the field of ophthalmic lenses, and in particular in the field of contact lenses, a biocompatible lens may be generally defined as one which will not substantially damage the surrounding ocular tissue and ocular fluid during the time period of contact. The phrase "ophthalmically compatible" more appropriately describes the biocompatibility requirements of ophthalmic lenses.

One ophthalmic compatibility requirement for contact lenses is that the lens must allow oxygen to reach the cornea in an amount which is sufficient for long-term corneal health. The contact lens must allow oxygen from the surrounding air to reach the cornea because the cornea does not receive oxygen from the blood supply like other tissue. If sufficient oxygen does not reach the cornea, corneal swelling occurs. Extended periods of oxygen deprivation causes the undesirable growth of blood vessels in the cornea. "Soft" contact lenses conform closely to the shape of the eye, so oxygen cannot easily circumvent the lens. Thus, soft contact lenses must allow oxygen to diffuse through the lens to reach the cornea.

Another ophthalmic compatibility requirement for soft contact lenses is that the lens must not strongly adhere to the eye. Clearly, the consumer must be able to easily remove the lens from the eye for disinfecting, cleaning, or disposal. However, the lens must also be able to move on the eye in order to encourage tear flow between the lens and the eye. Tear flow between the lens and eye allows for debris, such as foreign particulates or dead

epithelial cells, to be swept from beneath the lens and, ultimately, out of the tear fluid. Thus, a contact lens must not adhere to the eye so strongly that adequate movement of the lens on the eye is inhibited.

While there exist rigid gas permeable ("RGP") contact lenses which have high oxygen permeability and which move on the eye, RGP lenses are typically quite uncomfortable for the consumer. Thus, soft contact lenses are preferred by many consumers because of comfort. Moreover, a contact lens which may be continuously worn for a period of a day or more (including wear during periods of sleeping) requires comfort levels which exclude RGP lenses as popular extended-wear candidates.

In order to balance the ophthalmic compatibility and consumer comfort requirements in designing a daily wear soft contact lens, polymers and copolymers of 2-hydroxyethyl methacrylate (HEMA) were developed. These hydrophilic polymers move well on the eye and provide sufficient oxygen permeability for daily wear. Certain soft contact lenses have been approved by the FDA for extended wear periods of up to about 6 nights of overnight wear and seven days of daily wear. However, the consumer cannot safely and comfortably wear these poly(HEMA) lenses for extended periods of seven days or more, because the oxygen permeability is insufficient. True extended wear (i.e., seven days or more) of these lenses may result, at a minimum, in corneal swelling and development of surface blood vessels in the cornea.

In order to improve oxygen permeability, polymers containing silicone groups were developed. A variety of siloxane-containing polymers have been disclosed as having high oxygen permeability. For example, see U.S. Patent Nos. 3,228,741; 3,341,490; 3,996,187; and 3,996,189. However, polysiloxanes are typically highly lipophilic. The properties (e.g., lipophilicity, glass transition temperature, mechanical properties) of known polysiloxanes has resulted in contact lenses which adhere to the eye, inhibiting the necessary lens movement. In addition, polysiloxane lipophilicity promotes adhesion to the lens of lipids and proteins in the tear fluid, causing a haze which interferes with vision through the lens.

There have been attempts to blend the desirable hydrophilic properties of hydrophilic polymers, formed from monomers such as HEMA, with the desirable oxygen permeability of polymers formed from siloxane-containing monomers. For example, see U.S. Patent Nos. 3,808,178; 4,136,250; and 5,070,169. However, prior attempts at producing a true extended wear contact lens have been unsuccessful, either because of the effect of the

extended-wear lens on corneal health or because the lens would not move on the eye. Thus, there remains a need for an ophthalmically compatible, transparent polymeric material which is suited to extended periods of continuous contact with ocular tissue and tear fluid.

OBJECTS AND SUMMARY OF THE INVENTION

An object of the invention is to provide a material having a balance of oxygen permeability, ion permeability, on-eye movement and tear exchange, all of which are sufficient for corneal health and wearer comfort during extended periods of continuous wear.

Another object of the invention is to provide an ophthalmic lens capable of extended continuous wear periods of at least 24 hours without substantial adverse impact on ocular health or consumer comfort, and more preferably, to provide a lens capable of continuous wear of 4 to 30 days or more without substantial adverse impact on ocular health or consumer comfort.

A further object of the invention is to provide an ophthalmic lens capable of extended continuous wear periods of at least 24 hours without substantial corneal swelling or consumer discomfort, and more preferably, to provide a lens capable of continuous wear of 4, 7, 14 or 30 days or more without substantial corneal swelling or consumer discomfort.

Yet another object of the invention is to provide methods of forming an extended-wear ophthalmic lens.

Still a further object of the invention is to provide methods of testing and classifying ophthalmic lenses as candidates for true extended-wear.

These and other objects of the invention are met by the various embodiments described herein.

One embodiment of the invention is an ophthalmic lens, suited to extended periods of wear in continuous, intimate contact with ocular tissue and tear fluid. The lens displays a balance of oxygen permeability and ion permeability sufficient to maintain good corneal health, adequate movement of the lens on the eye and wearer comfort during extended wear periods. The lens is formed by polymerization, preferably copolymerization, of (a) at least

one oxypem polymerizable material which is capable of polymerizing to form a polymer having a high oxygen permeability; and (b) at least one ionopem polymerizable material which is capable of polymerizing to form a polymer having a high ion permeability. Preferably, the lens includes a core polymeric material and ophthalmically compatible surfaces. In a preferred embodiment, the surface is more hydrophilic and lipophobic than the core polymeric material.

Another embodiment of the invention is a method of forming an ophthalmic lens having high oxygen permeability and high ion permeability. The method includes the step of forming a core material, having an inner surface and an outer surface, such that at least one pathway for ion transport and at least one pathway for oxygen transport are present from the inner to the outer surface. In a preferred embodiment, the method includes treating the surface of the lens to render the surface more hydrophilic than the core.

A further embodiment of the invention is an ophthalmic lens comprising a polymeric material which has a high oxygen permeability and a high ion or water permeability, the polymeric material being formed from at least one polymerizable material including (a) at least one oxypem segment and (b) at least one ionopem segment. The lens displays a balance of oxygen permeability and ion permeability sufficient to maintain good corneal health, adequate movement of the lens on the eye and wearer comfort during extended wear periods.

Yet another embodiment of the invention is a method of using a contact lens having both an oxygen transmission pathway and an ion transmission pathway from inner to outer surface as an extended wear lens. The method includes (a) applying the lens to the ocular environment and (b) allowing the lens to remain in intimate contact with the ocular environment for a period of at least 24 hours without substantial adverse impact on corneal health or wearer comfort. A preferred method includes additional steps of (c) removing the lens from the ocular environment; (d) disinfecting the lens; (e) applying the lens to the ocular environment; and (f) allowing the lens to remain in intimate contact with the ocular environment for a period of at least an additional 24 hours. In a preferred embodiment, the lens is worn for a continuous period of at least seven days without substantial adverse impact on corneal health or wearer comfort.

OUTLINE OF DESCRIPTION OF THE PREFERRED EMBODIMENTS

I. DEFINITION OF TERMS

II. CORE POLYMER AND LENS

- A. Oxypem polymerizable materials
- B. Ionopem polymerizable materials
- C. Weight ratio of oxypem to ionopem polymerizable materials
- D. Morphology
- E. Bulk Water Content
- F. Ion and Water Permeability
 - 1. Ionoflux Ion Permeability Measurements
 - 2. Ionoton Ion Permeability Measurements
 - 3. Hydrodell Water Permeability Measurements
- G. Oxygen Permeability and Transmissibility
- H. Mechanical On-eye Movement Parameters
 - 1. Tensile Modulus and Short Relaxation Time
 - 2. Tangent Delta
 - 3. Parameter Combinations
- I. Examples of suitable materials
 - 1. Material "A"
 - 2. Material "B"
 - 3. Material "C"
 - 4. Material "D"

III. OPHTHALMICALLY COMPATIBLE SURFACES

IV. UTILITY

- A. Ophthalmic lenses
- B. Contact lenses

V. METHODS OF USE AS EXTENDED-WEAR LENSES

VI. METHODS OF MANUFACTURE OF LENSES

DESCRIPTION OF THE PREFERRED EMBODIMENTS

One embodiment of the present invention is an ophthalmically compatible, transparent lens suited to extended periods of continuous contact with ocular tissue and tear fluids. A particularly preferred embodiment of the invention is an extended-wear vision correction lens suited for safe and comfortable long term wear without removal. In order to properly describe the invention and to delineate the metes and bounds of the claims, a set of basic terms will be defined at the outset.

I. DEFINITION OF TERMS

An "ophthalmic lens", as used herein, refers to lenses which are placed in intimate contact with the eye or tear fluid, such as contact lenses for vision correction (e.g., spherical, toric, bifocal), contact lenses for modification of eye color, ophthalmic drug delivery devices, ocular tissue protective devices (e.g., ophthalmic healing promoting lenses), and the like. A particularly preferred ophthalmic lens is an extended-wear contact lens, especially extended-wear contact lenses for vision correction.

A "polymerizable material which is capable of polymerizing to form a polymer having a high oxygen permeability", as used herein, refers to monomers, oligomers, macromers, and the like, and mixtures thereof, which are capable of polymerizing with like or unlike polymerizable materials to form a polymer which displays a relatively high rate of oxygen diffusion therethrough. For convenience of reference, these materials will be referred to herein as "oxyperm polymerizable materials" and the resultant polymers will be referred to herein as "oxyperm polymers".

The "oxygen transmissibility" of a lens, as used herein, is the rate at which oxygen will pass through a specific ophthalmic lens. Oxygen transmissibility, Dk/t , is conventionally expressed in units of barrers/mm, where t is the average thickness of the material [in units of mm] over the area being measured and "barrer" is defined as:

$$[(\text{cm}^3 \text{ oxygen})(\text{mm}) / (\text{cm}^2)(\text{sec})(\text{mm Hg})] \times 10^{-9}$$

The "oxygen permeability", Dk , of a lens material does not depend on lens thickness. Oxygen permeability is the rate at which oxygen will pass through a material. Oxygen permeability is conventionally expressed in units of barrers, where "barrer" is defined as:

$$[(\text{cm}^3 \text{ oxygen})(\text{mm}) / (\text{cm}^2)(\text{sec})(\text{mm Hg})] \times 10^{-10}$$

These are the units commonly used in the art. Thus, in order to be consistent with the use in the art, the unit "barrer" will have the meanings as defined above. For example, a lens having a Dk of 90 barrers ("oxygen permeability barrers") and a thickness of 90 microns (0.090 mm) would have a Dk/t of 100 barrers/mm ("oxygen transmissibility barrers"/mm).

A "polymerizable material which is capable of polymerizing to form a polymer having a high ion permeability", as used herein, refers to monomers, oligomers, macromers, and the like, and mixtures thereof, which are capable of polymerizing with like or unlike polymerizable materials to form a polymer which displays a relatively high rate of ion or water permeation therethrough. For convenience of reference, these materials will be referred to herein as "ionoperm polymerizable materials" and the resultant polymers will be referred to herein as "ionoperm polymers".

A "macromer", as used herein, refers to a polymerizable material which has a molecular weight of at least about 800 grams/mol. The term "macromer", as used herein, also encompasses oligomers.

A "monomer", as used herein refers to a polymerizable material which has a molecular weight of less than about 800 grams/mol.

A "phase", as used herein, refers to a region of substantially uniform composition which is a distinct and physically separate portion of a heterogeneous polymeric material. However, the term "phase" does not imply that the material described is a chemically pure substance, but merely that certain bulk properties differ significantly from the properties of another phase within the material. Thus, with respect to the polymeric components of a lens, an ionoperm phase refers to a region composed of essentially only ionoperm polymer (and water, when hydrated), while an oxypem phase refers to a region composed of essentially only oxypem polymer.

A "continuous phase", as used herein, refers to a region of substantially uniform composition which forms a continuous pathway from one surface of an article to another surface of an article.

"Co-continuous phases", as used herein, refers to at least two regions, each of substantially uniform composition which differs from the other, and each of which forms a continuous pathway from one surface of an article to another surface of an article. Thus,

an ophthalmic lens having co-continuous phases of oxypem polymer and ionopem polymer will have two continuous pathways or sets of continuous pathways extending from the inner surface of the lens to the outer surface of the lens.

"Morphology", as used herein, refers to the structure and relationship of the phases of a material.

"Ophthalmically compatible", as used herein, refers to a material or surface of a material which may be in intimate contact with the ocular environment for an extended period of time without significantly damaging the ocular environment and without significant user discomfort. Thus, an ophthalmically compatible contact lens will not produce significant corneal swelling, will adequately move on the eye with blinking to promote adequate tear exchange, will not have substantial amounts of lipid adsorption, and will not cause substantial wearer discomfort during the prescribed period of wear.

"Ocular environment", as used herein, refers to ocular fluids (e.g., tear fluid) and ocular tissue (e.g., the cornea) which may come into intimate contact with a contact lens used for vision correction, drug delivery, wound healing, eye color modification, or other ophthalmic applications.

"Hydrophilic", as used herein, describes a material or portion thereof which will more readily associate with water than with lipids.

A "hydrophilic surface", as used herein, refers to a surface which is more hydrophilic and lipophobic than the bulk or core material of an article. Thus, an ophthalmic lens having a hydrophilic surface describes a lens having a core material having a certain hydrophilicity surrounded, at least in part, by a surface which is more hydrophilic than the core.

The "outer surface" of a lens, as used herein, refers to the surface of the lens which faces away from the eye during wear. The outer surface, which is typically substantially convex, may also be referred to as the front curve of the lens. The "inner surface" of a lens, as used herein, refers to the surface of the lens which faces towards the eye during wear. The inner surface, which is typically substantially concave, may also be referred to as the base curve of the lens.

"TRIS", as used herein, refers to 3-methacryloxypropyltris(trimethylsiloxy) silane, which is represented by CAS No. 17096-07-0. The term "TRIS" also includes dimers of 3-methacryloxypropyltris(trimethylsiloxy) silane.

"Molecular weight" of a polymeric material (including monomeric or macromeric materials), as used herein, refers to the number-average molecular weight unless otherwise specifically noted or unless testing conditions indicate otherwise.

A. Oxyperm Polymerizable Materials

Oxyperm polymerizable materials include a wide range of materials which may be polymerized to form a polymer displaying a relatively high oxygen diffusion rate therethrough. In addition, these materials must be relatively ophthalmically compatible. These oxyperm polymerizable materials include, without limitation thereto, siloxane-containing macromers and monomers, fluorine-containing macromers and monomers, and carbon-carbon triple bond-containing macromers and monomers. The oxyperm macromer or monomer may also contain hydrophilic groups.

Preferred oxyperm polymers are those formed from a siloxane-containing macromer. Macromers having dialkyl siloxane groups, especially dimethyl siloxanes, are particularly preferred. These macromers are broadly referred to as poly(dimethyl siloxanes) (also, PDMS). The siloxane-containing macromer may also include hydrophilic groups. Examples of suitable siloxane-containing macromers include, without limitation thereto, the Materials A, B, C, and D as described herein.

The oxygen transmissibility (Dk/t) of the lens is preferably at least 70 barrers/mm, more preferably at least 75 barrers/mm, and most preferably at least 87 barrers/mm. The lens center thickness is typically more than about 30 microns, preferably about 30 to about 200 microns, more preferably about 40 to about 150 microns, even more preferably about 50 to about 120 microns, and most preferably about 60 to about 100 microns.

The oxygen transmissibility of the extended-wear lens from the outer surface to the inner surface must be sufficient to prevent any substantial corneal swelling during the period of extended wear. It is known that the cornea swells approximately 3% to 4% during overnight periods of sleep when the eyelids are closed, as a result of oxygen deprivation. It is also known that wearing a typical contact lens, such as ACUVUE (Johnson & Johnson), for a

period of about 8 hours (overnight wear) causes corneal swelling of about 11%. However, a preferred extended-wear contact lens will produce, after wear of about 24 hours, including normal sleep periods, corneal swelling of less than about 8%, more preferably less than about 6%, and most preferably less than about 4%. A preferred extended-wear contact lens will produce, after wear of about 7 days, including normal sleep periods, corneal swelling of less than about 10%, more preferably less than about 7%, and most preferably less than about 5%. Thus, the extended-wear lens must have oxypem polymer in an amount sufficient to produce oxygen diffusion pathways from the outer surface to the inner surface of the lens which are sufficient to yield the above properties relating to corneal swelling. Preferably, the extended-wear lens has a continuous phase of oxypem polymer extending from the outer surface to the inner surface of the lens.

B. Ionoperm Polymerizable Materials

Ionoperm polymerizable materials include a wide range of materials which may be polymerized to form a polymer displaying a relatively high ion diffusion rate therethrough. In addition, these materials must be relatively ophthalmically compatible. These ionoperm polymerizable materials include, without limitation thereto, acrylates and methacrylates, such as 2-hydroxyethyl methacrylate, acrylamide, methacrylamide, and dimethylacrylamide; poly(alkylene glycols), such as poly(ethylene glycol); N-vinyl pyrrolidones such as N-vinyl-2-pyrrolidone; and the like and mixtures thereof. Other ionoperm materials are disclosed in the specific embodiments of Materials A-D, described below.

C. Weight Ratios

The ratios of oxypem to ionoperm polymerizable materials may vary substantially, depending on the selected balance of oxygen permeability and ion permeability for the chosen end-use of the molded polymeric article. Preferably, the volumetric ratio of oxypem to ionoperm material (including water) in the fully hydrated lens is about 40 to about 60 to about 60 to about 40. However, weight percentages, based on the total weight of the lens, will be defined because weight percentages are more conveniently utilized in lens fabrication. Preferably, the extended-wear contact lenses having substantially only ionoperm and oxypem materials will have about 60 to about 85 weight percent oxypem polymerizable material and about 15 to about 40 weight percent ionoperm polymerizable material in the prepolymerization mixture, based on total polymerizable material weight. More preferably, the prepolymerization mixture will contain about 70 to about 82 weight

percent oxypem polymerizable material and about 18 to about 30 weight percent ionopem polymerizable material, based on total polymerizable material weight.

A wide variety of additional polymerizable materials may be included in the mixture prior to polymerization. Cross-linking agents, such as ethylene glycol dimethacrylate (EGDMA), may be added to improve structural integrity and mechanical strength. Antimicrobial polymerizable materials such as poly(quaternary ammonium) salts may be added to inhibit microbial growth on the lens material. Also, additional ionopem monomers or macromers and oxypem polymerizable materials may be added to adjust the oxygen permeability and ion permeability of the final molded article. An especially advantageous polymerizable material is TRIS, which may act both to increase oxygen permeability and to improve the modulus of elasticity.

A preferred prepolymerization mixture will include (a) about 30 to 60 weight percent oxypem macromer, (b) about 20 to 40 weight percent ionopem polymerizable material, and (c) about 1 to 35 weight percent TRIS, based on the total lens weight. More preferably, the amount of TRIS is about 10 to 33 weight percent, based on the total prepolymerization mixture weight.

In a preferred embodiment, the prepolymerization mixture includes less than about 5 weight percent cross-linking agent, based on the total prepolymerization mixture weight. More preferably, the prepolymerization mixture includes less than about 2 weight percent cross-linking agent, based on the total prepolymerization mixture weight. Even more preferably, the prepolymerization mixture includes substantially no cross-linking agent. In a particularly preferred embodiment, the prepolymerization mixture includes no added cross-linking agent.

The previously described ranges for oxypem polymerizable materials, ionopem polymerizable materials, and TRIS are offered to enable the reader to better comprehend the invention. However, it should be noted that the specific weight or volume percentages of oxypem and ionopem polymerizable materials are not the most critical factors to consider in preparing a good extended-wear ophthalmic lens. More importantly, the lens must have sufficient ion permeability for good on-eye movement and sufficient oxygen permeability for good corneal health during the extended wear period.

D. Morphology

One requirement of the lens material is that the lens allow a high visible light transmission from the outer to inner surface of the lens. A lens morphology which includes large phase separated regions will reduce visible light transmission and cause substantial undesirable image distortion, thereby destroying the value of the lens as a vision correction device. Thus, the lens must have a morphology which allows at least about 80%, more preferably about 90%, visible light transmission and does not produce any significant undesirable image distortion.

In one preferred embodiment, the lens material has at least two phases: the phases including at least one oxypem phase and at least one ionopem phase. While there may be two distinct phases, it is believed that there may be a transition phase, or interphase, in which the material composition and the material properties are a blend of those of the oxypem and ionopem materials. Thus, there may exist a distinct oxypem phase or plurality of distinct oxypem phases, a distinct ionopem phase or a plurality of distinct ionopem phases, and an amphipathic phase mixture or blend of oxypem and ionopem phases. In one preferred embodiment, the glass transition temperature (T_g) of the oxypem phase is less than about -115° Celsius (minus 115 degrees Celsius).

The existence of separate oxypem and ionopem phases, rather than a complete blend of oxypem and ionopem phases, is believed to be advantageous in promoting the diffusion of oxygen and ions. Oxygen will diffuse predominantly through the oxypem polymer, while the ionopem polymer provides a higher barrier to oxygen diffusion. Similarly, ions will diffuse well through the ionopem polymer, but the oxypem polymer provides a higher resistance to ion diffusion. Thus, one homogeneous oxypem/ionopem phase will provide undesirable resistance to both oxygen and ion diffusion, while two separate oxypem and ionopem phases will provide low resistance pathways for transmission of both oxygen and ions or water. Thus, the ideal extended-wear lens has a pathway or series of pathways from the outer surface to the inner surface for transmission of oxygen therethrough, and an analogous continuous pathway or series of pathways for transmission of water or ions therethrough. In a particularly preferred embodiment, the lens has two co-continuous phases, one an oxypem phase and the other an ionopem phase, allowing for permeation of water or ions and oxygen between the front and base curves of the lens.

E. Bulk Water Content

The measurement of water content is difficult because the removal of adhered surface droplets, without affecting the bulk lens water content, is difficult. In addition, water may evaporate from the lens surface quickly, thereby lowering the water content from the equilibrium level. Accordingly, a discussion of the bulk water content of a lens warrants a discussion of the measurement technique used to determine the water content.

The preferred bulk water content of the hydrated lens will be a function of the lens material properties. The material properties are dependent on the prepolymerization macromers and monomers and polymerization conditions. Thus, the preferred water content for a lens including a fluorine-containing oxypem material may be different from that of a lens including a siloxane-containing oxypem material. Accordingly, while general ranges for bulk water content are offered for a better understanding of the invention, the invention is not generally limited to specific bulk water contents.

One method of measuring the water content of a lens formed in accordance with the present invention, referred to herein as the "Bulk Technique", is as follows. First the lens is thoroughly hydrated in a physiological saline solution, such that the water in the lens is in equilibrium with the surrounding water. Next the lens is gently blotted between two lint-free blotting cloths to remove surface moisture. The lens is quickly placed on an aluminum weighing pan and the first wet weight, W_1 , is measured. Next, the aluminum pan with lens is placed in a oven at 36°C for a period of at least 24 hours. After heat treating, the pan with lens is removed, placed in a desiccator, and allowed to cool to room temperature (about 22°C). The pan with lens is weighed again to determine the dry weight, W_d . The lens is re-equilibrated in physiological saline solution and a second wet weight W_2 is determined thereon. The wet weights (W_1 and W_2) are averaged to yield an average wet weight, W_w . The bulk water content is determined by the following equation:

$$\text{Percent water content} = (W_w - W_d) / W_w \times 100$$

A preferred lens bulk water content, determined by the "Bulk Technique", is less than about 32 weight percent. More preferably, the lens has a water content of about 10 to 30 weight percent, based on the total lens weight. A particularly preferred lens water content is about 15 to about 25 weight percent.

F. Ion and Water Permeability

Unexpectedly, it has been determined that the ion permeability through the lens correlates well with on-eye movement. As discussed earlier, it is known that on-eye movement of the lens is required to ensure good tear exchange, and ultimately, to ensure good corneal health. While the invention is not bound by theory presented herein, it may be useful to discuss some theory for a better understanding of ways to practice the invention.

It is theorized that water permeability is an exceptionally important feature for an extended-wear lens which includes oxypm polymers such as those disclosed herein. Siloxane-containing oxypm materials tend to adhere strongly to the eye, thereby stopping on-eye movement. The ability to pass water through the lens is believed to allow a siloxane-containing polymeric lens to move on the eye, where the movement occurs via forces exerted by water being squeezed out of the lens. The water permeability of the lens is also believed important in replenishing lens water content once pressure is removed. Further, the permeability of ions is believed to be directly proportional to the permeability of water. Thus, ion permeability is a predictor of on-eye movement.

However, regardless of whether the water permeability theory is a correct understanding of the actual on-eye movement phenomenon, it has been unexpectedly found that above a certain threshold of ion permeability through a lens, from the inner surface of the lens to the outer, or vice versa, the lens will move on the eye, and below the threshold the lens will adhere to the eye. Thus, the present innovative extended-wear contact lenses provide a balance between the relatively high oxygen permeability (and associated high binding capacity) of oxypm materials with the low binding capacity (high on-eye movement) of ionopm materials. It is believed that this is accomplished by providing a plurality of continuous ion transmission pathways for ion and water movement through the lens.

It should be noted that ions may move through the lens via these ion pathways by a number of means. For example, ions may diffuse through the lens because of concentration differences from one surface to another. Ions may also be forced through the ion pathways by the mechanical action of blinking, with the concomitant compression forces on the lens essentially squeezing water out of the lens. In addition, the charge nature of the surfaces may provide an electromotive force which drives ion permeation through the lens. At times, one of these driving forces may be larger than the others, while at other times the relative

magnitude may reverse. This discussion is presented to clarify that the invention is not restricted by the method or driving force by which ions move through the lens.

Neither the measurement of water permeability nor ion permeability through an ophthalmic lens is considered a routine matter of testing in the industry. Accordingly, a discussion of the preferred ion or water permeability ranges warrants a discussion of the measurement techniques used to determine the permeability.

The water permeability of a lens may be determined from the rate of water permeation through the lens, from one surface to another surface. The water permeability of a lens may be determined by positioning a lens between two reservoirs holding solutions having known, and different, initial concentrations of radiolabeled water (e.g., tritiated water), and then measuring concentration of radiolabeled water in the "receiving" reservoir (the reservoir towards which the net flow of radiolabeled water is positive) as a function of time.

The relative ion permeability of a lens may be determined from the rate of ion permeation through the lens, from one surface to another surface. The rate of ion permeation may be determined by positioning a lens between two reservoirs holding solutions having known, and different, initial ion concentrations, and then measuring conductivity in the "receiving" reservoir (the reservoir towards which the net flow of ions is positive) as a function of time. The concentration of ions, such as sodium, can be measured accurately using a pH meter and an ion-selective electrode. Ions are believed to be transmitted through a lens, from inner to outer surfaces and vice versa, primarily by the diffusion of ions through water pathways in the lens. Ion permeability through a lens is believed to be directly proportional to water permeability through a lens.

1. Ionoflux Measurement Technique

The following technique, referred to herein as the "Ionoflux Technique", is a preferred method for determining the ion permeability of a lens. This technique may be used to determine the likelihood of adequate on-eye movement.

The "Ionoflux Technique" involves the use of a conductometer (LF 2000/C, catalog no. 300105, Wissenschaftlich-Technische Werkstätten GmbH (WTW), Germany), an electrode equipped with a temperature sensor (LR 01/T, catalog no. 302 520, WTW), a donor chamber containing a salt solution, a receiving chamber containing about 60 ml of deionized water, a stir bar and a thermostat.

The donor chamber is specially designed for sealing a contact lens thereto, so that the donor solution does not pass around the lens (i.e., ions may only pass through the lens). The donor chamber is composed of a glass tube which is threaded at the end which is immersed in the receiving solution. The glass tube includes a centrally located hole of about 9 mm in diameter. A lid, which is threaded to mate with the glass tube, holds a lens-retaining member which includes a centrally located hole of about 8 mm in diameter. The lens-retaining member includes a male portion adapted to mate with and seal the edges of the inner (concave) surface of a lens and a female portion adapted to mate with and seal the edges of the outer (convex) surface of a lens.

The lens to be measured is placed in the lens-retaining member, between the male and female portions. The male and female portions include flexible sealing rings which are positioned between the lens and the respective male or female portion. After positioning the lens in the lens-retaining member, the lens-retaining member is placed in the threaded lid. The lid is screwed onto the glass tube to define the donor chamber. The donor chamber is filled with 16 ml of 0.1 molar NaCl solution. The receiving chamber is filled with 60 ml of deionized water. The leads of the conductivity meter are immersed in the deionized water of the receiving chamber and a stir bar is added to the receiving chamber. The receiving chamber is placed in a thermostat and the temperature is held at about 35°C. Finally, the donor chamber is immersed in the receiving chamber.

Measurements of conductivity are taken every 20 minutes for about three hours, starting 10 minutes after immersion of the donor chamber into the receiving chamber. The Ionoflux Diffusion Coefficient, D , is determined by applying Fick's law as follows:

$$D = -n' / (A \times dc/dx)$$

where n' = rate of ion transport [mol/min]
 A = area of lens exposed [mm²]
 D = Ionoflux Diffusion Coefficient [mm²/min]
 dc = concentration difference [mol/L]
 dx = thickness of lens [mm]

An Ionoflux Diffusion Coefficient of greater than about 6.4×10^{-6} mm²/min is preferred for achieving sufficient on-eye movement. More preferably, the Ionoflux Diffusion Coefficient is greater than about 2.6×10^{-6} mm²/min, while most preferably, the Ionoflux Diffusion Coefficient is greater than about 1.5×10^{-6} mm²/min. It must be emphasized that the

Ionoflux Diffusion Coefficient correlates with ion permeability through the lens, and thereby is a predictor of on-eye movement.

2. Ionoton Measurement Technique

The following technique, referred to herein as the "Ionoton Technique", is another preferred method for determining the relative ion permeability of a lens. The technique is based on measurement of the diffusion of sodium chloride through a lens.

The "Ionoton Technique" involves the use of a pH meter (Beckman, VWR catalog no. BK123142), a VSC-1 Diffusion Cell Drive Console (Crown-Bio, Somerville, NJ), a DCB-100B Diffusion Cell (Crown-Bio), and a 6 cm sodium ion-specific electrode (Microelectronics, Londonderry, NH, catalog no. MI-414P). The technique is not limited to the aforementioned instruments or materials; equivalent instruments or materials may be used.

First, a contact lens is mounted onto an orifice of the DCB-100B cell chamber, the donor chamber. Next, the connecting cell chamber (receptor chamber) is placed against the cell chamber containing the contact lens and tightly clamped on the clamp holder supplied with the VSC-1 Drive Console. Then, a phosphate-buffered saline (PBS, Mediatech catalog no. 21-031-LV) is placed into the receptor side of the cell chamber. Stir bars are added to each cell chamber. The 6 cm electrode is placed into the PBS saline receptor side. After the electrode has equilibrated in the PBS saline, the pH meter is placed in the mV function to establish the 0 mV point. PBS which has been saturated with sodium chloride is added to the donor chamber.

The millivolt signal is recorded at 5, 10, 15, 30, 60, 120, and 180 minute intervals. The millivolt signal is converted to a sodium ion concentration by a standard curve of sodium ion concentration vs. millivolt signal. The Ionoton Ion Permeability Coefficient, P, is then determined in accordance with the following equation:

$$\ln(1 - 2C(t)/C(0)) = -2APt / Vd$$

where: C(t) = concentration of sodium ions at time t in the receiving cell
 C(0) = initial concentration of sodium ions in donor cell
 A = membrane area, i.e., lens area exposed to cells
 V = volume of cell compartment (3.0 ml)
 d = average lens thickness in the area exposed
 P = permeability coefficient

The average thickness of the lens in the exposed test area may be determined by averaging a number of readings, e.g., 10 readings, with a low-pressure thickness-measuring instrument, such as a Mitotoya micrometer VL-50, or equivalents thereof. The Ionoton Ion Permeability Coefficient, P , having units of $\text{cm}^2/\text{second}$, may be determined from the slope of a plot of time (t) v. $\ln(1 - 2C(t)/C(0)) \times (-2At / Vd)$.

An Ionoton Ion Permeability Coefficient, P , of greater than about $0.2 \times 10^{-6} \text{ cm}^2/\text{sec}$ is preferred, while greater than about $0.3 \times 10^{-6} \text{ cm}^2/\text{sec}$ is more preferred and greater than about $0.4 \times 10^{-6} \text{ cm}^2/\text{sec}$ is most preferred. It must be emphasized that the Ionoton Ion Permeability Coefficient correlates with ion permeability through the lens, and thereby is a predictor of on-eye movement.

3. Hydrodell Water Permeability Technique

The following technique, referred to herein as the "Hydrodell Technique", is a preferred method for determining the water permeability of a lens. This technique may be used to determine the likelihood of adequate on-eye movement.

The Hydrodell Technique involves the measurement of the rate of transfer of the radiolabeled solutes THO (^3H -HO or tritiated water) and ^{14}C -glucose across the contact lens using a two-chamber apparatus. ^{14}C -glucose is used in this measurement technique to reveal any leak in the system during testing. The lens is mounted between chambers, which are stirred at a controllable rate. Chamber I contains a solution with a high concentration of labeled solute. Chamber II, the "receiving chamber", contains an identical solution but without the labeled solute. Samples of the solution in chambers I and II are taken at intervals over the test period. The radioactivity in the samples is measured. The permeability of the lens is calculated from the measured radioactivity, the sample times, the chamber volumes and the lens area exposed to the solutions. A more detailed description of the Hydrodell Technique follows.

a. Solution Preparation

Dulbecco's phosphate buffered saline (DPBS) is prepared by first dissolving, sequentially, about 160 g sodium chloride (NaCl), about 4 grams potassium chloride (KCl), about 23 grams disodium hydrogen orthophosphate (Na_2HPO_4), about 4 grams potassium dihydrogen orthophosphate (KH_2PO_4), and about 10 grams sodium azide in a liter of reverse-osmosis (MilliQ) water. Then, the pH is adjusted to about 7.3 by adding appropriate

amounts of HCl. Finally, the buffer solution is diluted to 1:20 (50 ml buffer solution with 950 ml reverse-osmosis water) and allowed to degas either in a screw-capped container overnight or under vacuum.

A Cold Glucose buffer solution is prepared by adding about 0.1 grams D-glucose to one liter of DPBS, followed by sterilization via filtration through a 0.2 μ l millipore filter and storage at 4°C until use.

The Chamber I solution is prepared by adding about 6 μ l THO (TR53, 1.0 mCi/ml activity, available from Amersham Australia, located in North Ryde NSW Australia) and about 16 μ l 14 C-glucose (in ethanol, available from Amersham Australia) to about 12 ml of the Cold Glucose buffer solution. Preferably, this solution is used within about 24 hours of preparation. The Chamber II solution is DPBS.

b. Apparatus Preparation

The chambers have a volume sufficient to hold about 12 ml of solution during testing. While the exact shape of the chambers is not critical, both chambers have rectangular cross-sections for ease of construction. The chambers may be made from a variety of water-proof rigid materials, preferably clear (e.g., acrylic plates, FX Plastics, Marrickville NSW Australia) so that samples may be observed during testing. Each chamber has a circular aperture of about 7 mm diameter appropriate for mounting a lens between the chambers for contact with solutions held within the chambers. Some affixing means, such as a set of mounting bolts, are necessary to securely affix one chamber to the other with the lens mounted in between.

A test contact lens is mounted symmetrically over the aperture of Chamber II. Folds and wrinkles are manually removed from the lens. Chamber I is positioned adjacent the aperture and mounted lens of Chamber II, and the chambers are secured to one another using mounting bolts.

About 12 ml (V_2) of DPBS is placed in Chamber II. About 12 ml of the Chamber I labeled solution is placed in Chamber I, at which point time $t=0$ is established. Stirrers are added to both chambers and the stirrer speed is set at about 1200 rpm.

c. Sampling

Sampling generally starts at time $t_0 = 5$ minutes. The final sample time, t_f , is usually at about 50 minutes for high water content lenses and about 120 minutes for low water content lenses, although these times are not critical.

At time $t_0 = 5$ minutes, two samples of about 0.2 ml volume are pipetted from Chamber I, and two 0.2 ml aliquots of DPBS are added to Chamber I to restore the volume. These samples are placed into plastic counting tubes with about 4 ml Ultima Gold™ cocktail (available from Packard Instrument Co., Meriden, Connecticut) and about 0.9 ml DPBS.

Also at time t_0 , one sample of about 1.0 ml volume is pipetted from Chamber II and one 1.0 ml aliquot of DPBS is added to Chamber II to restore the volume. The sample is placed into a plastic counting tube with about 4 ml Ultima Gold™ cocktail.

At intermediate times between t_0 and t_f (e.g., every 10 minutes), one sample of about 1.0 ml volume is pipetted from Chamber II and one 1.0 ml aliquot of DPBS is added to Chamber II to restore the volume. Each sample is placed into a plastic counting tube with about 4 ml Ultima Gold™ cocktail.

At time t_f , two samples of about 0.2 ml volume are pipetted from Chamber I. These samples are placed into plastic counting tubes with about 4 ml Ultima Gold™ cocktail and about 0.9 ml DPBS.

Also at time t_f , two samples of about 1.0 ml volume are pipetted from Chamber II. These samples are placed into plastic counting tubes with about 4 ml Ultima Gold™ cocktail.

d. Measurements

The activity of the samples are measured by liquid scintillation counting, or other appropriate technique. Liquid scintillation counting may be advantageously accomplished by using protocol number 6 for $^3\text{H}/^{14}\text{C}$ on a Tri-Carb Liquid Scintillation Analyzer (1900TR, available from Packard Instrument Co.).

Three standards containing about 10^4 to 10^5 cpm THO in reversed-osmosis (MilliQ) water are prepared. Three standards containing about 10^4 to 10^5 cpm ^{14}C glucose in reversed-osmosis (MilliQ) water are also prepared. A blank containing MilliQ water is prepared.

The scintillation analyzer settings are LLA = 0 KeV and ULA = 12 KeV for ^3H ("1") in channel 1 and LLB = 12 KeV and ULB = 156 KeV for ^{14}C ("2") in channel 2. The standards and blank are counted three times during each counting of samples, and the counts are averaged. The following denote the relevant measured sample activities:

- b_1 = measured activity of blank sample in channel 1
- b_2 = measured activity of blank sample in channel 2
- S'_{11} = measured activity of standard ^3H sample in channel 1
- S'_{12} = measured activity of standard ^{14}C sample in channel 2
- S'_{21} = measured activity of standard ^3H sample in channel 1
- S'_{22} = measured activity of standard ^{14}C sample in channel 2
- y_1 = measured activity of test sample (both ^3H and ^{14}C) in channel 1
- y_2 = measured activity of test sample (both ^3H and ^{14}C) in channel 2

e. Water Permeability Calculation

In order to calculate the actual activity of a sample, the measured activities of the isotopes, ^3H and ^{14}C , must first be corrected to remove the cross-contamination error due to the presence of both isotopes in one sample. Without explaining the mathematical derivations, the following stepwise procedure is offered as an example of one method of determining water permeability from the above measurements:

- (1) Calculate S_{11} , S_{12} , S_{21} , and S_{22} , from the following equations:

$$S_{11} = S'_{11} - b_1$$

$$S_{12} = S'_{12} - b_1$$

$$S_{21} = S'_{21} - b_2$$

$$S_{22} = S'_{22} - b_2$$

- (2) Calculate a_{12} and a_{21} from the following equations:

$$a_{12} = S_{12} / S_{22}$$

$$a_{21} = S_{21} / S_{11}$$

- (3) Calculate corrected concentrations of ^3H ("1") and ^{14}C ("2") from the following equations:

$$c_1 = [(y_1 - b_1) - a_{12} (y_2 - b_2)] / (1 - a_{12} a_{21})V$$

$$c_2 = [(y_2 - b_2) - a_{21} (y_1 - b_1)] / (1 - a_{12} a_{21})V$$

where V is the volume of the test sample.

- (4) Calculate water permeability for an interval from t_1 to t_2 as follows:

$$P = V_{II} [c_{II}(t_2) - c_{II}(t_1)] / A(c_I - c_{II})(t_1 - t_2)$$

where V_{II} is the volume of Chamber II, $c_{II}(t_2)$ is the concentration of ^3H in Chamber II at time t_2 , $c_{II}(t_1)$ is the concentration of ^3H in Chamber II at time t_1 , A is the area of lens exposure, c_I is the average concentration of ^3H in Chamber I over the time period t_1 to t_2 and c_{II} is the average concentration of ^3H in Chamber II over the time period t_1 to t_2 .

The ophthalmic lenses of one embodiment of the present invention have a Hydrodell Water Permeability Coefficient of greater than about $0.2 \times 10^{-6} \text{ cm}^2/\text{sec}$. The ophthalmic lenses in a preferred embodiment of the invention have Hydrodell Water Permeability Coefficient of greater than about $0.3 \times 10^{-6} \text{ cm}^2/\text{sec}$. The ophthalmic lenses in a preferred embodiment of the invention have Hydrodell Water Permeability Coefficient of greater than about $0.4 \times 10^{-6} \text{ cm}^2/\text{sec}$.

G. Oxygen Transmissibility and Permeability

As mentioned earlier, the cornea receives oxygen primarily from the corneal surface which is exposed to the environment, in contrast to other tissues which receives oxygen from blood flow. Thus, an ophthalmic lens which may be worn on the eye for extended periods of time must allow sufficient oxygen to permeate through the lens to the cornea to sustain corneal health. One result of the cornea receiving an inadequate amount of oxygen is that the cornea will swell. In a preferred embodiment, the oxygen transmissibility of the present ophthalmic lenses is sufficient to prevent any clinically significant amount of corneal swelling from occurring.

A preferred ophthalmic lens material will have an oxygen transmissibility, Dk/t , of at least 70 $(\text{cm}^3 \text{ oxygen})(\text{mm})/\text{mm-cm}^2 \times (\text{sec}/\text{mm Hg}) \times 10^{-9}$ or [barrers/mm], more preferably at least 75 barrers/mm, and most preferably at least 87 barrers/mm.

The oxygen permeability of a lens and oxygen transmissibility of a lens material may be determined by the following technique. Oxygen fluxes (J) are measured at 34°C in a wet cell (i.e., gas streams are maintained at about 100% relative humidity) using a Dk1000 instrument (available from Applied Design and Development Co., Norcross, Georgia), or

similar analytical instrument. An air stream, having a known percentage of oxygen (e.g., 21%), is passed across one side of the lens at a rate of about 10 to 20 cm³/min., while a nitrogen stream is passed on the opposite side of the lens at a rate of about 10 to 20 cm³/min. The barometric pressure surrounding the system, P_{measured} , is measured. The thickness (t) of the lens in the area being exposed for testing is determined by measuring about 10 locations with a Mitotoya micrometer VL-50, or similar instrument, and averaging the measurements. The oxygen concentration in the nitrogen stream (i.e., oxygen which diffuses through the lens) is measured using the DK1000 instrument. The oxygen permeability of the lens material, D_k , is determined from the following formula:

$$D_k = Jt/(P_{\text{oxygen}})$$

where J = oxygen flux [microliters O₂/cm²-minute]

$$P_{\text{oxygen}} = (P_{\text{measured}} - P_{\text{water vapor}}) \times (\%O_2 \text{ in air stream}) \text{ [mm Hg]}$$

= partial pressure of oxygen in the air stream

$$P_{\text{measured}} = \text{barometric pressure [mm Hg]}$$

$$P_{\text{water vapor}} = 0 \text{ mm Hg at } 34^\circ\text{C (in a dry cell) [mm Hg]}$$

$$P_{\text{water vapor}} = 40 \text{ mm Hg at } 34^\circ\text{C (in a wet cell) [mm Hg]}$$

$$t = \text{average thickness of the lens over the exposed test area [mm]}$$

where D_k is expressed in units of barrers,

$$\text{i.e., } [(cc \text{ oxygen})(mm)/cm^2] \times [sec/mm Hg] \times 10^{-10}.$$

The oxygen transmissibility (D_k/t) of the material may be calculated by dividing the oxygen permeability (D_k) by the average thickness (t) of the lens.

H. Mechanical On-eye Movement Parameters

On-eye movement of a lens may be predicted from the mechanical properties of a lens, the ion or water permeability through the lens, or both the mechanical properties and ion or water permeability. In fact, on-eye movement may be predicted more accurately from a combination of mechanical properties and ion or water permeability.

1. Tensile Modulus and Short Relaxation Time

Tensile mechanical testing may be performed on lens materials to determine mechanical properties. A procedure for preparing a test sample from a lens for subsequent mechanical testing includes the following steps:

1. Cut a parallel-sided strip through the center of the lens. A suitable width for the strip is about 3.1 mm.
2. Immerse the test strip in a phosphate-buffered saline solution (approximating ocular fluid osmolality) for a period of about 24 hours before testing.
3. Conduct mechanical testing with the test strip immersed in phosphate-buffered saline at ambient temperature (about 23°C).

Tensile modulus may be measured by applying a strain rate of about 100% per minute to the test strip and recording the resultant stress. However, the procedure may be used at differing strain rates.

Stress relaxation is measured by applying a constant strain of about 5% to the test strip and recording the resultant stress for about 5 minutes. A useful mechanical testing instrument for this type of testing is the Vitrodyne V-200 from Liveco Biomechanical Instruments, located in Burlington, Vermont.

In order to analyze stress relaxation data, a three element Maxwell-Wiechert model (a spring and two spring-dashpot elements in parallel) may be assumed for the polymer material. For this model the stress relaxation modulus is given by the following equation:

$$E(t) = E_0 + E_1 \exp(-t/\tau_1) + E_2 \exp(-t/\tau_2)$$

Stress v. time curves may be normalized to the maximum (initial) stress induced in the samples. These curves may be analyzed by a variety of commercially available software (for example, ORIGIN software) by fitting the double exponential equation:

$$y(t) = y_0 + A_1 \exp(-t/\tau_1) + A_2 \exp(-t/\tau_2)$$

in order to obtain the stress relaxation parameters y_0 , τ_1 , A_1 , τ_2 , and A_2 .

It has been determined that the tensile modulus (modulus of elasticity, E) and the short relaxation time constant (τ_1) correlate well with on-eye movement. In order to have appropriate on-eye movement, a lens preferably has a tensile modulus of less than about 3 MPa. More preferably, E is about 0.4 to about 2.5 MPa while a particularly preferred E is about 0.5 to about 1.5 MPa.

A preferred short relaxation time constant (τ_1) is greater than about 3.5 seconds. More preferably, τ_1 is greater than about 4 seconds, while a particularly preferred τ_1 is greater than about 4.5 seconds.

2. Tangent Delta

Lenses may also be evaluated by dynamic mechanical analysis (DMA) methods. It has been determined that a factor known as $\tan \delta$ (i.e., tangent delta), also known as mechanical loss factor, correlates well with on-eye movement. It has been observed that lens materials which move on the eye exhibit a distinct increase in $\tan \delta$ with increasing frequency from about 0.1 to 10 Hz when these materials are tested by dynamic mechanical analysis. The $\tan \delta$ of a preferred lens material is above about 0.2 at 0.1 Hz and increases to about 0.25 or more at about 10 Hz. A $\tan \delta$ of about 0.3 or greater at 10 Hz is more preferred, while a $\tan \delta$ of about 0.5 or greater at 10 Hz is even more preferred.

DMA measurements may be determined in accordance with the following procedure. A disk of lens material having a diameter of about 3.0 mm and a thickness of about 0.50 mm is formed. The disk is placed in a Perkin-Elmer DMA-7 instrument. The disk is immersed in a solution buffered to a pH of about 7.2 and held isothermally for a period of about 10 minutes or more prior to testing, at a temperature of about 23 to 35°C. The instrument is set to a compression measuring mode and the strain on the sample is adjusted to about 2% to 4%, depending on the sample response. The amplitude of compression is about 2 to 4 μm . Measurements of the modulus of elasticity and $\tan \delta$ are taken at frequencies of about 0.1, about 1, and about 10 Hz.

3. Parameter Combinations

In order to assure appropriate movement of the lens on the eye, one may select materials which have a combination of the above-discussed properties. Therefore, a preferred group of extended-wear contact lens materials have (a) a modulus of elasticity (E) of about 1.5 MPa or less, (b) a short time relaxation constant (t_1) of greater than about 4 seconds, and (c) an Ionoton Ion Permeability Coefficient of greater than about $0.3 \times 10^{-6} \text{ cm}^2/\text{sec}$ and/or an Ionoflux Diffusion Coefficient greater than about $6.4 \times 10^{-6} \text{ mm}^2/\text{min}$.

I. Examples of Suitable Materials

1. Material "A"

One embodiment of a suitable core material of the present ophthalmic lenses is a copolymer formed from the following monomeric and macromeric components:

(a) about 5 to about 94 dry weight percent of a macromer having the segment of the formula



- 26 -

where PDMS is a divalent poly(disubstituted siloxane),

ALK is an alkylene or alkyleneoxy group having at least 3 carbon atoms,

DU is a diurethane-containing group,

PAO is a divalent polyoxyalkylene, and

CP is selected from acrylates and methacrylates,

wherein said macromer has a number-average molecular weight of 2000 to 10,000;

(b) about 5 to about 60 weight percent methacryloxypropyltris(trimethylsiloxy)silane;

(c) about 1 to about 30 weight percent of an acrylate or methacrylate monomer; and

(d) 0 to 5 weight percent cross-linking agent,

with the weight percentages being based upon the dry weight of the polymer components.

A preferred polysiloxane macromer segment is defined by the formula



where PDMS is a divalent poly(disubstituted siloxane);

CP is an isocyanatoalkyl acrylate or methacrylate, preferably isocyanatoethyl methacrylate,

where the urethane group is bonded to the terminal carbon on the PAO group;

PAO is a divalent polyoxyalkylene (which may be substituted), and is preferably a polyethylene oxide, i.e., $(-\text{CH}_2-\text{CH}_2-\text{O}-)_m\text{CH}_2\text{CH}_2-$ where m may range from about 3 to about 44, more preferably about 4 to about 24;

DU is a diurethane, preferably including a cyclic structure,


where an oxygen of the urethane linkage (1) is bonded to the PAO group and an oxygen of the urethane linkage (2) is bonded to the ALK group;

and ALK is an alkylene or alkyleneoxy group having at least 3 carbon atoms, preferably a branched alkylene group or an alkyleneoxy group having 3 to 6 carbon atoms, and most preferably a sec-butyl (i.e., $-\text{CH}_2\text{CH}_2\text{CH}(\text{CH}_3)-$) group or an ethoxypropoxy group (e.g., $-\text{O}-(\text{CH}_2)_2-\text{O}-(\text{CH}_2)_3-$).

It will be noted that the DU group can be formed from a wide variety of diisocyanates or triisocyanates, including aliphatic, cycloaliphatic or aromatic polyisocyanates. These isocyanates include, without limitation thereto, ethylene diisocyanate; 1,2-diisocyanatopropane; 1,3-diisocyanatopropane; 1,6-diisocyanatohexane; 1,2-diisocyanatocyclohexane; 1,3-diisocyanatocyclohexane; 1,4-diisocyanatobenzene, bis(4-isocyanatocyclohexyl)methane; bis(4-isocyanatocyclohexyl)methane, bis(4-isocyanatophenyl)methane; 1,2- and 1,4-toluene diisocyanate; 3,3-dichloro-4,4'-

diisocyanatobiphenyl; tris(4-isocyanatophenyl)methane; 1,5-diisocyanatonaphthalene; hydrogenated toluene diisocyanate; 1-isocyanatomethyl-5-isocyanato-1,3,3-trimethylcyclohexane (i.e., isophorone diisocyanate); 1,3,5-tris(6-isocyanatohexyl) biuret; 1,6-diisocyanato-2,2,4-(2,4,4)-trimethylhexane; 2,2'-diisocyanatodiethyl fumarate; 1,5-diisocyanato-1-carboxypentane; 1,2-, 1,3-, 1,6-, 1,7-, 1,8-, 2,7- and 2,3-diisocyanatonaphthalene; 2,4- and 2,7-diisocyanato-1-methylnaphthalene; 1,4-diisocyanatomethylcyclohexane; 1,3-diisocyanato-6(7)-methylnaphthalene; 4,4'-diisocyanatobiphenyl; 4,4'-diisocyanato-3,3'-dimethoxybisphenyl; 3,3'- and 4,4'-diisocyanato-2,2'-dimethylbisphenyl; bis(4-isocyanatophenyl) ethane; bis(4-isocyanatophenyl ether); 1,2- or 1,4-toluene diisocyanate; and mixtures thereof. Preferably DU is formed from isophorone diisocyanate or toluene diisocyanate, and more preferably, isophorone diisocyanate, where one isomeric diurethane structure of isophorone diisocyanate is defined above.

A preferred Material A macromer segment has the following formula:



wherein:

R_1 and R_2 are lower alkyl (C_1 - C_6), preferably C_1 - C_3 alkyl, more preferably methyl;
 R_3 , R_4 , R_5 , and R_6 are lower alkylene (C_1 - C_6), preferably C_1 - C_3 alkylene, more preferably C_2 - C_3 alkylene, and preferably, where the total number of carbon atoms in R_3 and R_5 , or R_4 and R_6 is greater than 4;

R_7 and R_8 are linear or branched alkylene or a bivalent cycloalkylene, preferably bivalent cycloalkylene;

R_9 , R_{10} , R_{11} , and R_{12} are C_1 - C_2 alkylene, preferably C_2 alkylene;

R_{13} and R_{14} are lower alkylene (C_1 - C_6), preferably C_1 - C_3 alkylene, more preferably ethylene;

and

R_{15} and R_{16} are linear or branched lower alkenylene, preferably C_2 - C_3 alkenylene;

m and p, independently of one another, may range from about 3 to about 44, more preferably about 4 to about 24; and n may range from about 13 to about 80, more preferably, about 20 to about 50, and even more preferably about 24 to about 30.

The polysiloxane macromer may be synthesized by the following preferred process. At about room temperature (about 20-25°C), poly(dimethylsiloxane) dialkanol having hydroxyalkyl (e.g., hydroxy-sec-butyl) or hydroxyalkoxy (e.g., hydroxyethylpropoxy) end groups and having a molecular weight of about 2000 to 3000 (preferably about 2200, i.e., having about 28 repeating siloxane groups) is reacted with isophorone diisocyanate at about a 1:2 molar ratio, using about 0.2 weight percent (based on polydimethylsiloxane) dibutyltin dilaurate added as a catalyst. The reaction is carried out for about 36 to 60 hours. To this mixture is added poly(ethylene glycol) having a molecular weight of about 400 to 1200 (more preferably about 500 to 700) at about a 2:1 or 2.1:1 molar ratio with respect to the PDMS, about 0.4 to 0.5 weight percent dibutyltin dilaurate (based on polyethylene glycol weight), and chloroform sufficient to ensure substantial mixture homogeneity. The mixture is agitated for about 12 to 18 hours, then held at a temperature of about 44 to 48°C for about 6 to 10 hours. Excess chloroform is evaporated therefrom at about room temperature to produce a composition having about 50 weight percent solids. Then, isocyanatoethyl methacrylate is added to the mixture in about a 2:1 to 2.3:1 molar ratio with respect to PDMS. The mixture is agitated at room temperature for about 15 to 20 hours. The resulting solution contains a polysiloxane macromer having the composition described above and a number-average molecular weight of about 2000 to 10,000, more preferably about 3000 to 5000.

An advantageous polymeric material formed from the Material A macromer of the present invention is a copolymer of the aforementioned Material A macromer; an acrylated or methacrylated siloxane monomer, preferably methacryloxypropyltris (trimethylsiloxy) silane (referred to herein as "Tris"); a hydrophilic monomer, preferably 2-hydroxyethyl methacrylate (HEMA); and preferably, a cross-linking agent such as ethylene glycol dimethacrylate (EGDMA). The final copolymer composition includes about 10 to 90, preferably 70 to 90, weight percent polysiloxane macromer; about 5 to 60, preferably about 8 to 20, weight percent siloxane monomer; about 1 to 30, preferably about 1 to 5, weight percent acrylate or methacrylate monomer; and 0 to about 5, preferably up to about 2 weight percent cross-linking agent (e.g., EGDMA) based on a total dry copolymer weight. A more preferred composition includes about 80 to 84 polysiloxane macromer, about 12 to 15 weight percent

TRIS, about 3 to about 4 weight percent 2-hydroxyethyl methacrylate, and about 0.7 to about 1.2 weight percent ethylene glycol dimethacrylate.

The advantageous copolymers of the present invention may be formed from the previously-described polysiloxane macromer in the following manner. A monomeric solution is formed by adding Tris, HEMA, DAROCUR® 1173 (a photoinitiator available from Ciba-Geigy Corporation), and optionally, EGDMA to the polysiloxane macromer solution. The resulting polymer precursor solution preferably contains about 83 to about 95 weight percent polysiloxane macromer solution; about 5 to about 10 weight percent Tris, about 0.5 to about 5 weight percent HEMA, about 0.1 to about 1.0 weight percent DAROCUR® 1173, and about 0.1 to about 1.0 weight percent EGDMA. More preferably, the monomer solution contains about 87 to about 93 weight percent polysiloxane macromer solution, about 7 to about 8 weight percent Tris, about 2 to about 4 weight percent HEMA, about 0.3 to about 0.7 weight percent DAROCUR® 1173, and about 0.3 to about 0.7 weight percent EGDMA. The monomer solution is preferably agitated for about 8 to about 24 hours prior to the polymerization step.

Contact lenses may be prepared from the monomer solution by applying the monomer solution to appropriate lens molds and applying sufficient ultraviolet (UV) radiation to initiate polymerization. The ultraviolet light may be applied for a period of a few minutes to about 5 hours, depending on the intensity of light applied. Subsequent to polymerization, the contact lens may be extracted with a solvent, e.g., isopropanol, to remove unreacted monomers.

Thus, generally, one embodiment of the present invention is a method of forming a molded polymeric article suitable for ophthalmic applications (especially a contact lens), including the following steps:

- (a) contacting a poly(dialkylsiloxane) dialkanol with a diisocyanate compound in the presence of a first catalyst at conditions sufficient to cause reaction of said dialkanol with said diisocyanate, thereby forming a first mixture;
- (b) contacting said first mixture with poly(alkylene glycol), a second catalyst, and sufficient solvent to ensure mixture homogeneity, thereby forming a second mixture;
- (c) evaporating sufficient solvent from said second mixture to generate a third mixture having a solids content of about 40 to 60 weight percent;
- (d) adding isocyanatoalkyl methacrylate to said third mixture, thereby forming a fourth mixture containing a polysiloxane macromer;

- 30 -

(e) adding to said fourth mixture 3-methacryloxypropyltris(trimethylsiloxy)silane (TRIS), a hydrophilic monomer, a cross-linking agent and a photoinitiator, thereby forming a fifth mixture;


(f) placing said fifth mixture into a mold; and

(g) applying sufficient radiation to copolymerize said monomers, thereby forming said polymeric material into a molded polymeric article.

The hydrophilic copolymers of the present invention are especially advantageous in the formation of "soft" contact lenses. In the use of the copolymers in the contact lens field, the lenses have a water content of about 10 to about 50 weight percent, more preferably about 10 to about 30 weight percent, and most preferably about 15 to about 22 weight percent, based on total hydrophilic polymer weight. Preferably, the fully-hydrated contact lens has an oxygen transmissibility (D_k/t) of greater than 70 barrers/mm (i.e., $[(\text{cc oxygen})(\text{mm})/\text{cm}^2] \times [\text{sec}/\text{mm Hg}] \times 10^{-10}$), more preferably greater than about 75 barrers/mm, and most preferably greater than about 87 barrers/mm.

2. Material "B" (Polysiloxane-comprising perfluoroalkyl ethers)

The Material "B" macromer is defined by formula (I):



where each P_1 , independently of the others, is a free-radical-polymerizable group;


each Y , independently of the others, is $-\text{CONHCOO}-$, $-\text{CONHCONH}-$, $-\text{OCONHCO}-$, $-\text{NHCONHCO}-$, $-\text{NHCO}-$, $-\text{CONH}-$, $-\text{NHCONH}-$, $-\text{COO}-$, $-\text{OCO}-$, $-\text{NHCOO}-$ or $-\text{OCONH}-$;

m and p , independently of one another, are 0 or 1;

each L , independently of the others, is a divalent radical of an organic compound having up to 20 carbon atoms;

each X_1 , independently of the others, is $-\text{NHCO}-$, $-\text{CONH}-$, $-\text{NHCONH}-$, $-\text{COO}-$, $-\text{OCO}-$, $-\text{NHCOO}-$ or $-\text{OCONH}-$; and

Q is a bivalent polymer fragment consisting of the segments:




where $x+y$ is a number in the range of 10 to 30;

each Z, independently of the others, is a divalent radical having up to 12 carbon atoms or Z is a bond;

each E, independently of the others, is $-(OCH_2CH_2)_q-$, where q has a value of from 0 to 2,

and where the link -Z-E- represents the sequence $-Z-(OCH_2CH_2)_q-$; and

k is 0 or 1;



where n is an integer from 5 to 100;

Alk is alkylene having up to 20 carbon atoms;

80-100% of the radicals R_1 , R_2 , R_3 and R_4 , independently of one another, are alkyl and

0-20% of the radicals R_1 , R_2 , R_3 and R_4 , independently of one another, are alkenyl, aryl or cyanoalkyl; and



where R is a divalent organic radical having up to 20 carbon atoms, and

each X_2 , independently of the others, is $-\text{NHCO}-$, $-\text{CONH}-$, $-\text{NHCONH}-$, $-\text{COO}-$, $-\text{OCO}-$, $-\text{NHCOO}-$ or $\text{OCONH}-$;

with the provisos that there must be at least one of each segment (a), (b), and (c) in Q, that each segment (a) or (b) has a segment (c) attached to it, and that each segment (c) has a segment (a) or (b) attached to it.

The number of segments (b) in the polymer fragment Q is preferably greater than or equal to the number of segments (a). The ratio between the number of segments (a) and (b) in the polymer fragment Q is preferably 3:4, 2:3, 1:2 or 1:1. The molar ratio between the number of segments (a) and (b) in the polymer fragment Q is more preferably 2:3, 1:2 or 1:1.

The mean molecular weight of the polymer fragment Q is in the range of about 1000 to about 20000, preferably in the range of about 3000 to about 15000, particularly preferably in the range of about 5000 to about 12000.

The total number of segments (a) and (b) in the polymer fragment Q is preferably in the range of 2 to about 11, particularly preferably in the range of 2 to about 9, and in particular

in the range of 2 to about 7. The smallest polymer unit Q is preferably composed of one perfluoro segment (a), one siloxane segment (b) and one segment (c).

In a preferred embodiment of the polymer fragment Q, which preferably has a composition in the abovementioned ratios, the polymer fragment Q is terminated at each end by a siloxane segment (b).

The compositions in a bivalent polymer fragment Q always correspond above and below to a mean statistical composition. This means that, for example, even individual block copolymer radicals containing identical recurring units are included, so long as the final mean statistical composition is as specified.

X_1 is preferably -NHCONH-, -NHCOO- or -OCONH-, particularly preferably -NHCOO- or -OCONH-.

The X_2 -R- X_2 segment is preferably a radical derived from a diisocyanate, where each X_2 , independently of the other, is NHCONH-, -NHCOO- or -OCONH-, in particular -NHCOO- or -OCONH-.

Z is preferably a bond, lower alkylene or -CONH-arylene, in which the -CO- moiety is linked to a CF_2 group. Z is particularly preferably lower alkylene, in particular methylene.

q is preferably 0, 1, 1.5 or 2, particularly preferably 0 or 1.5.

The perfluoroalkoxy units OCF_2 and OCF_2CF_2 with the indices x and y in segment (a) can either have a random distribution or be in the form of blocks in a chain. The sum of the indices x+y is preferably a number in the range of 10 to 25, particularly preferably of 10 to 15. The ratio x:y is preferably in the range of 0.5 to 1.5, in particular in the range of 0.7 to 1.1.

A free-radical-polymerizable group P_1 is, for example, alkenyl, alkenylaryl or alkenylarylenealkyl having up to 20 carbon atoms. Examples of alkenyl are vinyl, allyl, 1-propen-2-yl, 1-buten-2-, -3- and -4-yl, 2-buten-3-yl, and the isomers of pentenyl, hexenyl, octenyl, decenyl and undecenyl. Examples of alkenylaryl are vinylphenyl, vinylnaphthyl or allylphenyl. An example of alkenylarylenealkyl is o-, m-, or p-vinylbenzyl.

P_i is preferably alkenyl or alkenylaryl having up to 12 carbon atoms, particularly preferably alkenyl having up to 8 carbon atoms, in particular alkenyl having up to 4 carbon atoms.

Y is preferably -COO-, -OCO-, -NHCONH-, -NHCOO-, -OCONH-, NHCO- or -CONH-, particularly preferably -COO-, -OCO-, NHCO- or -CONH-, and in particular, -COO- or -OCO-.

In a preferred embodiment, the indices, m and p, are not simultaneously zero. If p is zero, m is preferably 1.

L is preferably alkylene, arylene, a saturated bivalent cycloaliphatic group having 6 to 20 carbon atoms, arylenealkylene, alkylenearylene, alkylenearylenealkylene or arylenealkylenearylene.

Preferably, L is a divalent radical having up to 12 carbon atoms, particularly preferably a divalent radical having up to 8 carbon atoms. In a preferred embodiment, L is furthermore alkylene or arylene having up to 12 carbon atoms. A particularly preferred embodiment of L is lower alkylene, in particular lower alkylene having up to 4 carbon atoms.

The divalent radical R is, for example, alkylene, arylene, alkylenearylene, arylenealkylene or arylenealkylenearylene having up to 20 carbon atoms, a saturated bivalent cycloaliphatic group having 6 to 20 carbon atoms or cycloalkylenealkylenecycloalkylene having 7 to 20 carbon atoms.

In a preferred embodiment, R is alkylene, arylene, alkylenearylene, arylenealkylene or arylenealkylenearylene having up to 14 carbon atoms or a saturated divalent cycloaliphatic group having 6 to 14 carbon atoms. In a particularly preferred embodiment, R is alkylene or arylene having up to 12 carbon atoms or a saturated bivalent cycloaliphatic group having 6 to 14 carbon atoms.

In a preferred embodiment, R is alkylene or arylene having up to 10 carbon atoms or a saturated bivalent cycloaliphatic group having 6 to 10 carbon atoms.

In a particularly preferred meaning, R is a radical derived from a diisocyanate, for example from hexane 1,6-diisocyanate, 2,2,4-trimethylhexane 1,6-diisocyanate, tetramethylene diisocyanate, phenylene 1,4-diisocyanate, toluene 2,4-diisocyanate, toluene 2,6-

diisocyanate, m- or p-tetramethylxylene diisocyanate, isophorone diisocyanate or cyclohexane 1,4-diisocyanate.

In a preferred meaning, n is an integer from 5 to 70, particularly preferably 10 to 50, in particular 14 to 28.

In a preferred meaning, 80-100%, preferably 85-100%, in particular 90-100%, of the radicals R_1 , R_2 , R_3 and R_4 are, independently of one another, lower alkyl having up to 8 carbon atoms, particularly preferably lower alkyl having up to 4 carbon atoms, especially lower alkyl having up to 2 carbon atoms. A further particularly preferred embodiment of R_1 , R_2 , R_3 and R_4 is methyl.

In a preferred meaning, 0-20%, preferably 0-15%, in particular 0-10%, of the radicals R_1 , R_2 , R_3 and R_4 are, independently of one another, lower alkenyl, unsubstituted or lower alkyl- or lower alkoxy-substituted phenyl or cyano(lower alkyl).

Arylene is preferably phenylene or naphthylene, which is unsubstituted or substituted by lower alkyl or lower alkoxy, in particular 1,3-phenylene, 1,4-phenylene or methyl-1,4-phenylene, 1,5-naphthylene or 1,8-naphthylene.

Aryl is a carbocyclic aromatic radical which is unsubstituted or substituted preferably by lower alkyl or lower alkoxy. Examples are phenyl, tolyl, xylyl, methoxyphenyl, t-butoxyphenyl, naphthyl and phenanthryl.

A saturated bivalent cycloaliphatic group is preferably cycloalkylene, for example cyclohexylene or cyclohexylene(lower alkylene), for example cyclohexylenemethylene, which is unsubstituted or substituted by one or more lower alkyl groups, for example methyl groups, for example trimethylcyclohexylenemethylene, for example the bivalent isophorone radical.

For the purposes of the present invention, the term "lower" in connection with radicals and compounds, unless defined otherwise, denotes, in particular, radicals or compounds having up to 8 carbon atoms, preferably having up to 4 carbon atoms.

Lower alkyl has, in particular, up to 8 carbon atoms, preferably up to 4 carbon atoms, and is, for example, methyl, ethyl, propyl, butyl, tert-butyl, pentyl, hexyl or isohexyl.

Alkylene has up to 12 carbon atoms and can be straight-chain or branched. Suitable examples are decylene, octylene, hexylene, pentylene, butylene, propylene, ethylene, methylene, 2-propylene, 2-butylene, 3-pentylene, and the like.

Lower alkylene is alkylene having up to 8 carbon atoms, particularly preferably up to 4 carbon atoms. Particularly preferred meanings of lower alkylene are propylene, ethylene and methylene.

The arylene unit in alkylenearylene or arylenealkylene is preferably phenylene, unsubstituted or substituted by lower alkyl or lower alkoxy, and the alkylene unit therein is preferably lower alkylene, such as methylene or ethylene, in particular methylene. These radicals are therefore preferably phenylenemethylene or methylenephénylene.

Lower alkoxy has, in particular, up to 8 carbon atoms, preferably up to 4 carbon atoms, and is, for example, methoxy, ethoxy, propoxy, butoxy, tert-butoxy or hexyloxy.

Arylenealkylenearylene is preferably phenylene(lower alkylene)phenylene having up to 8, in particular up to 4, carbon atoms in the alkylene unit, for example phenyleneethylenephénylene or phenylenemethylenephénylene.

The macromers of the formula (I) can be prepared by processes known per se, for example as follows:

In a first step, a perfluoropolyalkyl ether derivative of formula (IV):



in which X_3 is $-OH$, $-NH_2$, $-COOH$, $-COCl$, $-NCO$ or $-COOR_5$, where $-COOR_5$ is generally an activated ester in which R_5 is alkyl or aryl which is unsubstituted or substituted by halogen or cyano, and the variables Z , E , k , x and y are as defined above, is preferably reacted with two equivalents of a bifunctional radical of formula (V):




in which R is as defined above and X_4 is a functional radical which is coreactive with an X_3 and is preferably $-OH$, $-NH_2$, $COOH$, $-COCl$, $-COOR_5$ or $-NCO$; in the presence or absence

of a suitable catalyst, where the reaction of X_3 with X_4 gives a group X_2 ; after which a reactive derivative of formula (VI):




is obtained which is then preferably reacted with two equivalents of an α,ω -substituted siloxane of formula (VII):



where the variables R_1 , R_2 , R_3 , R_4 , n , X_3 and Alk are as defined above, in the presence or absence of a suitable catalyst, giving a compound of formula (VIII):




in which $PFPE$ is $(E)_k-Z-CF_2-(OCF_2)_x-(OCF_2CF_2)_y-OCF_2-Z-(E)_k$, Sil is the siloxane radical



and the other variables are as defined above; after which the reactive intermediate of the formula (VIII) is preferably reacted with two equivalents of a compound of the formula (IXa) or (IXb):



in the presence or absence of a catalyst, to give the macromer of the formula (I):



in which Y_2 is a functional radical which is coreactive with X_3 and is preferably -OH, -NH₂, -COOH, -COCl, -COOR₃, -CONCO or -NCO, and the variables are as defined above, and in which X_1 is formed from the reaction of X_3 with X_4 and Y is formed from the reaction of Y_2 with X_3 .

The starting materials of formula (IV) for the preparation of the perfluoroalkyl ethers are known and many are commercially available. For example, U.S. Patent No. 3,810,875 and European Patent No. 0211237 (U.S. Patent No. 4,746,575) describe such compounds. Ausimont, Italy, markets perfluoroalkyl ether dimethanols under the name Fomblin, for example Fomblin ZDOL and Fomblin ZDOL-TX. Further Fomblin derivatives of the formula (IV) are commercially available, including, for example, Fomblin ZDISOC, in which the radical -Z- X_3 in the formula (IV) is CONH-C₆H₃(CH₃)-NCO; Fomblin ZDEAL, in which the radical Z- X_3 in the formula (IV) is -COOR₃; and Fomblin ZDIAC, in which the radical -Z- X_3 in the formula (IV) is -COOH.

Bifunctional radicals having a substitution pattern as per formula (V) exist in large numbers and are commercially available. Examples include, without limitation thereto: diisocyanates, such as isophorone diisocyanate and 2,2,4-trimethylhexane 1,6-diisocyanate; diols, such as glycol and cyclohexane-1,2-diol; dicarboxylic acids, such as adipic acid and maleic acid; diamines, such as ethylenediamine and hexamethylenediamine, diesters, such as diethyl phthalate and dibutyl malonate; derivatives containing various functional groups, such as 2-aminoethanol, monomethyl malonate, glycolic acid, salicylic acid, glycine and glycine methyl ester.

Preference is given to bifunctional derivatives of the formula (V) which have different reactivities irrespective of the nature of their functional radicals X_4 . In the case of identical radicals X_4 , this is achieved, for example, through different steric requirements in the direct vicinity of a radical X_4 . Examples thereof are isophorone diisocyanate, 2,2,4-trimethylhexane 1,6-diisocyanate and toluene 2,4-diisocyanate. The advantage of using bifunctional derivatives of formula (V) of different reactivity is that the chain length of polymer Q (number of segments (a), (b) and (c)) is easily adjustable and controllable.

α,ω -substituted siloxanes of formula (VII) are likewise commercially available, for example α,ω -hydroxypropyl-terminated polydimethylsiloxane KF6001 from Shin-Etsu.

The novel compounds can be prepared in the presence or absence of a solvent. It is advantageous to use a substantially inert solvent, i.e., one which does not participate in the reaction. Suitable examples thereof are ethers, such as tetrahydrofuran (THF), diethyl ether, diethylene glycol dimethyl ether or dioxane, halogenated hydrocarbons, such as chloroform or methylene chloride, bipolar aprotic solvents, such as acetonitrile, acetone, dimethylformamide (DMF) or dimethyl sulfoxide (DMSO), hydrocarbons, such as hexane, petroleum ether, toluene or xylene, and furthermore pyridine or N-methylmorpholine.

In the preparation of novel compounds, the reactants are advantageously employed in stoichiometric amounts. The reaction temperature can be, for example, from -30°C to 150°C , preferably from 0° to room temperature. The reaction times are in the range of about 15 minutes to 7 days, preferably about 12 hours. If necessary, the reaction is carried out under argon or nitrogen as protective gas. In urethane-forming reactions, a suitable catalyst, for example, dibutyltin dilaurate (DBTDL), is advantageously added.

The present Material "B" furthermore relates to a polymer comprising a product of the polymerization of at least one compound of formula (I) as defined above and, if desired, at least one vinylic comonomer (a). In a preferred composition of a novel copolymer, the proportion by weight of a compound of formula (I) is in the range of 100 to 0.5%, in particular in the range of 80 to 10%, preferably in the range of 70 to 30%, based on the total polymer.

In a preferred polymer comprising a product of the polymerization of at least one compound of the formula (I), comonomer (a) is absent and the polymer is a homopolymer.

A comonomer (a) present in the novel polymer can be hydrophilic or hydrophobic or a mixture thereof. Suitable comonomers are, in particular, those which are usually used in the production of contact lenses and biomedical materials. A hydrophobic comonomer (a) is taken to mean a monomer which typically gives a homopolymer which is insoluble in water and can absorb less than 10% by weight of water. Analogously, a hydrophilic comonomer (a) is taken to mean a monomer which typically gives a homopolymer which is soluble in water or can absorb at least 10% by weight of water. Suitable hydrophobic comonomers (a) are, without limitation thereto, $\text{C}_1\text{-C}_{18}$ alkyl and $\text{C}_3\text{-C}_{18}$ cycloalkyl acrylates and methacrylates, $\text{C}_3\text{-C}_{18}$ alkylacrylamides and -methacrylamides, acrylonitrile, methacrylonitrile, vinyl $\text{C}_1\text{-C}_{18}$ alkanoates, $\text{C}_2\text{-C}_{18}$ alkenes, $\text{C}_2\text{-C}_{18}$ haloalkenes, styrene, (lower alkyl)-styrene, lower alkyl vinyl ethers, $\text{C}_2\text{-C}_{10}$ perfluoroalkyl acrylates and methacrylates and

correspondingly partially fluorinated acrylates and methacrylates, C₃-C₁₂perfluoroalkylethylthiocarbonylaminoethyl acrylates and methacrylates, acryloxy- and methacryloxyalkylsiloxanes, N-vinylcarbazole, C₁-C₁₂alkyl esters of maleic acid, fumaric acid, itaconic acid, mesaconic acid and the like.

Preference is given, for example, to acrylonitrile, C₁-C₄alkyl esters of vinylically unsaturated carboxylic acids having 3 to 5 carbon atoms or vinyl esters of carboxylic acids having up to 5 carbon atoms.

Examples of suitable hydrophobic comonomers (a) are methyl acrylate, ethyl acrylate, propyl acrylate, isopropyl acrylate, cyclohexyl acrylate, 2-ethylhexyl acrylate, methyl methacrylate, ethyl methacrylate, propyl methacrylate, butyl acrylate, vinyl acetate, vinyl propionate, vinyl butyrate, vinyl valerate, styrene, chloroprene, vinyl chloride, vinylidene chloride, acrylonitrile, 1-butene, butadiene, methacrylonitrile, vinyltoluene, vinyl ethyl ether, perfluorohexylethylthiocarbonylaminoethyl methacrylate, isobornyl methacrylate, trifluoroethyl methacrylate, hexafluoroisopropyl methacrylate, hexafluorobutyl methacrylate, tris-trimethylsilyloxysilylpropyl methacrylate (TRIS), 3-methacryloxy propylpentamethyldisiloxane and bis(methacryloxypropyl)tetramethyldisiloxane.

Preferred examples of hydrophobic comonomers (a) are methyl methacrylate, TRIS and acrylonitrile.

Suitable hydrophilic comonomers (a) are, without this being an exhaustive list, hydroxyl-substituted lower alkyl acrylates and methacrylates, acrylamide, methacrylamide, (lower alkyl)acrylamides and -methacrylamides, ethoxylated acrylates and methacrylates, hydroxyl-substituted (lower alkyl)acrylamides and -methacrylamides, hydroxyl-substituted lower alkyl vinyl ethers, sodium vinylsulfonate, sodium styrenesulfonate, 2-acrylamido-2-methylpropanesulfonic acid, N-vinylpyrrole, N-vinyl-2-pyrrolidone, 2-vinylloxazoline, 2-vinyl-4,4'-dialkylloxazolin-5-one, 2- and 4-vinylpyridine, vinylically unsaturated carboxylic acids having a total of 3 to 5 carbon atoms, amino(lower alkyl)- (where the term "amino" also includes quaternary ammonium), mono(lower alkylamino)(lower alkyl) and di(lower alkylamino)(lower alkyl) acrylates and methacrylates, allyl alcohol and the like. Preference is given, for example, to N-vinyl-2-pyrrolidone, acrylamide, methacrylamide, hydroxyl-substituted lower alkyl acrylates and methacrylates, hydroxy-substituted (lower alkyl)acrylamides and -methacrylamides and vinylically unsaturated carboxylic acids having a total of 3 to 5 carbon atoms.

Examples of suitable hydrophilic comonomers (a) are hydroxyethyl methacrylate (HEMA), hydroxyethyl acrylate, hydroxypropyl acrylate, trimethylammonium 2-hydroxypropylmethacrylate hydrochloride (Blemer® QA, for example from Nippon Oil), dimethylaminoethyl methacrylate (DMAEMA), dimethylaminoethylmethacrylamide, acrylamide, methacrylamide, N,N-dimethylacrylamide (DMA), allyl alcohol, vinylpyridine, glycerol methacrylate, N-(1,1-dimethyl-3-oxobutyl)acrylamide, N-vinyl-2-pyrrolidone (NVP), acrylic acid, methacrylic acid and the like.

Preferred hydrophilic comonomers (a) are trimethylammonium 2-hydroxypropylmethacrylate hydrochloride, 2-hydroxyethyl methacrylate, dimethylaminoethyl methacrylate, trimethylammonium 2-hydroxypropylmethacrylate hydrochloride, N,N-dimethylacrylamide and N-vinyl-2-pyrrolidone.

The novel polymers are synthesized in a manner known per se from the corresponding monomers (the term monomer here also including a macromer according to the definition of the formula (I)) by a polymerization reaction customary to the person skilled in the art. Usually, a mixture of the abovementioned monomers is warmed with addition of a free-radical former. Examples of such free-radical formers are azoisobutyronitrile (AIBN), potassium peroxodisulfate, dibenzoyl peroxide, hydrogen peroxide and sodium percarbonate. If, for example, said compounds are warmed, free radicals form with homolysis, and can then initiate, for example, a polymerization.

A polymerization reaction can particularly preferably be carried out using a photoinitiator. In this case, the term photopolymerization is used. In the photopolymerization, it is appropriate to add a photoinitiator which can initiate free-radical polymerization and/or crosslinking by using light. Examples thereof are customary to the person skilled in the art; suitable photoinitiators are, in particular, benzoin methyl ether, 1-hydroxycyclohexylphenyl ketone, Darocur and Irgacur products, preferably Darocur® 1173 and Irgacur® 2959. Also suitable are reactive photoinitiators, which can be incorporated, for example, into a macromer, or can be used as a specific comonomer (a). Examples thereof are given in European Patent No. 0632329. The photopolymerization can then be initiated by actinic radiation, for example light, in particular UV light having a suitable wavelength. The spectral requirements can, if necessary, be controlled appropriately by addition of suitable photosensitizers.

A polymerization can be carried out in the presence or absence of a solvent. Suitable

solvents are in principle all solvents which dissolve the monomers used, for example water, alcohols, such as lower alkanols, for example ethanol or methanol, furthermore carboxamides, such as dimethylformamide, dipolar aprotic solvents, such as dimethyl sulfoxide or methyl ethyl ketone, ketones, for example acetone or cyclohexanone, hydrocarbons, for example toluene, ethers, for example THF, dimethoxyethane or dioxane, halogenated hydrocarbons, for example trichloroethane, and also mixtures of suitable solvents, for example mixtures of water and an alcohol, for example a water/ethanol or water/methanol mixture.

A polymer network can, if desired, be reinforced by addition of a crosslinking agent, for example a polyunsaturated comonomer (b). In this case, the term crosslinked polymers is used. The invention, therefore, furthermore relates to a crosslinked polymer comprising the product of the polymerization of a macromer of the formula (I), if desired with at least one vinylic comonomer (a) and with at least one comonomer (b).

Examples of typical comonomers (b) are allyl (meth)acrylate, lower alkylene glycol di(meth)acrylate, poly(lower alkylene) glycol di(meth)acrylate, lower alkylene di(meth)acrylate, divinyl ether, divinyl sulfone, di- and trivinylbenzene, trimethylolpropane tri(meth)acrylate, pentaerythritol tetra(meth)acrylate, bisphenol A di(meth)acrylate, methylenebis(meth)acrylamide, triallyl phthalate and diallyl phthalate.

The amount of comonomer (b) used is expressed in a proportion by weight based on the total polymer and is in the range from 20 to 0.05%, in particular in the range from 10 to 0.1%, preferably in the range from 2 to 0.1%.

3. Material "C"

Material "C" polymers are formed by polymerizing polymerizable macromers which contain free hydroxyl groups. Macromers which are built up, for example, from an amino-alkylated polysiloxane which is derivatized with at least one polyol component containing an unsaturated polymerizable side chain are disclosed. Polymers can be prepared on the one hand from the macromers according to the invention by homopolymerization. The macromers mentioned furthermore can be mixed and polymerized with one or more hydrophilic and/or hydrophobic comonomers. A special property of the macromers according to the invention is that they function as the element which controls microphase separation between selected hydrophilic and hydrophobic components in a crosslinked end

product. The hydrophilic/hydrophobic microphase separation is in the region of less than 300nm. The macromers are preferably crosslinked at the phase boundaries between, for example, an acrylate comonomer on the one hand and an unsaturated polymerizable side chain of polyols bonded to polysiloxane on the other hand, by covalent bonds and additionally by reversible physical interactions, for example hydrogen bridges. These are formed, for example, by numerous amide or urethane groups. The continuous siloxane phase which exists in the phase composite has the effect of producing a surprisingly high permeability to oxygen.

The present embodiment of the invention relates to a macromer comprising at least one segment of the formula (I):



in which

(a) is a polysiloxane segment,

(b) is a polyol segment which contains at least 4 C atoms,

Z is a segment (c) or a group X_1 ,


(c) is defined as X_2-R-X_2 , wherein

R is a bivalent radical of an organic compound having up to 20 C atoms and

each X_2 independently of the other is a bivalent radical which contains at least one carbonyl group,

X_1 is defined as X_2 , and

(d) is a radical of the formula (II):



in which


P_1 is a group which can be polymerized by free radicals;

Y and X_3 independently of one another are a bivalent radical which contains at least one carbonyl group;

k is 0 or 1; and

L is a bond or a divalent radical having up to 20 C atoms of an organic compound.

A polysiloxane segment (a) is derived from a compound of the formula (III):



in which n is an integer from 5 to 500;

99.8-25% of the radicals R_1 , R_2 , R_3 , R_4 , R_5 and R_6 independently of one another are alkyl and 0.2-75% of the radicals R_1 , R_2 , R_3 , R_4 , R_5 and R_6 independently of one another are partly fluorinated alkyl, aminoalkyl, alkenyl, aryl, cyanoalkyl, alk-NH-alk-NH₂ or alk-(OCH₂)_m-(OCH₂)_p-OR₇,

R_7 is hydrogen or lower alkyl, alk is alkylene, and

m and p independently of one another are an integer from 0 to 10, one molecule containing at least one primary amino or hydroxyl group.

The alkyleneoxy groups -(OCH₂CH₂)_m and -(OCH₂)_p in the siloxane of the formula (III) are either distributed randomly in a ligand alk-(OCH₂CH₂)_m-(OCH₂)_p-OR₇ or are distributed as blocks in a chain.

A polysiloxane segment (a) is linked a total of 1-50 times, preferably 2-30 times, and in particular 4-10 times, via a group Z with a segment (b) or another segment (a), Z in an "a-Z-a" sequence always being a segment (c). The linkage site in a segment (a) with a group Z is an amino or hydroxyl group reduced by one hydrogen.

In a preferred embodiment, a polysiloxane segment is derived from a compound of the formula (III) in which the radicals R_1 , R_2 , R_3 , R_4 , R_5 and R_6 are a total of 1-50 times, more preferably 2-30 times, and in particular 4-10 times, independently either terminally or pendently aminoalkyl or hydroxyalkyl, the other variables being as defined above.

In a preferred embodiment, a polysiloxane segment is derived from a compound of the formula (III) in which 95-29% of the radicals R_1 , R_2 , R_3 , R_4 , R_5 and R_6 independently of one another are alkyl and 5-71% of the radicals R_1 , R_2 , R_3 , R_4 , R_5 and R_6 independently of one another are partly fluorinated alkyl, aminoalkyl, alkenyl, aryl, cyanoalkyl, alk-NH-alk-NH₂ or alk-(OCH₂CH₂)_m-(OCH₂)_p-OR₇, and in which the variables are as defined above.

In a preferred meaning, n is an integer from 5 to 400, more preferably 10 to 250 and particularly preferably 12 to 125.

In a preferred meaning, the two terminal radicals R_1 and R_6 are aminoalkyl or hydroxyalkyl, the other variables being as defined above.

In another preferred meaning, the radicals R_4 and R_5 are 1-50 times, more preferably 2-30 times and in particular 4-10 times pendently aminoalkyl or hydroxyalkyl and the other variables are as defined above.

In another preferred meaning, the radicals R_1 , R_2 , R_3 , R_4 , R_5 and R_6 are a total of 1-50 times, more preferably 2-30 times and in particular 4-10 times, independently both terminally and pendently aminoalkyl or hydroxyalkyl and the other variables are as defined above.

If Z is X_1 , X_1 is a bivalent group which contains at least one carbonyl group. A carbonyl group mentioned is flanked in any manner, if appropriate, by -O-, -CONH-, -NHCO- or -NH-.

Examples of bivalent groups Z are typically carbonyls, esters, amides, urethanes, ureas or carbonates.

X_1 is preferably an ester, amide, urethane or urea group, in particular an ester or amide group.

X_2 is defined in the same way as X_1 and is preferably an ester, amide, urethane, carbonate or urea group, more preferably an ester, amide, urethane or urea group and in particular an amide, urethane or urea group.

If Z in formula (I) is X_1 , a polyol segment b is preferably understood as meaning a polyol derived from a carbohydrate, carbohydrate monolactone or carbohydrate dilactone. A carbohydrate is understood as meaning a mono-, di-, tri-, tetra-, oligo- or polysaccharide. A carbohydrate lactone is understood as meaning the lactone of an aldonic or uronic acid. An aldonic or uronic acid is, for example, a carboxylic acid formed by oxidation of a mono-, di-, tri-, tetra-, oligo- or polysaccharide. Examples of aldonic acid lactones are gluconolactone, galactonolactone, lactobionolactone or maltoheptaonolactone; examples of uronic acid lactones are glucuronic acid lactone, mannuronic acid lactone or iduronic acid lactone. An example of a carbohydrate dilactone is D-glucaro-1,4:6,3-dilactone.

A carbohydrate lactone reacts, for example, with a primary amino group or a hydroxyl group of segment (a) to form a covalent amide or ester bond of the type X_1 . Such linkages are the constituent of a further preferred embodiment of macromers according to the invention. Such macromers have an alternating distribution of segments of type (a) and (b) which are interrupted by X_1 .

This embodiment of the invention preferably relates to a macromer of the formula (IV):



in which the variables are as defined above.

An embodiment of the invention furthermore preferably relates to a macromer according to formula (V):




in which the polysiloxane segment (a) contains q pendent ligands,

x is 0, 1 or 2,

q has an average numerical value of 1-20, preferably 1-10, and in particular 1-5, and the segments (b) in a macromer according to the formula (V) are linked in total (per molecule) with up to 20, preferably with up to 15, and in particular with up to 6 polymerizable segments (d).

An embodiment of the invention furthermore preferably relates to a macromer according to formula (VI):




in which a linear sequence is present,

x is 0, 1 or 2,

q has an average numerical value of 1-20, preferably 1-10, and in particular 1-5,

and the segments (b) in a macromer according to the formula (VI) are linked in total (per molecule) with up to 20, preferably with up to 15, and in particular with up to 6 polymerizable segments (d).

An embodiment of the invention furthermore very preferably relates to a macromer according to formula (VII):



in which x is 0, 1 or 2, and

the average number of segments (d) per molecule of the formula (VII) is preferably in the range from 2 to 5, and very preferably is in the range from 3 to 4.

A polyol segment (b) is derived from a polyol which carries no lactone group if the group Z is a segment (c). Examples of such polyols are a 1,2-polyol, for example the reduced monosaccharides, for example mannitol, glucitol, sorbitol or iditol, a 1,3-polyol, for example polyvinyl alcohol (PVA), which is derived from partly or completely hydrolysed polyvinyl acetate, and furthermore amino-terminal PVA telomers, aminopolyols, aminocyclodextrins, aminomono-, -di-, -tri-, -oligo- or -polysaccharides or cyclodextrin derivatives, for example hydroxypropylcyclodextrin. An abovementioned carbohydrate dilactone can be reacted, for example, with preferably 2 equivalents of an amino-terminal PVA telomer to give a polyol macromer which carries, in the central part, the carbohydrate compound derived from the dilactone. Such polyols of this composition are likewise understood to be a suitable polyol.

As illustrated in formula (I), a segment (b) carries at least one vinylic polymerizable segment (d), a linkage of a segment (d) via the bivalent radical X_3 thereof to an amino or hydroxyl group, of a segment (b), reduced by a hydrogen atom being intended.

A vinylic polymerizable segment (d) is incorporated either terminally or pendently preferably 1-20 times, more preferably 2-15 times, and in particular 2-6 times, per macromer molecule according to the invention.

A vinylic polymerizable segment (d) is incorporated terminally and also pendently as desired (as a terminal/pendent mixture) preferably 1-20 times, more preferably 2-15 times and in particular 2-6 times, per macromer molecule according to the invention.

A group P_1 which can be polymerized by free radicals is, for example, alkenyl, alkenylaryl or alkenylarylenealkyl having up to 20 C atoms. Examples of alkenyl are vinyl, allyl, 1-propen-2-yl, 1-buten-2- or -3- or -4-yl, 2-buten-3-yl and the isomers of pentenyl, hexenyl, octenyl, decenyl or undecenyl. Examples of alkenylaryl are vinylphenyl, vinylnaphthyl or allylphenyl. An example of alkenylarylenealkyl is vinylbenzyl.

P_1 is preferably alkenyl or alkenylaryl having up to 12 C atoms, more preferably alkenyl having up to 8 C atoms and in particular alkenyl having up to 4 C atoms.

L is preferably alkylene, arylene, a saturated bivalent cycloaliphatic group having 6 to 20 carbon atoms, arylenealkylene, alkylenearylene, alkylenearylenealkylene or arylenealkylenearylene. In a preferred meaning, L furthermore is preferably a bond.

In a preferred meaning, L is a divalent radical having up to 12 C atoms, and more preferably a divalent radical having up to 8 C atoms. In a preferred meaning, L furthermore is alkylene or arylene having up to 12 C atoms. A very preferred meaning of L is lower alkylene, in particular lower alkylene having up to 4 C atoms.

Y is preferably a carbonyl, ester, amide or urethane group, in particular a carbonyl, ester or amide group, and very preferably a carbonyl group.

In another preferred meaning, Y is absent, i.e., k is 0.

In a preferred meaning, X_3 is a urethane, urea, ester, amide or carbonate group, more preferably a urethane, urea, ester or amide group, and in particular a urethane or urea group.

A vinylic polymerizable segment (d) is derived, for example, from acrylic acid, methacrylic acid, methacryloyl chloride, 2-isocyanatoethyl methacrylate (IEM), allyl isocyanate, vinyl isocyanate, the isomeric vinylbenzyl isocyanates or adducts of hydroxyethyl methacrylate (HEMA) and 2,4-tolylene diisocyanate (TDI) or isophorone diisocyanate (IPDI), in particular the 1:1 adduct.

The invention furthermore preferably relates to a macromer in which a segment (d) is incorporated either terminally or pendently or as a terminal/pendent mixture 5 times. The invention furthermore preferably relates to a macromer in which a segment (d) is incorporated terminally 5 times.

The diradical R is, for example, alkylene, arylene, alkylenearylene, arylenealkylene or arylenealkylenearylene having up to 20 carbon atoms, a saturated bivalent cycloaliphatic group having 6 to 20 carbon atoms or cycloalkylenealkylenecycloalkylene having 7 to 20 carbon atoms.

In a preferred meaning, R is alkylene, arylene, alkylenearylene, arylenealkylene or arylenealkylenearylene having up to 14 carbon atoms or a saturated bivalent cycloaliphatic group having 6 to 14 carbon atoms.

In a preferred meaning, R is alkylene, arylene, alkylenearylene or arylenealkylene having up to 14 carbon atoms, or a saturated bivalent cycloaliphatic group having 6 to 14 carbon atoms. In a preferred meaning, R is alkylene or arylene having up to 12 carbon atoms, or a saturated bivalent cycloaliphatic group having 6 to 14 carbon atoms.

In a preferred meaning, R is alkylene or arylene having up to 10 carbon atoms, or is a saturated bivalent cycloaliphatic group having 6 to 10 carbon atoms.

In a very preferred meaning, a segment (c) is derived from a diisocyanate, for example from hexane 1,6-diisocyanate, 2,2,4-trimethylhexane 1,6-diisocyanate, tetramethylene diisocyanate, phenylene 1,4-diisocyanate, toluene 2,4-diisocyanate, toluene 2,6-diisocyanate, m- or p-tetramethylxylene diisocyanate, isophorone diisocyanate or cyclohexane 1,4-diisocyanate.

A preferred embodiment of segment (c) is furthermore derived from a diisocyanate in which the isocyanate groups have different reactivities. The different reactivity is influenced, in particular, by the spatial requirements and/or electron density in the neighbourhood of an isocyanate group.

The average molecular weight of a macromer according to the invention is preferably in the range from about 300 to about 30,000, very preferably in the range from about 500 to about

20,000, more preferably in the range from about 800 to about 12,000, and particularly preferably in the range from about 1000 to about 10,000.

A preferred embodiment of the macromer has a segment sequence of the formula (VIII):



in which r is an integer from 1 to 10, preferably from 1 to 7, and in particular from 1 to 3;
 t is 0 or 1, and preferably 1;
 a linear $(c-a)$ chain which may or may not be terminated by a segment (b) is present ($t=1$);
 and the above preferences apply to the total number of segments (d) , which are preferably bonded to a segment (b) .

A preferred embodiment of the macromer has a segment sequence of formula (IX):




in which the sequence $(c-a)-(Z-b)_t$ hangs pendently r times on the segment (a) and may or may not be terminated by a segment (b) ;
 r is an integer from 1 to 10, preferably from 1 to 7, and in particular from 1 to 3;
 t is 0 or 1, and is preferably 1;
 Z is a segment (c) or a group X_1 ; and
 the above preferences apply to the total number of segments (d) , which are preferably bonded to a segment (b) .

Another preferred embodiment of the macromer has a segment sequence of formula (X):



in which s is an integer from 1 to 10, preferably from 1 to 7, and in particular from 1 to 3;
 B is a segment (a) or (b) ; and
 the above preferences apply to the number of segments (d) , which are bonded to a segment (b) .

Another preferred embodiment of the macromer has a segment sequence of the formula (XI):



(XI)

in which the structures are linear,

s is an integer from 1 to 10, preferably from 1 to 7, and in particular from 1 to 3;

B is a segment (a) or (b);

t is 0 or 1, and

the above preferences apply to the number of segments (d), which are bonded to a segment (b).

The ratio of the number of segments (a) and (b) in a macromer according to the Material "C" embodiment of the invention is preferably in a range of (a):(b)=3:4, 2:3, 1:2, 1:1, 1:3 or 1:4.

The total sum of segments (a) and (b) or, where appropriate, (a) and (b) and (c) is in a range from 2 to 50, preferably 3 to 30, and in particular in the range from 3 to 12.

Alkyl has up to 20 carbon atoms and can be straight-chain or branched. Suitable examples include dodecyl, octyl, hexyl, pentyl, butyl, propyl, ethyl, methyl, 2-propyl, 2-butyl or 3-pentyl.

Arylene is preferably phenylene or naphthylene, which is unsubstituted or substituted by lower alkyl or lower alkoxy, in particular 1,3-phenylene, 1,4-phenylene or methyl-1,4-phenylene; or 1,5-naphthylene or 1,8-naphthylene.

Aryl is a carbocyclic aromatic radical, which is unsubstituted or substituted by preferably lower alkyl or lower alkoxy. Examples are phenyl, tolyl, xylyl, methoxyphenyl, t-butoxyphenyl, naphthyl or phenanthryl.

A saturated bivalent cycloaliphatic group is preferably cycloalkylene, for example cyclohexylene or cyclohexylene-lower alkylene, for example cyclohexylenemethylene, which is unsubstituted or substituted by one or more lower alkyl groups, for example methyl groups, for example trimethylcyclohexylenemethylene, for example the bivalent isophorone radical.

The term "lower" in the context of this invention in connection with radicals and compounds, unless defined otherwise, means, in particular, radicals or compounds having up to 8 carbon atoms, preferably having up to 4 carbon atoms.

Lower alkyl has, in particular, up to 8 carbon atoms, preferably up to 4 carbon atoms, and is, for example, methyl, ethyl, propyl, butyl, tert-butyl, pentyl, hexyl or isohexyl.

Alkylene has up to 12 carbon atoms and can be straight-chain or branched. Suitable examples include decylene, octylene, hexylene, pentylene, butylene, propylene, ethylene, methylene, 2-propylene, 2-butylene or 3-pentylene.

Lower alkylene is alkylene having up to 8, and particularly preferably having up to 4 carbon atoms. Particularly preferred examples of lower alkylenes are propylene, ethylene and methylene.

The arylene unit of alkylenearylene or arylenealkylene is preferably phenylene, which is unsubstituted or substituted by lower alkyl or lower alkoxy, and the alkylene unit of this is preferably lower alkylene, such as methylene or ethylene, in particular methylene. Such radicals are therefore preferably phenylenemethylene or methylenephenylene.

Lower alkoxy has, in particular, up to 8 carbon atoms, preferably up to 4 carbon atoms, and is, for example, methoxy, ethoxy, propoxy, butoxy, tert-butoxy or hexyloxy.

Partly fluorinated alkyl is understood as meaning alkyl in which up to 90%, preferably up to 70%, and in particular up to 50%, of the hydrogens are replaced by fluorine.

Arylenealkylenearylene is preferably phenylene-lower alkylene-phenylene having up to 8, and in particular having up to 4 carbon atoms in the alkylene unit, for example phenylenethylenephenylene or phenylenemethylenephenylene.

A monosaccharide in the context of the present invention is understood as meaning an aldopentose, aldohexose, aldotetrose, ketopentose or ketohexose.

Examples of an aldopentose are D-ribose, D-arabinose, D-xylose or D-lyxose; examples of an aldohexose are D-allose, D-altrose, D-glucose, D-mannose, D-gulose, D-idose, D-galactose, D-talose, L-fucose or L-rhamnose; examples of a ketopentose are D-ribulose or D-xylulose; examples of a tetrose are D-erythrose or threose; and examples of a ketohexose are D-psicose, D-fructose, D-sorbose or D-tagatose. Examples of a disaccharide are trehalose, maltose, somaltose, cellobiose, gentiobiose, saccharose, lactose, chitobiose, N,N-diacetylchitobiose, palatinose or sucrose. Raffinose, panose or

maltotriose may be mentioned as an example of a trisaccharide. Examples of an oligosaccharide are maltotetraose, maltohexaose, chitoheptaose and furthermore cyclic oligosaccharides, such as cyclodextrins.

Cyclodextrins contain 6 to 8 identical units of α -1,4-glucose. Some examples are α -, β - and γ -cyclodextrin, derivatives of such cyclodextrins, for example hydroxypropylcyclodextrins, and branched cyclodextrins.

The macromers according to this embodiment of invention can be prepared by processes known per se, for example as follows.



In a first step, a polysiloxane containing at least one primary amino- or hydroxyalkyl group is reacted with a carbohydrate lactone, an amide or ester bond being formed and a compound of the formula (XIIa) or (XIIb) being formed:



in which the variables are as defined above and Z is a group X_1 ,
after which the compound (XII) is reacted with an unsaturated polymerizable compound of the formula (XIII):



in which X_4 is a group which is coreactive with a hydroxyl or amino group of segment (b),
an X_3 group of a segment (d) according to formula (II) being formed from such a reaction,
where X_4 is preferably $-COOH$, $-COOR_{10}$, $-COCl$ or $-NCO$, in which
 R_{10} is alkyl, or is aryl which is unsubstituted or substituted by lower alkyl or lower alkoxy,
and the other variables are as defined above,
after which a macromer according to the formula (IV) or (V) is formed.




in which the segments (d) are incorporated terminally or pendently.

Another process starts from a polysiloxane (a) which contains terminal primary amino- or hydroxyalkyl groups and is reacted with a carbohydrate dilactone to form linear structures of the formula (XIV):



in which the variables are as defined and preferred above, after which a compound of the formula (XIV) is reacted with a compound of the formula (XIII) analogously to the above process to give a macromer of the formula (VI):



in which the variables are as defined and preferred above.

Another process starts from a polysiloxane (a) which contains terminal primary amino- or hydroxyalkyl groups and is initially reacted with a bifunctional compound of the formula (XV):



in which X_1 is a group which is coreactive with a hydroxyl or amino group of segment (a), an X_2 group of a segment (c) being formed from such a reaction, where X_1 is preferably $-\text{COOH}$, $-\text{COOR}_{10}$, $-\text{COCl}$ or $-\text{NCO}$, in which R_{10} is alkyl, or aryl which is unsubstituted or substituted by lower alkyl or lower alkoxy, and R is as defined above, after which this intermediate is reacted with a polyol which carries no lactone group to give a compound of the formula (XVI):



in which the variables are as defined and preferred above, after which the compound of the formula (XVI) is reacted with a compound of the formula (XIII) to give a macromer of the formula (X):



in which s is an integer from 1 to 10, preferably from 1 to 7, and in particular from 1 to 3; B is a segment (a) or (b); and the above preferences apply to the number of segments (d) which are bonded to a segment (b).

Another process starts from a bifunctional compound of the formula (XV):



which is reacted with an excess of polysiloxane (a) to give an $-a-(c-a)-$ sequence, in which the above meanings apply, after which, in a second step, the intermediate is reacted with a polyol which carries no lactone to give a compound of the formula (XVII):





after which the compound (XVII) is reacted with the compound (XIII) to give a macromer of the formula (VIII):



in which r is an integer from 1 to 10, preferably from 1 to 7, and in particular from 1 to 3; t is 0 or 1, and is preferably 1; in which a linear $(c-a)$ chain, which may or may not be terminated by a segment (b), is present ($t=1$); and the above preferences apply to the total number of segments (d), which are preferably bonded to a segment (b).

Another process starts from a carbohydrate lactone which is reacted in a first step with a compound of the formula (XIII), the lactone function being retained, after which the intermediate is reacted with a polysiloxane containing at least one amino or hydroxyl group to give a compound of the formula (IV) or (V):



(V)

in which q is typically 1 or 2, and in which the above meanings and preferences otherwise apply, and the segments (d) are incorporated terminally or pendently.

The present embodiment of the invention furthermore relates to the intermediates which are novel and which occur during synthesis of the macromers according to the invention.

The invention therefore furthermore relates to a compound of the formula (XIIa):




in which q is greater than 1,

- (a) is derived from a polysiloxane as defined by formula (I) above and
- (b) is derived from a carbohydrate dilactone.

An embodiment of the invention furthermore relates to a compound of the formula (XIIb):




in which Z, (b) and q are as defined and preferred above, but with the proviso that a segment (a) is derived from a compound of the formula (III):



in which n is an integer from 5 to 500;

99.8 - 25% of the radicals R_1 , R_2 , R_3 , R_4 , R_5 and R_6 independently of one another are alkyl and 0.2 - 75 % of the radicals R_1 , R_2 , R_3 , R_4 , R_5 and R_6 independently of one another are partly fluorinated alkyl, aminoalkyl, alkenyl, aryl, cyanoalkyl, alk-NH-Alk-NH₂ or alk-(OCH₂CH₂)_m-(OCH₂)_p-OR₇ in which R₇ is hydrogen or lower alkyl, alk is alkylene and m and p independently of one another are an integer from 0 to 10, one molecule containing at least one primary amino or hydroxyl group and at least one partly fluorinated alkyl group.

The invention furthermore relates to a compound of the formula (XVI):



(XVI)

in which a segment (b) is derived from a polyol which carries no lactone and the other variables are as defined and preferred above.

An embodiment of the invention furthermore relates to a compound of the formula (XVII):



(XVII)

in which a segment (b) is derived from a polyol which carries no lactone and the other variables are as defined and preferred above.

A siloxane (a) containing at least one primary amino or hydroxyl group is, for example, commercially obtainable. Examples are KF-6002, KF-8003, X-22-161C (Shin Etsu) or GP4 (Genesee). Other siloxanes can be synthesized with the aid of published processes.

A polyol (b) required for the synthesis is as a rule commercially obtainable. Examples are gluconolactone or lactobionolactone. Otherwise, they can be synthesized with the aid of a published process.

The compounds according to the invention can be prepared in the presence or absence of a solvent. A solvent which is largely inert, i.e., does not participate in the reaction, is advantageously used. Suitable examples of these are ethers, such as tetrahydrofuran (THF), 1,2-dimethoxyethane, diethylene glycol dimethyl ether or dioxane, halogenated hydrocarbons, such as chloroform or methylene chloride, bipolar aprotic solvents, such as acetonitrile, acetone, dimethylformamide (DMF) or dimethyl sulfoxide (DMSO), hydrocarbons, such as toluene or xylene, and furthermore pyridine or N-methylmorpholine.

The reactants are advantageously employed in stoichiometric amounts for the preparation of the compounds according to the invention. The reaction temperature can be, for example, from -30°C to 150°C. The range from 0°C to 40°C is a preferred temperature range. The reaction times here are in the range from about 15 minutes to 7 days, preferably in the region of about 12 hours. If necessary, the reaction is carried out under argon or nitrogen as an inert gas. A suitable catalyst is advantageously added for urethane-forming reactions, for example dibutyltin dilaurate (DBTDL).

The present invention furthermore relates to a polymer comprising a polymerization product of at least one macromer according to the invention as defined above and, if appropriate, at least one vinylic comonomer (a).

The preferred composition of a polymer according to the invention comprises a weight content, with respect to the total polymer, of a macromer according to the invention in the range from 100 to 0.5%, in particular in the range from 80 to 10%, and preferably in the range from 70 to 30%.

In a preferred polymer comprising a polymerization product of at least one macromer according to the invention, comonomer (a) is absent and the polymer is preferably a homopolymer.

A comonomer (a) which is contained in a polymer according to the invention can be hydrophilic or hydrophobic or a mixture of both. Suitable comonomers include, in particular, those which are usually used for the preparation of contact lenses and biomedical materials.

A hydrophobic comonomer (a) is understood as meaning monomers which typically give, as a homopolymer, polymers which are water-insoluble and can absorb less than 10% by weight of water.

Analogously, a hydrophilic comonomer (a) is understood as meaning a monomer which typically gives, as a homopolymer, a polymer which is water-soluble or can absorb at least 10% by weight of water.

Suitable hydrophobic comonomers (a) include, without this list being exhaustive, C_1 - C_{18} alkyl and C_3 - C_{18} cycloalkyl acrylates and methacrylates, C_3 - C_{18} alkylacrylamides and -methacrylamides, acrylonitrile, methacrylonitrile, vinyl C_1 - C_{18} alkanoates, C_2 - C_{18} alkenes, C_2 - C_{18} haloalkenes, styrene, lower alkyl styrene, lower alkyl vinyl ethers, C_2 - C_{10} perfluoroalkyl acrylates and methacrylates or correspondingly partly fluorinated acrylates and methacrylates, C_3 - C_{12} perfluoroalkyl-ethyl-thiocarbonylaminoethyl acrylates and methacrylates, acryloxy- and methacryloxy-alkylsiloxanes, N-vinylcarbazole and C_1 - C_{12} alkyl esters of maleic acid, fumaric acid, itaconic acid, mesaconic acid and the like. Preferred comonomers are, for example, acrylonitrile, C_1 - C_4 alkyl esters of vinylically unsaturated carboxylic acids having 3 to 5 carbon atoms, or vinyl esters of carboxylic acids having up to 5 carbon atoms.

Examples of suitable hydrophobic comonomers (a) include methyl acrylate, ethyl acrylate, propyl acrylate, isopropyl acrylate, isobutyl acrylate (IBA), isooctyl acrylate (OA), isodecyl acrylate (DA), cyclohexyl acrylate, 2-ethylhexyl acrylate (EHA), methyl methacrylate, ethyl methacrylate, propyl methacrylate, butyl acrylate, vinyl acetate, vinyl propionate, vinyl butyrate, vinyl valerate, styrene, chloroprene, vinyl chloride, vinylidene chloride, acrylonitrile, 1-butene, butadiene, methacrylonitrile, vinyl toluene, vinyl ethyl ether, perfluorohexyl-ethylthiocarbonylaminoethyl methacrylate, isobornyl methacrylate, trifluoroethyl methacrylate, hexafluoroisopropyl methacrylate, hexafluorobutyl (meth)acrylate (HFBMA and HFBA), tris-trimethylsilyloxy-silyl-propyl methacrylate (TRIS), 3-methacryloxypropylpentamethyldisiloxane and bis(methacryloxypropyl) tetramethyldisiloxane.

Preferred examples of hydrophobic comonomers (a) are methyl methacrylate, IBA, HFBA, HFBMA, OA, EHA, DA, TRIS and acrylonitrile.

Suitable hydrophilic comonomers (a) include, without this list being conclusive, hydroxyl-substituted lower alkyl acrylates and methacrylates, acrylamide, methacrylamide, lower alkylacrylamides and -methacrylamides, ethoxylated acrylates and methacrylates, hydroxyl-substituted lower alkylacrylamides and -methacrylamides, hydroxyl-substituted lower alkyl vinyl ethers, sodium vinylsulfonate, sodium styrenesulfonate, 2-acrylamido-2-methylpropanesulfonic acid, N-vinylpyrrole, N-vinyl-2-pyrrolidone, 2-vinyloxazoline, 2-vinyl-4,4'-di-alkyloxazolin-5-one, 2- and 4-vinylpyridine, vinylically unsaturated carboxylic acids having a total of 3 to 5 carbon atoms, amino-lower alkyl (where the term "amino" also includes quaternary ammonium), mono-lower alkylamino-lower alkyl and di-lower alkylamino-lower alkyl acrylates and methacrylates, allyl alcohol and the like. Preferred comonomers are, for example, N-vinyl-2-pyrrolidone, acrylamide, methacrylamide, hydroxyl-substituted lower alkyl acrylates and methacrylates, hydroxyl-substituted lower alkylacrylamides and -methacrylamides and vinylically unsaturated carboxylic acids having a total of 3 to 5 carbon atoms.

Examples of suitable hydrophilic comonomers (a) include hydroxyethyl methacrylate (HEMA), hydroxyethyl acrylate, hydroxypropyl acrylate, trimethylammonium-2-hydroxypropyl methacrylate hydrochloride (Blemer[®]QA, for example from Nippon Oil), dimethylaminoethyl methacrylate (DMAEMA), dimethylaminoethyl methacrylamide, acrylamide, methacrylamide, N,N-dimethylacrylamide (DMA), allyl alcohol, vinylpyridine, glycerol methacrylate, N-(1,1-

dimethyl-3-oxobutyl)acrylamide, N-vinyl-2-pyrrolidone (NVP), acrylic acid, methacrylic acid and the like.

Preferred hydrophilic comonomers (a) are 2-hydroxyethyl methacrylate, dimethylaminoethyl methacrylate, trimethylammonium-2-hydroxypropyl methacrylate hydrochloride, N,N-dimethylacrylamide and N-vinyl-2-pyrrolidone.

The polymers according to the invention are built up in a manner known per se from the corresponding monomers (the term monomers here also including a macromer according to the invention) by a polymerization reaction with which the expert is familiar. Usually, a mixture of the abovementioned monomers is heated, with the addition of an agent which forms free radicals. Such an agent which forms free radicals is, for example, azoisobutyronitrile (AIBN), potassium peroxodisulfate, dibenzoyl peroxide, hydrogen peroxide or sodium percarbonate. If the compounds mentioned are heated, for example, free radicals are then formed, by homolysis, and can then, for example, initiate a polymerization.

A polymerization reaction can particularly preferably be carried out using a photoinitiator. Photopolymerization is the term used in this case. For photopolymerization, a photoinitiator which can initiate free radical polymerization and/or crosslinking by the use of light is suitably added. Examples of this are familiar to the expert, and specifically, suitable photoinitiators are benzoin methyl ether, 1-hydroxycyclohexyl phenyl ketone and Darocur and Irgacur types, preferably Darocur 1173® and Darocur 2959®. Reactive photoinitiators which can be incorporated, for example, into a macromer or can be used as a special comonomer (a) are also suitable. Examples of these are to be found in EP 632 329. The photopolymerization can then be triggered off by actinic radiation, for example light, in particular UV light of a suitable wavelength. The spectral requirements can be controlled accordingly, if appropriate, by addition of suitable photosensitizers.

Polymerization can be carried out in the presence or absence of a solvent. Suitable solvents are in principle all solvents which dissolve the monomers used, for example water, alcohols, such as lower alkanols, for example ethanol or methanol, and furthermore carboxylic acid amides, such as dimethylformamide, dipolar aprotic solvents, such as dimethyl sulfoxide or methyl ethyl ketone, ketones, for example acetone or cyclohexanone, hydrocarbons, for example toluene, ethers, for example THF, dimethoxyethane or dioxane, and halogenated hydrocarbons, for example trichloroethane, and also mixtures of suitable

solvents, for example mixtures of water with an alcohol, for example a water/ethanol or a water/methanol mixture.


If appropriate, a polymer network can be intensified by addition of a so-called crosslinking agent, for example a polyunsaturated comonomer (b). The invention furthermore relates to a polymer comprising the polymerization product of a macromer according to the invention with, if appropriate, at least one vinylic comonomer (a) and with at least one comonomer (b).

Examples of typical comonomers (b) are, for example, allyl(meth)acrylate, lower alkylene glycol di(meth)acrylate, poly lower alkylene glycol di(meth)acrylate, lower alkylene di(meth)acrylate, divinyl ether, divinyl sulfone, di- or trivinylbenzene, trimethylolpropane tri(meth)acrylate, pentaerythritol tetra(meth)acrylate, bisphenol A di(meth)acrylate, methylenebis(meth)acrylamide, triallyl phthalate or diallyl phthalate.

The amount of comonomer (b) used is expressed in the weight content with respect to the total polymer and is in the range from 20 to 0.05 %, in particular in the range from 10 to 0.1%, and preferably in the range from 2 to 0.1%.

4. "Material D"

Another advantageous embodiment of the present invention relates to the use of a siloxane-containing macromer which is formed from a poly(dialkylsiloxane) dialkoxyalkanol having the following structure:



where n is an integer from about 5 to about 500, preferably about 20 to 200, more preferably about 20 to 100;

the radicals R₁, R₂, R₃, and R₄, independently of one another, are lower alkylene, preferably C₁-C₆ alkylene, more preferably C₁-C₃ alkylene, wherein in a preferred embodiment, the total number of carbon atoms in R₁ and R₂ or in R₃ and R₄ is greater than 4; and R₅, R₆, R₇, and R₈ are, independently of one another, lower alkyl, preferably C₁-C₆ alkyl, more preferably C₁-C₃ alkyl.


The general structure of the Material D macromer follows:



where the ACRYLATE is selected from acrylates and methacrylates; LINK is selected from urethanes and diurethane linkages, ALK - O - ALK is as defined above (R_1 -O- R_2 or R_3 -O- R_4), and PDAS is a poly(dialkylsiloxane).


For example, a Material D macromer may be prepared by reacting isophorone diisocyanate, 2-hydroxyethyl (meth)acrylate and a poly(dialkylsiloxane) dialkoxyalkanol in the presence of a catalyst.

A preferred Material D macromer may be prepared by reacting a slight excess of isocyanatoalkyl methacrylate, especially isocyanatoethyl methacrylate (IEM), with a poly(dialkylsiloxane) dialkoxyalkanol, preferably poly(dimethylsiloxane) dipropoxyethanol, in the presence of a catalyst, especially an organotin catalyst such as dibutyltin dilaurate (DBTL). The primary resulting structure is as follows:




wherein R_{100} and R_{200} are defined as follows:

R_{100} :



R_{200} :



where R_9 and R_{11} are alkylene; preferably C_{1-6} alkylene, more preferably ethylene; and R_{10} and R_{12} are methyl or hydrogen.

The "Material D" prepolymer mixture may be formed by mixing the aforementioned siloxane-containing macromer with one or more hydrophilic monomers and a thermoinitiator or a photoinitiator such as Darocur® 1173. A solvent, such as hexanol, is preferably added to

homogenize the mixture. Preferably, an appropriate amount of TRIS is added to lower the modulus of elasticity to a desired level. The ionoperm monomer or monomers may be selected from any of the aforementioned ionoperm or hydrophilic monomers. Preferably, the ionoperm monomer is selected from the group consisting of acrylates, methacrylates, acrylamides, methacrylamides and mixtures thereof. More preferably, the ionoperm monomers are selected from dimethylacrylamide (DMA) and methacrylic acid (MAA).

A preferred "Material D" prepolymer mixture, in weight percentages based on total mixture weight, includes about 35 to 60% Material D macromer; about 6 to 25% TRIS; about 15 to 35% ionoperm monomer; about 0.1 to 1% photoinitiator; and about 10 to 20% solvent. A more preferred "Material D" prepolymer mixture, in weight percentages based on total mixture weight, includes the following: about 40 to 55% Material D macromer; about 8 to 16% TRIS; about 20 to 30% dimethylacrylamide; about 0.2 to 2% methacrylic acid; about 0.1 to 1% photoinitiator; and about 10 to 20% solvent. A particularly preferred "Material D" prepolymer mixture, in weight percentages based on total mixture weight, includes the following: about 44 to 50% Material D macromer; about 10 to 12% TRIS; about 22 to 26% dimethylacrylamide; about 0 to 1% methacrylic acid; about 0.2 to 0.6% photoinitiator; and about 10 to 20% solvent.

The prepolymer mixture may be formed into lenses and other ophthalmic devices by any of a number of techniques known in the art and disclosed herein. Preferably, the prepolymer mixture is conveyed into a concave half of a lens mold, the convex mold half is mated with the concave mold half, and an appropriate amount of radiation is applied to initiate polymerization. While ultraviolet (UV) radiation is preferred, a number of other energy sources known in the art and disclosed herein may also be used.

The Material D ophthalmic lens is preferably a polymerization product of the following macromeric and monomeric components, based on total weight of polymerizable material:

- (a) about 45 to about 65 percent Material D macromer;
- (b) about 5 to about 25 percent TRIS; and
- (c) about 20 to about 40 percent ionoperm monomer.

The Material D ophthalmic lens is more preferably a polymerization product of the following macromeric and monomeric components, based on total weight of polymerizable material:

- (a) about 50 to about 60 percent Material D macromer;
- (b) about 10 to about 20 percent TRIS; and

(c) about 25 to about 35 percent ionoperm monomer.

In a preferred embodiment, the Material D ophthalmic lens is a polymerization product of the following macromeric and monomeric components, based on total weight of polymerizable material:

- (a) about 50 to about 60 percent Material D macromer;
- (b) about 10 to about 20 percent TRIS;
- (c) about 25 to about 35 percent DMA; and
- (d) up to about 2 percent MAA.

In another preferred embodiment, about 0.2 to 1.0 weight percent MAA is used, together with the components (a), (b), and (c) in the above-cited amounts.

III. OPHTHALMICALLY COMPATIBLE SURFACES

The ophthalmic lenses of the present invention have a surface which is biocompatible with ocular tissue and ocular fluids during the desired extended period of contact. In one preferred embodiment, the ophthalmic lenses of the present invention include a core material, as defined above, surrounded, at least in part, by a surface which is more hydrophilic and lipophobic than the core material. A hydrophilic surface is desirable in order to enhance the compatibility of the lens with the ocular tissues and tear fluids. As surface hydrophilicity increases, undesirable attraction and adherence of lipids and proteinaceous matter typically decreases. There are factors other than surface hydrophilicity, such as immunological response, which may contribute to deposit accumulation on the lens. Deposition of lipids and proteinaceous matter causes haze on the lens, thereby reducing visual clarity. Proteinaceous deposits may also cause other problems, such as irritation to the eye. After extended periods of continuous or intermittent wear, the lens must be removed from the eye for cleaning, i.e., deposit removal. Therefore, increased surface hydrophilicity, and concomitant reductions in deposits of biological matter, allows increased wear time.

"Surface treatment processes", as used herein, refers to processes to render a surface more ophthalmically compatible, in which, by means of contact with a vapor or liquid, and/or by means of application of an energy source (1) a coating is applied to the surface of an article, (2) chemical species are adsorbed onto the surface of an article, (3) the chemical

nature (e.g., electrostatic charge) of chemical groups on the surface of an article are altered, or (4) the surface properties of an article are otherwise modified.

There are a variety of methods disclosed in the art for rendering a surface of a material hydrophilic. For example, the lens may be coated with a layer of a hydrophilic polymeric material. Alternatively, hydrophilic groups may be grafted onto the surface of the lens, thereby producing a monolayer of hydrophilic material. These coating or grafting processes may be effected by a number of processes, including without limitation thereto, exposing the lens to plasma gas or immersing the lens in a monomeric solution under appropriate conditions.

Another set of methods of altering the surface properties of a lens involves treatment prior to polymerization to form the lens. For example, the mold may be treated with a plasma (i.e., an ionized gas), a static electrical charge, irradiation, or other energy source, thereby causing the prepolymerization mixture immediately adjacent the mold surface to differ in composition from the core of the prepolymerization mixture.

A preferred class of surface treatment processes are plasma processes, in which an ionized gas is applied to the surface of an article. Plasma gases and processing conditions are described more fully in U.S. Patent Nos. 4,312,575 and 4,632,844, which are incorporated herein by reference. The plasma gas is preferably a mixture of lower alkanes and nitrogen, oxygen or an inert gas.

In a preferred embodiment, the lens is plasma treated in the presence of a mixture of (a) a C_{1-4} alkane and (b) a gas selected from the group consisting of nitrogen, argon, oxygen, and mixtures thereof. In a more preferred embodiment, the lens is plasma treated in the presence of a mixture of methane and air.

IV. UTILITY

A. Ophthalmic Lenses

The novel polymers or crosslinked polymers can be converted into ophthalmic moldings in a manner known in the art, in particular into contact lenses, for example by carrying out the photopolymerization or photocrosslinking of the novel polymers in a suitable contact lens mold. Examples of novel ophthalmic moldings, in addition to contact lenses, include without

limitation thereto, contact lenses for vision correction, contact lenses for eye color modification, ophthalmic drug delivery devices, ophthalmic wound healing devices, and the like.

B. Contact Lenses

A specific embodiment of the invention is directed to contact lenses which comprise essentially a novel polymer or polymeric network. Such contact lenses have a range of unusual and extremely advantageous properties. Amongst these properties are, for example, their excellent compatibility with the human cornea (if necessary after suitable surface treatment (coating)) and with tear fluid, which is based on a balanced ratio between water content and water permeability, oxygen permeability and mechanical and adsorptive properties. This balance of desirable properties results in high comfort and the absence of irritation and allergenic effects. Owing to their favorable permeability properties with respect to various salts, nutrients, water and diverse other components of tear fluid and gases (CO_2 and O_2), the novel contact lenses have no effect, or virtually no effect, on the natural metabolic processes in the cornea. In contrast to many other siloxane-containing contact lenses, the present innovative extended-wear lenses have chemical and mechanical properties and ion permeability sufficient to avoid the undesired binding effect. Furthermore, the novel contact lenses have high dimensional stability and shelf life.

It must be emphasized that this balance of properties, especially the high ion permeability in combination with the high oxygen permeability, is key to producing a true extended-wear contact lens. The high oxygen permeability is required to prevent corneal swelling, thereby reducing the likelihood of ocular damage and wearer discomfort during periods of extended wear. The high ion permeability enables the lens to move on the eye such that corneal health is not substantially altered and wearer comfort is acceptable during a period of extended, continuous contact with ocular tissue and ocular fluids.

The preferred extended-wear contact lenses of the present invention are those which are comfortable over the period of extended wear. If the lens diameter is too small, the eyelids will not cover any portion of the lens when the eye is open. Thus, the eyelids will contact the edge of the lens each time the eyelid is closed. This repeated eyelid-lens interaction typically causes irritation, wearer discomfort, and lens dislodgement. Accordingly, the preferred contact lens diameters are those which are sufficiently large to minimize eyelid-lens interaction and the associated irritation. Preferably, the contact lens has a diameter of

about 12 to about 16 millimeters, more preferably about 13 to 15 mm, and most preferably about 13.5 to 14.8 mm.

V. METHODS OF USE AS EXTENDED-WEAR LENSES

The above-described ophthalmic lenses have special utility as extended-wear contact lenses. Contact lenses having sufficient oxygen and water transmission rates from inner (base curve) to outer (front curve) surface may be continuously worn for long periods of time without substantial corneal swelling or wearer discomfort. The method of wear includes (a) applying the lens to the eye and (b) allowing the lens to remain in intimate contact with the eye and tear fluids for a period of at least 24 hours without substantial adverse impact on corneal health or wearer comfort.

A preferred method includes additional steps of (c) removing the lens from the ocular environment; (d) treating the lens (i.e., disinfecting or cleaning the lens); (e) re-applying the lens to the eye; and (f) allowing the lens to remain in intimate contact with the eye and tear fluids for a period of at least an additional 24 hours without substantial adverse impact on corneal health or wearer comfort.

In a preferred embodiment, the lens is worn for a continuous period of at least four (4) days without substantial corneal swelling or wearer discomfort. In another preferred embodiment, the lens is worn for a continuous period of at least seven (7) days without substantial corneal swelling or wearer discomfort. In another preferred embodiment, the lens is worn for a continuous period of at least 14 days without substantial corneal swelling or wearer discomfort. In yet another preferred embodiment, the lens is worn for a continuous period of at least 30 days without substantial corneal swelling or wearer discomfort.

VI. METHODS OF MANUFACTURE

The ophthalmic lens may be manufactured, generally, by thoroughly mixing the oxypem and ionopem polymerizable materials, applying an appropriate amount of the mixture to a lens mold cavity, and initiating polymerization. Photoinitiators, such as those commercially available photoinitiators disclosed above, may be added to the prepolymerization mixture to aid in initiating polymerization. Polymerization may be initiated by a number of well known techniques, which, depending on the polymerizable material, may include application of

radiation such as microwave, thermal, e-beam and ultraviolet. A preferred method of initiating polymerization is by application of ultraviolet radiation.

It has been discovered that the ion and/or water permeability of some of the aforementioned core materials may be increased by initiating and completing polymerization in an atmosphere which is substantially free of oxygen. Suitable gases which are readily commercially available include, without limitation thereto, nitrogen and carbon dioxide. Thus, in a preferred embodiment, the oxypem and ionopem polymerizable materials are polymerized in an atmosphere having less than about 10000 ppm oxygen. More preferably, the atmosphere surrounding the polymerizable material contains less than about 1000 ppm oxygen. Even more preferably, the surrounding atmosphere contains less than about 100 ppm oxygen, while the most preferred oxygen content is less than about 20 ppm.

In the aforementioned embodiment, the prepolymer mixture must be degassed prior to polymerization. The degassing may be accomplished by a number of techniques known in the art. One technique for degassing the prepolymer mixture involves the use of a series of freezing and thawing steps which are repeated until the appropriate gas concentration level is achieved in the prepolymer mixture. This freeze/thaw method involves cooling the prepolymer mixture until the mixture solidifies, applying a vacuum to the solidified prepolymer mixture, discontinuing the vacuum, and thawing the prepolymer mixture until the mixture is again in liquid form. While this degassing technique is advantageous in a laboratory setting, other degassing techniques known in the art may be more advantageous for commercial lens manufacturing processes.

Alternatively, the atmosphere surrounding the lens mold may include oxygen, under certain conditions. For example, if the lens mold halves seal adequately to one another and the lens mold material has a low rate of oxygen permeability (e.g., polypropylene), it is possible to polymerize a degassed prepolymer mixture in a mold surrounded by ambient air without reaching prepolymer oxygen concentrations sufficiently high to substantially reduce ion or water permeability of the final lens. Thus, in another preferred embodiment of double-sided molding, the lens is formed by the following steps: (1) the prepolymer mixture is degassed, (2) a lens mold half is filled with the prepolymer mixture, (3) the mold halves are sealed to one another, and (4) the polymerization is initiated to form the lens, where the lens mold halves are formed from a material having a low oxygen permeability and steps (2)-(4) may occur in the presence or absence of oxygen. In this embodiment, it is preferred that the

lens molds are stored in an inert substantially oxygen-free atmosphere, e.g., nitrogen or carbon dioxide, prior to use.

An essential feature of the manufacturing methods of the present innovative lenses is that a balance of high oxygen permeability and high ion permeability is achieved. Manufacturing techniques and conditions which result in lowering either the oxygen permeability or the ion permeability below levels sufficient to maintain good corneal health and on-eye movement during periods of extended wear are unacceptable to produce the innovative extended-wear contact lenses of the present invention.

Preferably, the manufacturing method produces a contact lens having a Dk/t of at least 70 barrers/mm and a Ionoton Ion Permeability Coefficient of at least $0.2 \times 10^{-6} \text{ cm}^2/\text{sec}$. More preferably, the manufacturing method produces a contact lens having a Dk/t of at least 75 barrers/mm and a Ionoton Ion Permeability Coefficient of at least $0.3 \times 10^{-6} \text{ cm}^2/\text{sec}$. The manufacturing method preferably provides a contact lens having a Dk/t of at least 87 barrers/mm and a Ionoton Ion Permeability Coefficient of at least $0.4 \times 10^{-6} \text{ cm}^2/\text{sec}$.

The previous disclosure will enable one having ordinary skill in the art to practice the invention. In order to better enable the reader to understand specific embodiments and the advantages thereof, reference to the following examples is suggested. However, the following examples should not be read to limit the scope of the invention.

Examples A-D are arranged in accordance with the materials defined above. Thus, Examples A-1, A-2, etc. relate to Material "A" as defined above, Examples B-1, B-2, etc. relate to Material "B" as defined above, Examples C-1, C-2, etc. relate to Material "C", and Examples D-1, D-2, etc. relate to Material "D". Temperatures are stated in degrees Celsius unless otherwise specified.

Examples E, F and G are directed to demonstrating a correlation between on-eye movement and the Ionoton Ion Permeability Coefficient, the Ionoflux Ion Permeability Coefficient, and the Hydrodell Water Permeability Coefficient, respectively.

EXAMPLE A-1

A polysiloxane macromer is prepared by reacting, at room temperature (about 21°C), one mole equivalent (about 100 grams) of poly(dimethylsiloxane) dialkanol (Shin Etsu Chemical

Co., Tokyo, Japan) having hydroxyethyl propoxy end groups with 2 mole equivalents (about 21.2 grams) of isophorone diisocyanate (Aldrich Chemical Co., Milwaukee, Wisconsin) in the presence of about 0.2 grams dibutyltin dilaurate catalyst (Pfaltz & Bauer, Inc., Waterbury, Connecticut). After about 48 hours reaction time, 2.02 mole equivalents (about 38.7 grams) of poly(ethylene glycol) ("PEG", about 610 g/mol Mn, Dow Chemical Corp., Midland, MI) and about 0.17 grams of dibutyltin dilaurate (about 0.43% by weight PEG) are added to 80 grams of the reaction product from the prior step. Sufficient chloroform (Aldrich Chemical Co.) is added to the mixture to make the mixture homogeneous. This mixture is stirred at room temperature for about 15 hours. Next, the mixture is stirred for about 8 hours at a temperature of about 44 to 48°C, with the temperature held substantially constant by a surrounding oil bath. The chloroform is then evaporated, in order to achieve a final concentration of about 50% by weight solids, by stirring the mixture at room temperature for about 8 hours. Then, about 2.14 mole equivalents (about 10.4 grams) of isocyanatoethyl methacrylate ("IEM", Monomer Polymer, Inc., Feasterville, PA) is added to the mixture. Finally, the mixture is covered with aluminum foil and stirred at room temperature for about 17 hours, yielding a polysiloxane-containing macromer having a number-average molecular weight (Mn) of about 4000 grams per mole.

The macromeric solution is then polymerized, in the presence of about 0.5 weight percent DAROCUR® 1173 photoinitiator (Ciba-Geigy Corporation, Ardsley, NY) to form contact lenses. Polypropylene contact lens molds are filled with the copolymer precursor solution. Ultraviolet light (about 300 to 400 nm) at about 3-6 mW/cm² is applied to the solution in the mold for about 3 hours at room temperature. The UV light, in conjunction with the photoinitiator, causes polymerization, thereby allowing the solution to form a contact lens having the shape of the mold. The lenses are extracted with isopropanol to remove the remaining chloroform solvent and any unreacted components. The product is a polysiloxane-containing polymeric contact lens.

Prior to taking oxygen permeability measurements, the lenses are hydrated by placing the lenses in isotonic buffered saline solution for at least eight hours. After hydration, if necessary because of handling, each lens is cleaned with MIRAFLW® Daily Cleaner (CIBA Vision Corporation, Duluth, Georgia) to remove grease and lipids prior to testing. Excess MIRAFLW® cleaner is removed by rinsing with saline or purified water.

Oxygen fluxes (J) are measured at 34°C in a wet cell (i.e., gas streams are maintained at about 100% relative humidity) using a Dk1000 instrument. Oxygen transmissibility, D_t/l, is

determined as outlined in the portions of the specification relating to oxygen permeability and transmissibility.

EXAMPLE A-2

A polysiloxane macromer is first prepared substantially in accordance with the procedure described in Example A-1.

A copolymer precursor solution is prepared by mixing about 180 grams polysiloxane-containing macromer, about 15 grams 3-methacryloxypropyltris (trimethylsiloxy) silane (Shin Etsu), about 4 grams 2-hydroxyethyl methacrylate ("HEMA"), about one gram ethylene glycol dimethacrylate ("EDGMA"), and about one gram DAROCUR® 1173 photoinitiator at room temperature for about 16 hours.

The copolymer precursor solution is then polymerized to form contact lenses. Polypropylene contact lens molds are filled with the copolymer precursor solution. Ultraviolet light (about 300 to 400 nm) at about 3-6 mW/cm² is applied to the solution in the mold for about 3 hours at room temperature. The UV light causes polymerization, thereby allowing the solution to form a contact lens having the shape of the mold. The lenses are extracted with isopropanol to remove remaining chloroform solvent and any unreacted components. A preferred resulting polymer contains about 81.8 weight percent polysiloxane macromer, about 13.6% TRIS, about 3.6% 2-hydroxyethyl methacrylate, and about 0.9% EDGMA.

The contact lens is degassed by placing the lens under suitable vacuum for a period sufficient to remove substantially all gas from the lens matrix. Fully hydrated degassed contact lenses having this composition have a Dk of about 87 barrers, a water content of about 19 weight percent, and a modulus of elasticity of about 2.5 MPa.

EXAMPLE A-3

A contact lens is prepared substantially in accordance with the procedure described in Example A-2, but having the final composition of about 19.5 weight percent polysiloxane macromer, about 47% TRIS, and about 33.5% N,N-dimethylacrylamide. Fully hydrated contact lenses having this composition have a Dk of about 49 barrers, a water content of about 30 weight percent, and a modulus of elasticity of about 2.4 MPa.

macromer, about 45% TRIS, 5% fluoroacrylate, and about 20% N,N-dimethylacrylamide. Fully hydrated contact lenses having this composition have a Dk of about 69 barrers, a water content of about 20 weight percent, and a modulus of elasticity of about 1.4 MPa.

EXAMPLE A-9

A contact lens is prepared substantially in accordance with the procedure described in Example A-2, but having the final composition of about 82 weight percent polysiloxane macromer, about 14.4% TRIS, and about 3.7% 2-hydroxyethyl methacrylate. Fully hydrated contact lenses having this composition have a Dk of about 96 barrers, a water content of about 19 weight percent, and a modulus of elasticity of about 1.8 MPa.

EXAMPLE A-10

A polysiloxane macromer is prepared substantially in accordance with the procedures described in Example A-1, but the polyethylene glycol has a molecular weight of about 660.

A contact lens is prepared substantially in accordance with the procedure described in Example 2, but having the final composition of about 81.9 weight percent polysiloxane macromer, about 13.6% TRIS, about 3.7% 2-hydroxyethyl methacrylate, and about 0.8% ethylene glycol dimethacrylate. Fully hydrated contact lenses having this composition have a Dk of about 81 barrers, a water content of about 20 weight percent, and a modulus of elasticity of about 1.4 MPa.

EXAMPLE A-11

A contact lens is prepared substantially in accordance with the procedure described in Example A-2, but having the final composition of about 82 weight percent polysiloxane macromer, about 8.6% TRIS, about 4.9% fluoroacrylate, about 3.5% 2-hydroxyethyl methacrylate, and about 1% EDGMA. Fully hydrated contact lenses having this composition have a Dk of about 77 barrers, a water content of about 22 weight percent, and a modulus of elasticity of about 1.3 MPa.

EXAMPLE A-12

A contact lens is prepared substantially in accordance with the procedure described in Example A-1, but the polysiloxane macromer used has hydroxy-sec-butyl end groups as opposed to hydroxyethylpropoxy end groups. The fully hydrated contact lens, after degassing, has a Dk of about 70 barrers, about a 22 weight percent water content, and a modulus of elasticity of about 2.4 Mpa.

EXAMPLE B-1: Macromer synthesis

51.5 g (50 mmol) of the perfluoropolyether Fomblin® ZDOL (from Ausimont S.p.A, Milan) having a mean molecular weight of 1030 g/mol and containing 1.96 meq/g of hydroxyl groups according to end-group titration is introduced into a three-neck flask together with 50 mg of dibutyltin dilaurate. The flask contents are evacuated to about 20 mbar with stirring and subsequently decompressed with argon. This operation is repeated twice. 22.2g (0.1 mol) of freshly distilled isophorone diisocyanate kept under argon are subsequently added in a counterstream of argon. The temperature in the flask is kept below 30°C by cooling with a waterbath. After stirring overnight at room temperature, the reaction is complete. Isocyanate titration gives an NCO content of 1.40 meq/g (theory: 1.35 meq/g).

202 g of the α,ω -hydroxypropyl-terminated polydimethylsiloxane KF-6001 from Shin-Etsu having a mean molecular weight of 2000g/mol (1.00 meq/g of hydroxyl groups according to titration) are introduced into a flask. The flask contents are evacuated to approx. 0.1 mbar and decompressed with argon. This operation is repeated twice. The degassed siloxane is dissolved in 202 ml of freshly distilled toluene kept under argon, and 100 mg of dibutyltin dilaurate (DBTDL) are added. After complete homogenization of the solution, all the perfluoropolyether reacted with isophorone diisocyanate (IPDI) is added under argon. After stirring overnight at room temperature, the reaction is complete. The solvent is stripped off under a high vacuum at room temperature. Microtitration shows 0.36 meq/g of hydroxyl groups (theory 0.37 meq/g).

13.78 g (88.9 mmol) of 2-isocyanatoethyl methacrylate (IEM) are added under argon to 247 g of the α,ω -hydroxypropyl-terminated polysiloxane-perfluoropolyether-polysiloxane three-block copolymer (a three-block copolymer on stoichiometric average, but other block lengths are also present). The mixture is stirred at room temperature for three days.

Microtitration then no longer shows any isocyanate groups (detection limit 0.01 meq/g). 0.34 meq/g of methacryl groups are found (theory 0.34 meq/g).

The macromer prepared in this way is completely colourless and clear. It can be stored in air at room temperature for several months in the absence of light without any change in molecular weight.

EXAMPLE B-2: Macromer synthesis

The first step of the macromer synthesis described under Example B-1 is repeated. An isocyanate titration of the perfluoropolyether reacted with IPDI gives a content of 1.33 meq/g of NCO (theory 1.35 meq/g).

In a second step, 87.1 g of the α,ω -hydroxypropyl-terminated polydimethylsiloxane Tegomer H-Si2111 (Th. Goldschmidt AG, Essen) having a mean molecular weight of 890 g/mol (2.25 meq/g of hydroxyl groups according to titration) are dissolved in 87 ml of toluene. After the reaction has been carried out as indicated under B-1 and the solvent has been removed, a hydroxyl group content of 0.66 meq/g is determined by microtitration (theory 0.60 meq/g). The resultant intermediate is in turn reacted with a stoichiometric amount of isocyanatoethyl methacrylate. Microtitration then no longer shows any isocyanate groups (detection limit 0.01 meq/g). 0.56 meq/g of methacryl groups are found (theory 0.53 meq/g). The macromer prepared in this way is completely colourless and clear and has a long shelf life.

EXAMPLE B-3: Macromer synthesis

The first step of the macromer synthesis described under Example B-1 is repeated, but using a different perfluoropolyether: Fomblin® ZDOLTX (from Ausimont S.p.A., Milan). This material is terminated by $\text{O}-\text{CF}_2-\text{CH}_2-(\text{OCH}_2\text{CH}_2)_n-\text{OH}$ (where $n = 0, 1$ or 2). The material used has a mean molecular weight of 1146 g/mol, and contains 1.72 meq/g of hydroxyl groups according to end-group analysis. An isocyanate titration of the perfluoropolyether reacted with IPDI shows a content of 1.23 meq/g of NCO (theory 1.25 meq/g).

In the second step, a stoichiometric amount of Tegomer Hi-Si2111 and toluene are again added. After the reaction has been carried out as indicated under Example B-1 and the

solvent has been removed, a hydroxyl group content of 0.63meq/g is determined by microtitration (theory 0.58meq/g). The resultant intermediate is in turn reacted with a stoichiometric amount of isocyanatoethyl methacrylate. Microtitration then no longer shows any isocyanate groups (detection limit 0.01meq/g). 0.55meq/g of methacryl groups are found (theory 0.51meq/g). The macromer prepared in this way is completely colourless and clear and has a long shelf life.

EXAMPLE B-4: Macromer synthesis

The first step of the macromer synthesis described under Example B-1 is repeated, but 5.0 g of Fomblin/ZDOL and 2.18 g of IPDI are employed. When the reaction is complete, microtitration shows an isocyanate group content of 1.31meq/g of hydroxyl groups (theory 1.36 meq/g).

The second step of the synthesis described under Example B-1 is likewise carried out analogously, the stoichiometric ratio between isocyanate-terminated perfluoropolyether and hydroxypropyl-terminated polysiloxane being 2:3. After the reaction has been completed and the solvent has been removed, microtitration shows a content of 0.2meq/g of hydroxyl groups (theory 0.18meq/g).

The third step of the synthesis described under Example B-1 is likewise carried out analogously, IEM being employed in a precisely stoichiometric ratio. After the reaction, free isocyanate groups can no longer be detected (detection limit 0.01meq/g). 0.19meq/g of methacryl groups are found (theory 0.19meq/g).

EXAMPLE B-5: Production of contact lenses

13.0 g of macromer from Example B-1 are dissolved in 5.6 g of ethanol (Fluka, puriss. p.a.) (70% by weight solution). After complete homogenization of the solution, 5.2 g of 3-tris(trimethylsiloxy)silylpropyl methacrylate (TRIS from Shin-Etsu, product No. KF-2801), 7.8 g of freshly distilled dimethylacrylamide (DMA) and 160 mg of photoinitiator Darocur® 1173 (Ciba) are added. This solution is filtered through a Teflon membrane having a pore width of 0.45 mm under an argon pressure of from 1 to 2 atm. The filtered solution is frozen in a flask in liquid nitrogen, the flask is evacuated under a high vacuum, and the solution is returned to room temperature with the flask sealed. This degassing operation is repeated twice. The flask containing the macromer/comonomer solution is then transferred into a

glove box with an inert-gas atmosphere, where the solution is pipetted into dust-free contact-lens moulds made from polypropylene. The moulds are closed, and the polymerization reaction is effected by UV irradiation ($15\text{mW}/\text{cm}^2$, 5 min.), with simultaneous crosslinking. The moulds are then opened and placed in ethanol, causing the resultant lenses to swell out of the moulds. The lenses are extracted for 24 hours with constantly replenished distilled dichloromethane and subsequently dried in a high vacuum. The dried lenses are equilibrated in phosphate-buffered physiological saline solution in autoclave-resistant vials and then autoclaved at 120°C for 30 minutes. All physical data measurements are carried out on autoclaved lenses.

The lenses produced in this way are characterized by the following values: oxygen permeability (Dk) 77 barrer (determined by the "wet" method described below), water content of the equilibrated lenses 32 percent by weight, elongation at break at 35°C 360%, modulus of elasticity 30°C 0.5MPa (measured using a Minimat from Polymer Laboratories, UK).

"Wet" measurement of the oxygen permeability:

The oxygen permeability of a material is determined by the coulometric method. To this end, pre-autoclaved lenses are clamped in a holder and then covered on the upper side with a 2 cm layer of water. A gas mixture comprising 21% of oxygen and 79% of nitrogen is passed continuously through the water layer with swirling. The oxygen which diffuses through the lens is measured using a coulometric detector. The reference values are those measured on commercially available contact lenses using this method. Cibasoft® (CIBA-Vision, HEMA lens) gives a measurement of approx. 7-10 barrer, and Excelens® (CIBA-Vision, PVA lens) gives a measurement of approx. 22 barrer.

Unfortunately, the oxygen permeability of, for example, contact lenses is frequently given in the literature as a straight Dk value without further definition and frequently without giving any reference material. These are usually values determined on dry material (dry measurement). A comparative measurement of the oxygen permeability of polymer B-5 shows the differences:

a) "wet" measurement: 77 barrer, but b) dry measurement: 158 barrer

EXAMPLE B-6

The process described under Example B-5 for the production of contact lenses is repeated, but the mixture of comonomers has the following composition (in per cent by weight):

55 % of macromer from Example B-1
22 % of TRIS
22.5 % of DMA
0.5 % of Blemer® QA

EXAMPLE B-7

The process described under Example B-5 for the production of contact lenses is repeated, but the mixture of comonomers has the following composition (in percent by weight):

55 % of macromer from Example B-1
22 % of TRIS
23 % of DMA

EXAMPLE B-8

Analogously to EXAMPLE B-5 (in weight percent):

40 % of macromer from Example B-1
30 % of TRIS
30 % of DMA

EXAMPLE B-9

The process described under B-5 for the production of contact lenses is repeated, but a 70% by weight solution of the macromer in toluene is used instead of the 75% by weight solution in ethanol described above. The mixture of comonomers has the following composition (in percent by weight):

55 % of macromer from Example B-1
22 % of TRIS
23 % of DMA

EXAMPLE B-10

The process described under B-5 for the production of contact lenses is repeated, but a 70% by weight solution of the macromer in octamethylcyclotetrasiloxane is used instead of the 75% by weight solution in ethanol described above. The mixture of comonomers has the following composition (in percent by weight):

55 % of macromer from Example B-1
 22 % of TRIS
 23 % of DMA

Physical measurement data for the contact lens materials from Examples B-5 to B-10 (O₂ Dk value, wet method) are presented in TABLE B-I:

TABLE B-I

Example	Water Content [%]	Dk [barrer]	Modulus of Elasticity [MPa]	Elongation at Break [%]
B-5	32	77	0.5	360
B-6	23.8	110	1.1	160
B-7	19.5	110	0.6	130
B-8	30.9	81	0.3	300
B-9	30			
B-10	25			

EXAMPLE B-11

About 10.0 grams of macromer from Example B-1 are dissolved in 3.3 grams of ethanol (Fluka, puriss. p.a.). After complete homogenization of the solution, about 4.0 grams of 3-tris(trimethylsiloxy)silylpropyl methacrylate (TRIS, from Shin-Etsu, product no. KF-2801), about 5.9 g. freshly distilled dimethylacrylamide (DMA), about 0.1 g. Blemer® QA (a methacrylate having quaternary ammonium substituents, Linz Chemie) and about 100 mg of photoinitiator Darocur® 1173 (Ciba) are added. The solution is filtered through a TEFLON membrane having a pore width of 0.45 mm under an argon pressure of from about 1 to 2 atm.

The filtered solution is frozen in a flask in liquid nitrogen, the flask is evacuated under a high vacuum, and the solution is returned to room temperature with the flask sealed. This degassing operation is repeated twice. The flask containing the macromer/comonomer solution is then transferred into a glove box with an inert gas atmosphere, where the solution is pipetted into dust-free, polypropylene contact lens molds. The molds are closed, and the polymerization reaction is effected by UV irradiation, with simultaneous crosslinking.

The molds are then opened and placed in isopropyl alcohol, causing the resultant lenses to swell out of the molds. The lenses are extracted for about 24 hours with nearly continuous replenishing of isopropyl alcohol. Subsequently, the lenses are dried under high vacuum.

The dried contact lenses are equilibrated in autoclave-resistant vials in phosphate-buffered physiological saline solution, and then autoclaved for 30 minutes at about 120°C. Physical measurement data for the autoclaved lens is presented below:

Dk [barrer]:	93
water content [%]:	20.3%
modulus of elasticity [Mpa]:	0.96

EXAMPLE B-12

Lenses are prepared in accordance with the procedures described in Example B-11, but are subsequent surface treated as follows. The dried lenses are transferred into a plasma coating apparatus wherein they are surface treated in a methane/"air" mixture ("air", as used here, denotes 79% nitrogen and 21% oxygen) for a period of about 5 minutes. The apparatus and plasma treatment process have been disclosed by H. Yasuda in "Plasma Polymerization", Academic Press, Orlando, Florida (1985), pages 319 forward.

The plasma-treated contact lenses are equilibrated in autoclave-resistant vials in phosphate-buffered physiological saline solution, and then autoclaved for 30 minutes at about 120°C. Physical measurement data for the plasma-coated autoclaved lens is presented below:

Dk [barrer]:	88
water content [%]:	21.8%
modulus of elasticity [Mpa]:	1.03

EXAMPLE B-13

Lenses are prepared in accordance with the procedures described in Example B-5, but the mixture of comonomers has the following composition, in weight percentages:

Macromer of Example B-1:	60%
TRIS:	25%
DMA:	15%

EXAMPLE B-14

Lenses are prepared in accordance with the procedures described in Example B-6, with the same comonomer composition, but the comonomers are dispensed into dust-free contact lens molds in ambient air atmosphere.

EXAMPLE C-1

Reaction of α,ω -bis-aminopropyl-dimethylpolysiloxane with D(+)-gluconic acid d-lactone:

Before the reaction, the amino-functionalized polydimethylsiloxane employed for the synthesis (X-22-161-C, Shin Etsu, JP) was finely dispersed in acetonitrile, extracted and then subjected to molecular distillation.

The following reactions take place with exclusion of H_2O . 200 g of purified amino-functionalized polydimethylsiloxane (0.375 meq of NH_2/g ; Mn(VPO) 3400-3900 (VPO: Vapour Pressure Osmometry)), dissolved in 200 ml of absolute THF, are slowly added dropwise to a suspension of 13.35 g (75 mmol) of D(+)-gluconic acid d-lactone in 50 ml of absolute THF and the mixture is stirred at 40°C for about 24 hours until the lactone has reacted completely. (Monitoring of the reaction by thin layer chromatography (TLC): silica gel; i-propanol/ H_2O /ethyl acetate 6:3:1; staining with Ce(IV) sulfate/phosphoromolybdic acid solution (CPS reagent)). After the reaction, the reaction solution is concentrated to dryness and the residue is dried under 3 Pa (0.03 mbar) for 48 hours. 213.3 g of α,ω -bis(3-gluconamidopropyl)-poly-dimethylsiloxane are obtained. Titration of the amino groups with perchloric acid shows a conversion of the amino groups of more than 99.8%.

Reaction of α,ω -bis-3-gluconamidopropyl-dimethylpolysiloxane with IEM :

The product obtained above (213.3 g) is dissolved in 800 ml of absolute THF and the solution is heated to 40°C with the addition of catalytic amounts of dibutyltin dilaurate (DBTDL). 14 g (90 mmol) of IEM in 20 ml of absolute THF are added dropwise to this solution over a period of about 4 hours. This corresponds to a concentration of 1.2 equivalents of IEM per gluconamide unit. The reaction is carried out in the course of 48 hours (monitoring of the reaction by IR spectroscopy detection of the NCO ties). The reaction solution is concentrated and the product is dried in a brown glass flask under 3 Pa

(0.03mbar) for 24 hours, while cooling with ice. 227.2 g of a colourless rubber-elastic product of high optical transparency remain.

EXAMPLE C-2 to C-7

Further amino propyl-dimethylpolysiloxanes (PDMS) are reacted with a different amount of gluconolactone and concentrations of IEM analogously to Example C-1. The examples are summarized in Table C-1

TABLE C-1

Example	Poly(dimethyl siloxane) [PDMS]				Amount of batch		
	Name	Type	Mn	NH ₂ *	PDMS g (mmol of NH ₂)	Glu g (mmol)	IEM g (mmol)
C-1	X-22-161-C	term.	3400	2	200 (75)	13.4 (75)	14.0 (90.0)
C-2	X-22-161-C	term.	3400	2	200 (74)	13.4 (75)	25.7 (165.0)
C-3	X-22-161-C	term.	3400	2	200 (75)	13.4 (75)	29.2 (187.5)
C-4	PS 813	pen.	1200	1			
C-5	GP 4	pen.	3150	2.6			
C-6	GP 6	pen.	5960	3			
C-7	KF 8003	pen.	9700	4.7	200 (98)	17.5 (98)	18.2 (117.4)

Legend:

X-22-161-C and KF 8003 are products from Shin Etsu (Japan), PS813 is a product from Petrarch-H Is, GP4 and GP6 are products from Genesee.

* Amino groups per macromer chain

Glu: D(+) gluconic acid d-lactone

term: terminal

pen: pendent

EXAMPLE C-8

The reaction is carried out in accordance with Example C-1, but instead of D(+)-gluconic acid d-lactone, 75 mmol of lactobionic acid 1,5-lactone, suspended in 50 ml of absolute THF, are added dropwise to a solution of amino-functionalized polydimethylsiloxane (X-22-161-C) in 180 ml of absolute THF and 20 ml of DMSO (pure, 99%). Titration of the amino groups with perchloric acid indicates a reaction conversion of 99% (<0.01 meq of NH_2/g). Here also, a colourless optically clear macromer is obtained.

EXAMPLE C-9 and C-10

The reactions are carried out analogously to Example C-1. However, the catalyst necessary for addition of the isocyanate onto the hydroxyl groups is varied. Instead of DBTDL, catalytic amounts of 1,4-diazabicyclo[2.2.2]octane (DABCO) or 4-dimethylamino-pyridine (DMAP) are added and the reaction is continued as described under Example C-1. In both cases, an optically clear, colourless rubber-elastic macromer results in a manner corresponding to Example C-1.

EXAMPLE C-11

The reaction is carried out analogously to Example C-1. In a manner corresponding to Example C-8, 0.1 mol of lactobionic acid 1,5-lactone is suspended in 50 ml of absolute THF and the suspension is added dropwise to a solution of amino-functionalized polydimethylsiloxane (KF-8003) in 180 ml of absolute THF and 20 ml of DMSO (pure, 99%). The reaction time is increased to about 48 hours. A residual content of 0.07 meq of NH_2/g can be detected, and is reacted completely by addition of the corresponding molar amount of D(+)-gluconic acid d-lactone to the reaction solution. The colourless highly transparent product has a residual content of amino groups of <0.01 meq/g.

EXAMPLE C-12

52.09 g (9.78 mmol) of purified amino-functionalized polydimethylsiloxane (X-22-161-C, Shin Etsu JP), dissolved in 110 ml of absolute THF, are initially introduced into the reaction vessel under an inert gas atmosphere, and 1.14 g (6.52 mmol) of D-glucaro-1,4:6,3-dilactone, dissolved in 20 ml of absolute THF, are added. The reaction solution is stirred at room temperature for 15 hours and then worked up in a manner corresponding to Example

C-1. The amine content is 0.134 meq/g. The terminal amino groups of the resulting penta-block macromer are reacted with gluconolactone in the following reaction step. 41.84 g (5.146 meq of NH_2) of the above macromer and 0.917 g (5.15 mmol) of D(+)-gluconic acid δ -lactone are suspended in 300 ml of absolute THF and the suspension is stirred under nitrogen at 40°C for 18 hours. The filtered solution is then concentrated and the residue is dried under 3 Pa (0.03 mbar) for 48 hours. A highly viscous optically clear substance having a residual content of amino groups of 0.013 meq/g results.

EXAMPLE C-13

Preparation of an amino- and perfluoroalkyl-functionalized polydimethylsiloxane:

3.0 ml of absolute toluene are added to 15 g of poly(dimethylsiloxane-co-methylhydro-siloxane) [Bayer Silopren U-230; 10,000 g/mol; 2.3 mmol of Si-H/g], and 1.72 g (9.2 mmol) of allylphthalimide [CAS Reg. No. 5428-09-1] are then added. The mixture is frozen several times and the flask evacuated and then brought to room temperature again. The flask is then let down with argon. 0.7 ml of a 0.005 molar solution of Lamoreaux catalyst (prepared in accordance with US 3,220,972, General Electric) in absolute toluene (100 ppm of Pt/mol of Si-H) is added and the mixture is heated to 80°C. After a reaction time of half an hour, a colourless, clear to slightly cloudy solution, the ^1H -NMR spectrum of which no longer shows resonances of allylic hydrogen atoms, is obtained.

Thereafter, 6.2 g (15.3 mmol) of degassed allyl 1H,1H,2H,2H-perfluorooctyl ether are slowly added and the mixture is stirred at 80°C for 2 hours. A ^1H -NMR spectrum now shows a severely weakened resonance of the Si-H function at 4.6 ppm and an intense resonance at 0.5 ppm, which originates from Si-CH₂ hydrogen atoms.

3.0 ml of 1-hexene are then added in order to react the remaining excess of Si-H groups, which could otherwise cause crosslinking of the polymer when air later has access. The mixture is further stirred at 80°C for another half an hour. The reaction mixture is then left to stand overnight. The product is purified over a silica gel column with hexane/ethyl acetate (3:2), the solvent is stripped off and the macromer is dried under a high vacuum. A colourless, clear, viscous product is obtained. The macromer purified in this way is taken up in 20 ml of hexane, 20 ml of methylamine [33% in ethanol] are added and the mixture is heated to 40°C. After 10-15 minutes, a white voluminous precipitate separates out. After 30 minutes, the suspension is cooled and filtered and the precipitate is washed with a little

hexane. The filtrate is evaporated and the residue is then dried under a high vacuum. Thereafter, the content of amino groups is determined by titrimetry (perchloric acid).

The resulting macromer is clear and viscous. The amino group content is 78.6% of theory. The total yield of macromer after the chromatographic purification is 75%.

Preparation of a gluconamide:

17.3 g (corresponding to an amine content of 5.4 meq) of this aminoalkyl-substituted product are dissolved in 20 ml of dried THF. The solution is repeatedly frozen, degassed and let down with argon. All the following operations are carried out in an argon atmosphere. 712 mg of D(+)-gluconic acid d-lactone (4 mmol) are then added. Because of the low solubility of the lactone, a suspension is initially obtained. After stirring overnight at 50°C, the solution is clear and the lactone has been used completely. The stoichiometric remaining amount of D(+)-gluconic acid d-lactone (260 mg, 1.46 mmol) is then added and the mixture is stirred again at 50°C overnight. A trace of unreacted lactone is observed. Completion of the reaction is monitored by means of thin layer chromatography on silica gel plates with the mobile phase 1-propanol/ethyl acetate/water (6:1:3). The silica gel plates are developed by means of Ce(IV) sulfate/phosphoromolybdic acid solution. Subsequent titration on amino groups yields a residual amino content of < 0.1%. After filtration and removal of the solvent by distillation, a highly viscous clear macromer with 0.295 mequivalent of gluconamide per gram of macromer is obtained.

EXAMPLE C-14

Before the polymerization, the acrylates employed, isobutyl acrylate (IBA), N,N-dimethylacrylamide (DMA) and 3-methacryloyloxypropyl-tris(trimethylsilyloxy)silane (TRIS) are each freed from inhibitors by distillation. 0.32 g (2.76 mmol) of IBA, 0.80 g (8.1 mmol) of DMA and 1.44 g (3.4 mmol) of TRIS are weighed into a 50ml round-bottomed flask and the flask is flushed with N₂ for half an hour, while cooling with ice. 1.44 g of macromer from Example C-1 are transferred to a round-bottomed flask with a nitrogen attachment, degassed under 3 Pa (0.03 mbar) for 24 hours and then dissolved in 2.7 g of ethanol which has been flushed with N₂ for half an hour beforehand. The subsequent preparation of samples and the polymerization are carried out inside a glove box with exclusion of oxygen. The above monomer mixture and the macromer solution from Example C-1 are mixed, with the addition of 0.012 g (0.21 mmol) of Darocur® 1173 and the mixture is subjected to microfiltration (0.45 mm filter). 180 µl of this mixture are introduced into a polypropylene

mould, which is then closed with an appropriate lid of polypropylene. The mixture is then irradiated with a UV-A mercury high pressure lamp in a nitrogen atmosphere in a UV oven equipped for this for 5 minutes. The lamps (5 each of the brand TLK40W/10R, Philips) are above and below the holder inserted. The irradiation intensity is 14.5 mW/cm^2 .

The polypropylene mould is opened and the finished discs or lenses are removed by soaking by means of a solvent mixture of methylene chloride and ethanol (2:3). The lenses and discs are extracted in ethanol at room temperature in special polypropylene cages for 48 hours and then dried at 40°C under 10Pa (0.1mbar) for 24 hours (autoclaving at 120°C , 30 minutes). The discs show an E modulus of 1.1MPa, a permeability to oxygen of 183 barrier and a hardness (Shore A) of 53.

EXAMPLE C-15 to C-19

Further polymers are prepared in a manner corresponding to Example C-14 (composition in percentages by weight). Table C-II shows examples C-15 to C-19 and the properties of the resulting materials measured on discs.

TABLE C-II

Example	Water Content [%]	Macromer from Example	Macromer weight percent	DMA weight percent	TRIS weight percent	E modulus [Mpa]	Dk [barrer]
C-15	not tested	C-3	32.8	30*	37.2	-	-
C-16	19.9	C-3	32.9	34.3	32.7	0.7	84
C-17	25.1	C-3	39.3	34.3	36.4	0.9	72
C-18	17.5	C-3	35.7	34.3	30.0	0.7	100
C-19	23.4	C-3	33.3	33.3	33.4	0.7	96

Legend:

DMA: N,N-Dimethylacrylamide

TRIS: 3-Methacryloyloxypropyl-tris(trimethylsilyloxy)silane

*: instead of DMA, in this example DMEA (2-Dimethylaminoethyl acrylate) was used

EXAMPLE C-20: Uncoated contact lens

A contact lens is prepared in a manner corresponding to Example C-14, using the Example C-3 macromer, with the following composition in percentages by weight:

Macromer: 33.3,

DMA: 33.3,

TRIS: 33.4.

The lens has a Dk of about 94 and a water content of about 20.0 weight percent. The results are presented in TABLE C-III for comparison with coated lens properties.

EXAMPLE C-21: Plasma-treated contact lens

Dried lenses prepared in accordance with the procedures described in Example C-20 are transferred into a plasma coating apparatus where the lenses are surface treated in a methane/"air" mixture ("air", as used here, denotes 79% nitrogen and 21% oxygen). The apparatus and plasma treatment process have been disclosed by H. Yasuda in "Plasma Polymerization", Academic Press, Orlando, Florida (1985), pages 319 forward.

The dried plasma-treated contact lenses are equilibrated in autoclave-resistant vials in phosphate-buffered physiological saline solution, and then autoclaved for 30 minutes at about 120°C. The plasma-treated autoclaved lens has a Dk [barrer] of 90 and a water content of 21.5%. The results are presented in TABLE C-III for comparison with coated lens properties.

TABLE C-III

Example	Surface type	Dk [barrer]	Water content [%]
C-20	untreated	94	20.0
C-21	plasma-treated	90	21.5

EXAMPLE C-22

The synthesis of this polymer corresponds to Example C-14 with the following comonomer composition: Example C-3 macromer/TRIS/DMA: 32.8%/32.6%/34.2% (in percentages by weight) and an addition of 0.4% by weight of trimethylammonium-2-hydroxypropyl methacrylate hydrochloride (Blemer® QA, Nippon Oil Corp.). The polymer has a modulus of

0.9MPa and a permeability to oxygen of 82 barrer. The water content is 25.1% (after 30 minutes' autoclaving at 120°C). For comparison, Example C-16 has a water content of 20% with a very similar comonomer composition (no addition of Blemer® QA).

EXAMPLE C-23

The polymer is prepared analogously to Example C-14, but the polymerization is carried out in bulk, which means without addition of ethanol. The composition of the comonomers and the material properties of the polymer synthesized, measured on discs is given below.

Example C-7 macromer: 41%,
 IBA: 23%,
 1-vinyl-2-pyrrolidone (NVP): 24%,
 acrylonitrile (AN): 12%.

The disc hardness (shore A) is 68.

EXAMPLE C-24

The polymerization is carried out in accordance with Example C-14 but with the following changed comonomer composition:
 macromer of Example C-7/IBA/TRIS 20%/19%/60% and 1% (in percentages by weight) of bis(3-methacryloyloxypropyl)tetra methyldisiloxane. An optically clear polymer with an E modulus of 0.4MPa, a permeability to oxygen of 241 barrer and a hardness (Shore A) of 42 is obtained.

EXAMPLES C-25 through C-27

Contact lenses are prepared in accordance with the procedure described in Example C-14. The compositions in weight percentages are as follows:

Example	Macromer	Macromer weight percent	IBA weight percent	DMA weight percent	TRIS weight percent	HFBA weight percent
C-25	C-3	36.0	8.0	20.0	36.0	-
C-26	C-2	35.0	5.0	20.0	35.0	5.0
C-27	C-3	32.8	-	30.0	37.2	-

where IBA is isobutylacrylate,
DMA is N,N-Dimethylacrylamide,
TRIS is 3-methacryloyloxypropyl-tris(trimethylsiloxy) silane,
HFBA is 2,2,3,4,4,4-hexafluorobutyl acrylate.

EXAMPLE C-28

The polymerization is carried out in accordance with Example C-14 but with the following changed comonomer composition: macromer of Example C-1/DMA/TRIS 33.3% / 33.3% / 33.3%. An optically clear polymer is obtained.

EXAMPLE D-1: Macromer Synthesis

In a dry box under nitrogen atmosphere, about 200 grams of dry PDMS dipropoxyethanol (Shin-Etsu) is added to a container. Isocyanatoethyl methacrylate (IEM) in an amount equal to about 2 moles per mole PDMS dialkanol is added to the container. About 0.1 weight percent dibutyltin dilaurate (DBTL) catalyst, based on PDMS dialkanol weight, is added to the container along with a stir bar. The container is immersed in an oil bath atop a stir plate, and secured in place with a clamp. A stream of UPC air at about 2 psig is passed over the mixture. The mixture is agitated at room temperature (about 22°C) for about 24 hours. An iterative procedure follows in which the mixture is analyzed for isocyanate content and IEM is added if the PDMS dialkoxyalkanol has not been completely reacted. The mixture is stirred about 24 hours more. The macromer produced is a siloxane-containing macromer.

EXAMPLE D-2: Lens fabrication

A prepolymerization mixture is prepared by mixing about 56 grams of the macromer from Example D-1, about 14 grams of TRIS, about 29 grams N,N-dimethylacrylamide (DMA), about 1 gram methacrylic acid, about 0.5 grams Darocur® 1173 photoinitiator, and about 20 grams hexanol. The mixture is agitated for about 20 minutes at room temperature. Next, the mixture is degassed via a series of freezing and thawing steps. The container is placed in a liquid nitrogen bath until the mixture solidifies. A vacuum is applied to the container at a pressure of about 200 millitorr or less for about 5 minutes. Then, the container is placed in a bath of room temperature water until the mixture is liquid again. This process is performed a total of three times. The mixture is then polymerized to form contact lenses.

The prepolymerization mixture is poured into polypropylene contact lens molds in a nitrogen atmosphere. The polymerization is effected by applying UV radiation (about 4-6 mW/cm²) for a period of about 15 minutes. The resulting fully hydrated contact lens has a water content of about 23%. The lens has a Dk of about 115 barrers and a modulus of elasticity of about 2 MPa.

EXAMPLE D-3: Lens fabrication

A contact lens is prepared in accordance with the procedure described in Example D-2, with the difference being that the composition is about 50% macromer of Example D-1, about 20% TRIS and about 30% DMA. The resulting fully hydrated contact lens has a water content of about 20%. The lens has a Dk of about 118 barrers and a modulus of elasticity of about 1.8 Mpa.

EXAMPLE E-1 (Material A)

A contact lens is prepared substantially in accordance with the procedure described in Example A-2. Prior to polymerization, the prepolymerization mixture is degassed by cooling the prepolymer mixture with liquid nitrogen until the mixture solidifies and is near liquid nitrogen temperature, then applying a vacuum (about 0.1 mm Hg) to the solidified prepolymer mixture, discontinuing the vacuum, and thawing the prepolymer mixture until the mixture is again in liquid form. This degassing procedure is performed a total of three times on the prepolymerization mixture. The prepolymer mixture is cured in a nitrogen atmosphere to form the contact lens. The cured lens has an equilibrium water content of about 19%. Subsequent to curing, the lens is plasma treated for about 10 minutes in an atmosphere of methane and air at a 2:1 CH₄:air volume:volume ratio. The working pressure of the gas is about 50 millitorr. The plasma treatment is accomplished in a Plasma Polymerization Apparatus LCVD-20-400A (Plasmacarb, Bedford, Massachusetts). The Ionon Ion Permeability Coefficient of the lens is 0.81×10^{-3} cm²/sec. Clinical examination shows that the lens moves on the human eye. See Table E for a summary of the results.

EXAMPLE E-2 (Material B)

A contact lens is prepared substantially in accordance with the procedure described in Example B-10. Prior to polymerization, nitrogen gas is bubbled through the prepolymer

mixture in order to remove oxygen from the prepolymer mixture. The prepolymer mixture is cured in a nitrogen atmosphere to form the contact lens. The cured lens has an equilibrium water content of about 26 weight percent. No coating is applied to the surface. The Ionon Ion Permeability Coefficient of the lens is $- 0.063 \times 10^{-3} \text{ cm}^2/\text{sec}$. Clinical examination shows that the lens does not move on the human eye. See Table E for a summary of the results.

EXAMPLE E-3 (Material B)

A contact lens is prepared substantially in accordance with the procedure described in Example B-12. Prior to polymerization, the prepolymerization mixture is degassed by the repeated freeze/thaw procedure of Example E-1. The prepolymer mixture is cured in a nitrogen atmosphere to form the contact lens. The cured lens has an equilibrium water content of about 30 weight percent. Subsequent to curing, the lens is plasma treated for about 3 minutes in an atmosphere of methane and air at a 2:1 CH_4 :air volume ratio. The Ionon Ion Permeability Coefficient of the lens is $0.50 \times 10^{-3} \text{ cm}^2/\text{sec}$. Clinical examination shows that the lens moves on the human eye. See Table E for a summary of the results.

EXAMPLE E-4 (Material B)

A contact lens is prepared substantially in accordance with the procedure described in Example B-12. Prior to polymerization, the prepolymerization mixture is degassed by the repeated freeze/thaw procedure of Example E-1. The prepolymer mixture is cured in a nitrogen atmosphere to form the contact lens. The cured lens has an equilibrium water content of about 30 weight percent. Subsequent to curing, the lens is plasma treated for about 5 minutes in an atmosphere of methane and air at a 2:1 CH_4 :air volume ratio. The Ionon Ion Permeability Coefficient of the lens is $0.47 \times 10^{-3} \text{ cm}^2/\text{sec}$. Clinical examination shows that the lens moves on the human eye. See Table E for a summary of the results.

EXAMPLE E-5 (Material B)

A contact lens is prepared substantially in accordance with the procedure described in Example B-12. Prior to polymerization, the prepolymerization mixture is degassed by the repeated freeze/thaw procedure of Example E-1. The prepolymer mixture is cured in a

nitrogen atmosphere to form the contact lens. The cured lens has an equilibrium water content of about 30 weight percent. Subsequent to curing, the lens is plasma treated for about 7.5 minutes in an atmosphere of methane and air at a 2:1 CH₄:air volume ratio. The Ionoton Ion Permeability Coefficient of the lens is $0.35 \times 10^{-3} \text{ cm}^2/\text{sec}$. Clinical examination shows that the lens moves on the human eye. See Table E for a summary of the results.

EXAMPLE E-6 (Material B)

A contact lens is prepared substantially in accordance with the procedure described in Example B-11. Prior to polymerization, the prepolymerization mixture is degassed by the repeated freeze/thaw procedure of Example E-1. The prepolymer mixture is cured in a nitrogen atmosphere to form the contact lens. The cured lens has an equilibrium water content of about 30 weight percent. The lens is not subsequently coated. The Ionoton Ion Permeability Coefficient of the lens is $1.1 \times 10^{-3} \text{ cm}^2/\text{sec}$. Clinical examination shows that the lens moves on the human eye. See Table E for a summary of the results.

EXAMPLE E-7 (Material C)

A contact lens is prepared substantially in accordance with the procedure described in Example C-21. Prior to polymerization, the prepolymerization mixture is degassed by the repeated freeze/thaw procedure of Example E-1. The prepolymer mixture is cured in a nitrogen atmosphere to form the contact lens. Subsequent to curing, the lens is plasma treated for about 5 minutes in an atmosphere of methane and air at a 2:1 CH₄:air volume ratio. The Ionoton Ion Permeability Coefficient of the lens is $2.9 \times 10^{-3} \text{ cm}^2/\text{sec}$. Clinical examination shows that the lens moves on the human eye. See Table E for a summary of the results.

EXAMPLE E-8 (Material C)

A contact lens is prepared substantially in accordance with the procedure described in Example C-21. Prior to polymerization, the prepolymerization mixture is degassed by the repeated freeze/thaw procedure of Example E-1. The prepolymer mixture is cured in a nitrogen atmosphere to form the contact lens. Subsequent to curing, the lens is plasma

treated for about 7.5 minutes in an atmosphere of methane and air at a 2:1 CH₄:air volume ratio.

The Ionoton Ion Permeability Coefficient of the lens is $0.25 \times 10^{-3} \text{ cm}^2/\text{sec}$. Clinical examination shows that the lens moves on the human eye. See Table E for a summary of the results.

EXAMPLE E-9 (Material C)

A contact lens is prepared substantially in accordance with the procedure described in Example C-20. Prior to polymerization, the prepolymerization mixture is degassed by the repeated freeze/thaw procedure of Example E-1. The prepolymer mixture is cured in an air atmosphere to form the contact lens. Subsequent to curing, the lens is not surface treated. The Ionoton Ion Permeability Coefficient of the lens is $0.008 \times 10^{-3} \text{ cm}^2/\text{sec}$. Clinical examination shows that the lens does not move on the human eye. See Table E for a summary of the results.

EXAMPLE E-10 (Material D)

A contact lens is prepared substantially in accordance with the procedure described in Example D-2. Prior to polymerization, the prepolymerization mixture is degassed by the repeated freeze/thaw procedure of Example E-1. The prepolymer mixture is cured in a nitrogen atmosphere to form the contact lens. Subsequent to curing, the lens is not surface treated.

The Ionoton Ion Permeability Coefficient of the lens is $1.4 \times 10^{-3} \text{ cm}^2/\text{sec}$. Clinical examination shows that the lens moves on the human eye. See Table E for a summary of the results.

EXAMPLE E-11 (Material D)

A contact lens is prepared substantially in accordance with the procedure described in Example D-2. Prior to polymerization, the prepolymerization mixture is degassed by the repeated freeze/thaw procedure of Example E-1. The prepolymer mixture is cured in a nitrogen atmosphere to form the contact lens. Subsequent to curing, the lens is plasma treated for about 7.5 minutes in an atmosphere of methane and air at a 2:1 CH₄:air volume ratio.

The Ionoton Ion Permeability Coefficient of the lens is $0.61 \times 10^{-3} \text{ cm}^2/\text{sec}$. Clinical examination shows that the lens moves on the human eye. See Table E for a summary of the results.

EXAMPLE E-12 (Material D)

A contact lens is prepared substantially in accordance with the procedure described in Example D-2. Prior to polymerization, the prepolymerization mixture is degassed by the repeated freeze/thaw procedure of Example E-1. The prepolymer mixture is cured in a nitrogen atmosphere to form the contact lens. Subsequent to curing, the lens is plasma treated for about 5 minutes in an atmosphere of methane and air at a 2:1 CH_4 :air volume ratio.

The Ionoton Ion Permeability Coefficient of the lens is $1.5 \times 10^{-3} \text{ cm}^2/\text{sec}$. Clinical examination shows that the lens moves on the human eye. See Table E for a summary of the results.

EXAMPLE E-13 (Material D)

A contact lens is prepared substantially in accordance with the procedure described in Example D-2. Prior to polymerization, the prepolymerization mixture is degassed by the repeated freeze/thaw procedure of Example E-1. The prepolymer mixture is cured in an air atmosphere to form the contact lens. Subsequent to curing, the lens is not surface treated.

The Ionoton Ion Permeability Coefficient of the lens is $-0.001 \times 10^{-3} \text{ cm}^2/\text{sec}$. Clinical examination shows that the lens does not move on the human eye. See Table E for a summary of the results.

TABLE E

Example	Material	Degassing	Curing atmosphere	Surface treatment CH ₄ :air plasma [minutes]	Ionoton Ion Permeability Coefficient [10 ⁻³ cm ² /sec]	On-eye Movement
E-1	A	3-cycle freeze/thaw	nitrogen	10	0.81	YES
E-2	B	nitrogen bubble	nitrogen	no plasma	-0.063	NO
E-3	B	3-cycle freeze/thaw	nitrogen	3	0.50	YES
E-4	B	3-cycle freeze/thaw	nitrogen	5	0.47	YES
E-5	B	3-cycle freeze/thaw	nitrogen	7.5	0.35	YES
E-6	B	3-cycle freeze/thaw	nitrogen	no plasma	1.1	YES
E-7	C	3-cycle freeze/thaw	nitrogen	5	2.9	YES
E-8	C	3-cycle freeze/thaw	nitrogen	7.5	0.25	YES
E-9	C	3-cycle freeze/thaw	air	no plasma	0.008	NO
E-10	D	3-cycle freeze/thaw	nitrogen	no plasma	1.4	YES
E-11	D	3-cycle freeze/thaw	nitrogen	7.5	0.61	YES
E-12	D	3-cycle freeze/thaw	nitrogen	5	1.5	YES
E-13	D	3-cycle freeze/thaw	air	no plasma	-0.001	NO

Considering Examples E-1 through E-13 of Table E, the lowest value of Ionoton Ion Permeability Coefficient for which a lens moves on the eye is $0.25 \times 10^{-3} \text{ cm}^2/\text{sec}$. The highest value of Ionoton Ion Permeability Coefficient for a lens which bound on the eye is $0.008 \times 10^{-3} \text{ cm}^2/\text{sec}$. Thus, a contact lens preferably has an Ionoton Ion Permeability Coefficient greater than about $0.008 \times 10^{-3} \text{ cm}^2/\text{sec}$, more preferably greater than about $0.25 \times 10^{-3} \text{ cm}^2/\text{sec}$.

EXAMPLE F-1 (Material C)

A contact lens is prepared substantially in accordance with the procedure described in Example C-25. Prior to surface treatment, the Ionoflux Ion Permeability Coefficient is determined to be about $0 \text{ mm}^2/\text{min}$.

Subsequent to ion permeability measurements, the lens surface is coated with polyvinylpyrrolidone (PVP) in accordance with the following procedure, using a glass plasma reactor equipped with an external ring electrode and a 27.13 MHz radio frequency (RF) generator for the generation of an inductively-coupled, cold glow discharge plasma. Highly purified argon is used as a plasma gas and as a carrier gas for N-vinylpyrrolidone (NVP) monomer feed. The NVP feed line is located about 10 cm below the glow zone.

The contact lens is placed in the 20 cm diameter plasma reactor at a position about 15 cm below the plasma glow zone. The reactor is then evacuated for about 30 minutes to about 0.009 mbar. Subquent to evacuation, the plasma gas flow is set to 20 sccm (standard cubic centimeters), the glow discharge is started at a pressure of about 0.15 mbar and maintained for about one minute at a power of about 170 Watts (in order to clean and activate the lens surface). After reduction of argon plasma gas flow to about 10 sccm, the argon carrier gas flow for the NVP monomer is also set to 10 sccm. The temperature of the NVP source (with the carrier gas bubbling through the liquid NVP) is held at about 40°C . The lenses are treated for about 10 minutes with a pulsing glow discharge plasma (1 μsec . on, 3 μsec . off) at about 0.35 mbar pressure and about 150 Watts power.

After interrupting the glow discharge and the carrier gas flow, the reactor is continuously purged with a 20 sccm argon stream at a pressure of about 0.009 mbar for about 30 minutes, in order to remove residual monomer and activated species. The PVP coated contact lenses thus produced are highly wettable and show the following dynamic contact angles, measured with a KRUESS (Hamburg, Germany) K-12 instrument:

	Untreated	Treated
Advancing	102	38
Receding	48	23
Hysteresis	53	15

Clinical tests show that the lens does not move on the eye. See Table F for a summary of the results.

EXAMPLE F-2 (Material C)

A contact lens is prepared substantially in accordance with the procedure described in Example C-26. Prior to surface treatment, the Ionoflux Ion Permeability Coefficient is determined to be about 2.8×10^{-7} mm²/min. Subsequent to ion permeability measurements, the lens surface is coated with polyvinylpyrrolidone as in Example F-1. Clinical tests show that the lens does not move on the eye. See Table F for a summary of the results.

EXAMPLE F-3 (Material C)

A contact lens is prepared substantially in accordance with the procedure described in Example C-27. Prior to surface treatment, the Ionoflux Ion Permeability Coefficient is determined to be about 9.3×10^{-7} mm²/min. Subsequent to ion permeability measurements, the lens surface is coated with polyvinylpyrrolidone as in Example F-1. Clinical tests show that the lens does not move on the eye. See Table F for a summary of the results.

EXAMPLE F-4 (Material C)

A contact lens is prepared substantially in accordance with the procedure described in Example C-18. Prior to surface treatment, the Ionoflux Ion Permeability Coefficient is determined to be about 2.6×10^{-6} mm²/min. Subsequent to ion permeability measurements, the lens surface is coated with polyvinylpyrrolidone as in Example F-1.

Clinical tests show that the lens moves on the eye. See Table F for a summary of the results.

EXAMPLE F-5 (Material C)

A contact lens is prepared substantially in accordance with the procedure described in Example C-16. Prior to surface treatment, the Ionoflux Ion Permeability Coefficient is determined to be about 1.3×10^{-5} mm²/min. Subsequent to ion permeability measurements, the lens surface is coated with polyvinylpyrrolidone as in Example F-1. Clinical tests show that the lens moves on the eye. See Table F for a summary of the results.

EXAMPLE F-6 (Material C)

A contact lens is prepared substantially in accordance with the procedure described in Example C-19. Prior to surface treatment, the Ionoflux Ion Permeability Coefficient is determined to be about 2.7×10^{-5} mm²/min. Subsequent to ion permeability measurements, the lens surface is coated with polyvinylpyrrolidone as in Example F-1. Clinical tests show that the lens moves on the eye. See Table F for a summary of the results.

EXAMPLE F-7 (Material C)

A contact lens is prepared substantially in accordance with the procedure described in Example C-17. Prior to surface treatment, the Ionoflux Ion Permeability Coefficient is determined to be about 7.8×10^{-6} mm²/min. Subsequent to ion permeability measurements, the lens surface is coated with polyvinylpyrrolidone as in Example F-1. Clinical tests show that the lens moves on the eye. See Table F for a summary of the results.

EXAMPLE F-8 (Material B)

A contact lens is prepared substantially in accordance with the procedure described in Example B-13. Prior to surface treatment, the Ionoflux Ion Permeability Coefficient is determined to be about 1.5×10^{-6} mm²/min. Subsequent to ion permeability measurements, the lens surface is coated with polyvinylpyrrolidone as in Example F-1. Clinical tests show that the lens does not move on the eye. See Table F for a summary of the results.

EXAMPLE F-9 (Material B)

A contact lens is prepared substantially in accordance with the procedure described in Example B-14. Prior to surface treatment, the Ionoflux Ion Permeability Coefficient is

determined to be about 1.1×10^{-6} mm²/min. Subsequent to ion permeability measurements, the lens surface is coated with polyvinylpyrrolidone as in Example F-1. Clinical tests show that the lens does not move on the eye. See Table F for a summary of the results.

EXAMPLE F-10 (Material B)

A contact lens is prepared substantially in accordance with the procedure described in Example B-7. Prior to surface treatment, the Ionoflux Ion Permeability Coefficient is determined to be about 3.8×10^{-6} mm²/min. Subsequent to ion permeability measurements, the lens surface is coated with polyvinylpyrrolidone as in Example F-1. Clinical tests show that the lens moves on the eye. See Table F for a summary of the results.

EXAMPLE F-11 (Material B)

A contact lens is prepared substantially in accordance with the procedure described in Example B-6. Prior to surface treatment, the Ionoflux Ion Permeability Coefficient is determined to be about 8.5×10^{-6} mm²/min. Subsequent to ion permeability measurements, the lens surface is coated with polyvinylpyrrolidone as in Example F-1. Clinical tests show that the lens moves on the eye. See Table F for a summary of the results.

EXAMPLE F-12 (Material B)

A contact lens is prepared substantially in accordance with the procedure described in Example B-5. Prior to surface treatment, the Ionoflux Ion Permeability Coefficient is determined to be about 7.1×10^{-5} mm²/min. Subsequent to ion permeability measurements, the lens surface is coated with polyvinylpyrrolidone as in Example F-1. Clinical tests show that the lens moves on the eye. See Table F for a summary of the results.

TABLE F

EXAMPLE	MATERIAL (Example reference number)	IONOFLUX ION PERMEABILITY COEFFICIENT* [mm ² /min]	ON-EYE MOVEMENT -CLINICAL DETERMINATION
		0	NO
F-1	C-25		
F-2	C-26	0.28×10^{-6}	NO
F-3	C-27	0.93×10^{-6}	NO
F-4	C-18	2.6×10^{-6}	YES
F-5	C-16	13.0×10^{-6}	YES
F-6	C-19	27.0×10^{-6}	YES
F-7	C-17	7.8×10^{-6}	YES
F-8	B-13	1.5×10^{-6}	NO
F-9	B-14	1.1×10^{-6}	NO
F-10	B-7	3.8×10^{-6}	YES
F-11	B-6	8.5×10^{-6}	YES
F-12	B-5	71.0×10^{-6}	YES

* All Ionoflux Ion Permeability Coefficients were determined on uncoated lenses.

Considering only Examples F-1 through F-13 of Table F, the lowest value of Ionoflux Ion Permeability Coefficient for which a lens moves on the eye is 2.6×10^{-6} mm²/min. The highest value of Ionoflux Ion Permeability Coefficient for a lens which binds on the eye is 1.5×10^{-6} mm²/min. Thus, a contact lens preferably has an Ionoflux Ion Permeability Coefficient greater than about 1.5×10^{-6} mm²/min., more preferably greater than about 2.6×10^{-6} mm²/min.

EXAMPLE G-1

A contact lens is prepared substantially in accordance with the procedure described in Example A-2. The Hydrodell Water Permeability Coefficient is determined to be about 0.71×10^{-6} cm²/second. Clinical tests show that the lens moves on the eye. See Table G for a summary of the results.

EXAMPLE G-2

A contact lens is prepared substantially in accordance with the procedure described in Example B-5. The Hydrodell Water Permeability Coefficient is determined to be about $1.09 \times 10^{-6} \text{ cm}^2/\text{second}$. Clinical tests show that the lens moves on the eye. See Table G for a summary of the results.

EXAMPLE G-3

A contact lens is prepared substantially in accordance with the procedure described in Example B-6. The lens is surface treated in a plasma gas in accordance with the procedure described in Example F-1. The Hydrodell Water Permeability Coefficient is determined to be about $0.27 \times 10^{-6} \text{ cm}^2/\text{second}$. Clinical tests show that the lens moves on the eye. See Table G for a summary of the results.

EXAMPLE G-4

A contact lens is prepared substantially in accordance with the procedure described in Example C-19. The lens is surface treated in a plasma gas in accordance with the procedure described in Example F-1. The Hydrodell Water Permeability Coefficient is determined to be about $0.37 \times 10^{-6} \text{ cm}^2/\text{second}$. Clinical tests show that the lens moves on the eye. See Table G for a summary of the results.

EXAMPLE G-5

A contact lens is prepared substantially in accordance with the procedure described in Example D-2. The Hydrodell Water Permeability Coefficient is determined to be about $1.26 \times 10^{-6} \text{ cm}^2/\text{second}$. Clinical tests show that the lens moves on the eye. See Table G for a summary of the results.

EXAMPLE G-6

A contact lens is prepared substantially in accordance with the procedure described in Example C-14. The Hydrodell Water Permeability Coefficient is determined to be about $0.08 \times 10^{-6} \text{ cm}^2/\text{second}$. Clinical tests show that the lens does not move on the eye. See Table G for a summary of the results.

TABLE G

EXAM PLE	MATERIAL (Example reference number)	SURFACE TREATMENT	HYDRODELL WATER PERMEABILITY COEFFICIENT [cm ² /sec.]	ON-EYE MOVE- MENT -CLINICAL DETERMINATION
G-1	A-2	none	0.71×10^{-6}	YES
G-2	B-5	none	1.09×10^{-6}	YES
G-3	B-6	PVP	0.27×10^{-6}	YES
G-4	C-19	PVP	0.37×10^{-6}	YES
G-5	D-2	none	1.26×10^{-6}	YES
G-6	C-14	none	0.08×10^{-6}	NO

Considering only Examples G-1 through G-6 of Table G, the lowest value of Hydrodell Water Permeability Coefficient for which a lens moves on the eye is 0.27×10^{-6} cm²/sec. The highest value of Hydrodell Water Permeability Coefficient for a lens which binds on the eye is 0.08×10^{-6} cm²/sec. Thus, a contact lens preferably has a Hydrodell Water Permeability Coefficient greater than about 0.08×10^{-6} cm²/sec., more preferably greater than 0.27×10^{-6} cm²/sec.

The invention has been described in detail, with reference to certain preferred embodiments, in order to enable the reader to practice the invention without undue experimentation. Theories of operation have been offered to better enable the reader to understand the invention, but such theories do not limit the scope of the invention. In addition, a person having ordinary skill in the art will readily recognize that many of the previous components, compositions, and parameters may be varied or modified to a reasonable extent without departing from the scope and spirit of the invention. Furthermore, titles, headings, example materials or the like are provided to enhance the reader's comprehension of this document, and should not be read as limiting the scope of the present invention. Accordingly, the intellectual property rights to the invention are defined by the following claims, reasonable extensions and equivalents thereof, as interpreted in view of the disclosure herein.

CLAIMS:

1. An ophthalmic lens having ophthalmically compatible inner and outer surfaces, said lens being suited to extended periods of wear in continuous, intimate contact with ocular tissue and ocular fluids, said lens comprising a polymeric material which has a high oxygen permeability and a high ion permeability, said polymeric material being formed from polymerizable materials comprising:

(a) at least one oxypem polymerizable material and

(b) at least one ionopem polymerizable material,

wherein said lens allows oxygen permeation in an amount sufficient to maintain corneal health and wearer comfort during a period of extended, continuous contact with ocular tissue and ocular fluids, and

wherein said lens allows ion or water permeation in an amount sufficient to enable the lens to move on the eye such that corneal health is not substantially harmed and wearer comfort is acceptable during a period of extended, continuous contact with ocular tissue and ocular fluids.

2. An ophthalmic lens of claim 1, wherein said ophthalmic lens is selected from the group consisting of contact lenses for vision correction, contact lenses for eye color modification, ophthalmic drug delivery devices, and ophthalmic wound healing devices.

3. An ophthalmic lens of claim 2, wherein said ophthalmic lens is a contact lens.

4. An ophthalmic lens of claim 1, wherein said ophthalmic lens has an oxygen transmissibility of at least about 70 barrers/mm.

5. An ophthalmic lens of claim 4, wherein said ophthalmic lens has an oxygen transmissibility of at least about 75 barrers/mm.

6. An ophthalmic lens of claim 5, wherein said ophthalmic lens has an oxygen transmissibility of at least about 87 barrers/mm.

7. An ophthalmic lens of claim 1, wherein said polymeric material comprises an ionopem phase which extends continuously from the inner surface of the ophthalmic lens to the outer surface of the ophthalmic lens.

8. An ophthalmic lens of claim 1, wherein said polymeric material comprises an oxypem phase which extends continuously from the inner surface of the ophthalmic lens to the outer surface of the ophthalmic lens.
9. An ophthalmic lens of claim 1, wherein said polymeric material comprises a plurality of co-continuous phases, including at least one oxypem phase which extends continuously from the inner surface of the ophthalmic lens to the outer surface of the ophthalmic lens and at least one ionopem phase which extends continuously from the inner surface of the ophthalmic lens to the outer surface of the ophthalmic lens.
10. An ophthalmic lens of claim 1, wherein said polymeric material comprises at least one ion or water pathway which extends continuously from the inner surface of the ophthalmic lens to the outer surface of the ophthalmic lens.
11. An ophthalmic lens of claim 1, wherein said polymeric material comprises at least one oxygen pathway which extends continuously from the inner surface of the ophthalmic lens to the outer surface of the ophthalmic lens.
12. An ophthalmic lens of claim 1, wherein said polymeric material comprises a plurality of co-continuous pathways, at least one being an ion or water pathway and at least one other being an oxygen pathway, which pathways extend continuously from the inner surface of the lens to the outer surface of the lens.
13. An ophthalmic lens of claim 12, wherein said co-continuous pathways include a continuous phase of ionopem polymeric material and a continuous phase of siloxane-containing polymeric material.
14. An ophthalmic lens of claim 12, wherein said pathways have a domain size which is less than a size which undesirably distorts visible light in an amount which is visible to the eye of the wearer.
15. An ophthalmic lens of claim 1, wherein said lens has an Ionoton Ion Permeability Coefficient of greater than about $0.2 \times 10^{-5} \text{ cm}^2/\text{sec}$.

16. An ophthalmic lens of claim 15, wherein said lens has an Ionoton Ion Permeability Coefficient of greater than about $0.3 \times 10^{-6} \text{ cm}^2/\text{sec}$.
17. An ophthalmic lens of claim 16, wherein said lens has an Ionoton Ion Permeability Coefficient of greater than about $0.4 \times 10^{-6} \text{ cm}^2/\text{sec}$.
18. An ophthalmic lens of claim 1, wherein said lens has an Ionoflux Diffusion Coefficient of greater than about $1.5 \times 10^{-6} \text{ mm}^2/\text{min}$.
19. An ophthalmic lens of claim 18, wherein said lens has an Ionoflux Diffusion Coefficient of greater than about $2.6 \times 10^{-6} \text{ mm}^2/\text{min}$.
20. An ophthalmic lens of claim 19, wherein said lens has an Ionoflux Diffusion Coefficient of greater than about $6.4 \times 10^{-6} \text{ mm}^2/\text{min}$.
21. An ophthalmic lens of claim 1, wherein said lens has a Hydrodell Water Permeability Coefficient of greater than about $0.2 \times 10^{-6} \text{ cm}^2/\text{sec}$.
22. An ophthalmic lens of claim 21, wherein said lens has a Hydrodell Water Permeability Coefficient of greater than about $0.3 \times 10^{-6} \text{ cm}^2/\text{sec}$.
23. An ophthalmic lens of claim 22, wherein said lens has a Hydrodell Water Permeability Coefficient of greater than about $0.4 \times 10^{-6} \text{ cm}^2/\text{sec}$.
24. An ophthalmic lens of claim 1, wherein when hydrated, said lens has an equilibrium water content of less than about 32 weight percent when tested in accordance with the Bulk Technique.
25. An ophthalmic lens of claim 24, wherein when hydrated, said lens has an equilibrium water content of about 10 to about 30 weight percent when tested in accordance with the Bulk Technique.
26. An ophthalmic lens of claim 25, wherein when hydrated, said lens has an equilibrium water content of about 15 to about 25 weight percent when tested in accordance with the Bulk Technique.

27. An ophthalmic lens of claim 1, wherein said lens comprises a core polymeric material and an ophthalmically compatible surface which is a hydrophilic surface, wherein said surface is more hydrophilic than said core.
28. An ophthalmic lens of claim 27, wherein said hydrophilic surface is a hydrophilic polymeric surface coating.
29. An ophthalmic lens of claim 28, wherein said hydrophilic surface coating is applied via a plasma coating process.
30. An ophthalmic lens of claim 29, wherein said plasma coating is generated in the presence of a mixture of (a) a C_{1-8} alkane and (b) a gas selected from the group consisting of nitrogen, argon, oxygen, air and mixtures thereof.
31. An ophthalmic lens of claim 30, wherein said plasma coating is generated in the presence of a mixture of methane and air.
32. An ophthalmic lens of claim 1, wherein said oxypem polymerizable material is a siloxane-containing macromer.
33. An ophthalmic lens of claim 32, wherein said siloxane-containing macromer is a poly(dimethyl siloxane) having a number average molecular weight of at least about 800 and a glass transition temperature less than about -115 degrees Celsius.
34. An ophthalmic lens of claim 33, wherein said siloxane-containing macromer has a number average molecular weight of at least about 1700.
35. An ophthalmic lens of claim 32, wherein said polymeric material is formed from a polymerizable mixture comprising about 1 to about 10 weight percent of a low molecular weight siloxane-containing monomer.
36. An ophthalmic lens of claim 35, wherein said low molecular weight siloxane-containing monomer is TRIS.
37. An ophthalmic lens of claim 1, wherein said polymeric material is formed from a polymerizable mixture comprising:

- (a) about 60 to about 85 weight percent oxypem macromer; and
- (b) about 15 to about 40 weight percent ionopem monomer.

38. An ophthalmic lens of claim 37, wherein said polymeric material is formed from a polymerizable mixture comprising:


- (a) about 70 to about 82 weight percent oxypem macromer; and
- (b) about 18 to about 30 weight percent ionopem monomer.

39. An ophthalmic lens of claim 1, wherein said polymeric material is formed from a polymerizable mixture comprising:

- (a) about 30 to 60 weight percent oxypem macromer;
- (b) about 20 to 40 weight percent ionopem polymerizable material; and
- (c) about 1 to 35 weight percent TRIS, based on the total lens weight.

40. An ophthalmic lens of claim 1, wherein said polymeric material includes a polymer composition having good optical clarity and high oxygen permeability, comprising:

- (a) about 5 to about 94 dry weight percent of a macromer having the formula:



wherein:

R₁ and R₂ are selected from C₁-C₆ alkyl,

R₃, R₄, R₅, and R₆ are selected from C₁-C₆ alkylene,

R₇ and R₈ are selected from linear or branched alkylene and bivalent cycloalkylene,

R₉, R₁₀, R₁₁, and R₁₂ are selected from C₁-C₂ alkylene,

R₁₃ and R₁₄ are selected from C₁-C₆ alkylene,

R₁₅ and R₁₆ are selected from linear or branched lower alkenylene,


m and p, independently of one another, are about 3 to about 44, and

n is about 13 to about 80.


wherein said macromer has a number-average molecular weight of 2000 to 10,000;
 (b) about 5 to about 60 weight percent of an acrylated or methacrylated siloxane monomer;
 (c) about 1 to about 30 weight percent of an acrylate or methacrylate monomer; and
 (d) 0 to 5 weight percent cross-linking agent;
 wherein said weight percentages are based upon the dry weight of the polymer components.

41. An ophthalmic lens of claim 40, wherein said lens is a contact lens.


42. An ophthalmic lens of claim 1, wherein said polymeric material comprises a polymer formed by polymerization of at least one macromer of formula (I):



where each P_1 , independently of the others, is a free-radical-polymerizable group;
 each Y , independently of the others, is $-\text{CONHCOO}-$, $-\text{CONHCONH}-$, $-\text{OCONHCO}-$, $-\text{NHCONHCO}-$, $-\text{NHCO}-$, $-\text{CONH}-$, $-\text{NHCONH}-$, $-\text{COO}-$, $-\text{OCO}-$, $-\text{NHCOO}-$ or $-\text{OCONH}-$;
 m and p , independently of one another, are 0 or 1;
 each L , independently of the others, is a divalent radical of an organic compound having up to 20 carbon atoms;
 each X_1 , independently of the others, is $-\text{NHCO}-$, $-\text{CONH}-$, $-\text{NHCONH}-$, $-\text{COO}-$, $-\text{OCO}-$, $-\text{NHCOO}-$ or $-\text{OCONH}-$; and
 Q is a bivalent polymer fragment consisting of the segments:



where $x+y$ is a number in the range of from 10 to 30;
 each Z , independently of the others, is a divalent radical having up to 12 carbon atoms or Z is a bond;
 each E , independently of the others, is $-(\text{OCH}_2\text{CH}_2)_q-$, where q has a value of from 0 to 2,
 and where the link $-Z-E-$ represents the sequence $-Z-(\text{OCH}_2\text{CH}_2)_q-$; and
 k is 0 or 1;



where n is an integer from 5 to 100;

Alk is alkylene having up to 20 carbon atoms;

80-100% of the radicals R_1 , R_2 , R_3 and R_4 , independently of one another, are alkyl and

0-20% of the radicals R_1 , R_2 , R_3 and R_4 , independently of one another, are alkenyl, aryl or cyanoalkyl; and



where R is a divalent organic radical having up to 20 carbon atoms, and each X_2 , independently of the others, is $-NHCO-$, $-CONH-$, $-NHCONH-$, $-COO-$, $-OCO-$, $-NHCOO-$ or $OCONH-$;

with the provisos that there must be at least one of each segment (a), (b), and (c) in Q, that each segment (a) or (b) has a segment (c) attached to it, and that each segment (c) has a segment (a) or (b) attached to it.

43. An ophthalmic lens of claim 42, wherein said lens is a contact lens.

44. An ophthalmic lens of claim 1, wherein said polymeric material comprises a polymer, which polymer is produced by polymerizing at least one macromer comprising at least one segment of formula (I)



in which

(a) is a polysiloxane segment,

(b) is a polyol segment which contains at least 4 C atoms,

Z is a segment (c) or a group X_1 ,

(c) is defined as X_2-R-X_2 , wherein

R is a bivalent radical of an organic compound having up to 20 C atoms and

each X_2 independently of the other is a bivalent radical which contains at least one carbonyl group,

X_1 is defined as X_2 , and

(d) is a radical of the formula (II):



in which P_1 is a group which can be polymerized by free radicals;


Y and X_3 independently of one another are a bivalent radical which contains at least one carbonyl group;

k is 0 or 1; and

L is a bond or a divalent radical having up to 20 C atoms of an organic compound.


45. An ophthalmic lens of claim 44 which is a contact lens.

46. An ophthalmic lens of claim 1, wherein said polymeric material comprises a polymer, which polymer is produced by polymerizing at least one macromer of the formula:




wherein R_{100} and R_{200} are defined as follows:

R_{100} :



R_{200} :



where n is an integer from about 5 to about 500,

R_1 , R_2 , R_3 , and R_4 , independently of one another, are lower alkylene,


R_5 , R_6 , R_7 , and R_8 , independently of one another, are alkyl,

R_9 and R_{11} are alkylene, and

R_{10} and R_{12} are methyl or hydrogen.


47. An ophthalmic lens of claim 46, wherein said polymeric material is formed by polymerization of a prepolymer mixture, which, in weight percentages based on total mixture weight, comprises:

(a) about 45 to about 65 percent of a siloxane-containing macromer of the formula:




wherein R_{100} and R_{200} are defined as follows:

R_{100} :



R_{200} :



where n is an integer from about 5 to about 500,

R_1 , R_2 , R_3 , and R_4 , independently of one another, are lower alkylene,

R_5 , R_6 , R_7 , and R_8 , independently of one another, are alkyl,

R_9 and R_{11} are alkylene, and

R_{10} and R_{12} are methyl or hydrogen;

(b) about 5 to about 25 percent TRIS; and

(c) about 20 to about 40 percent ionperm monomer

48. An ophthalmic lens of claim 47 which is a contact lens.

49. An ophthalmic lens of claim 1, wherein said lens allows oxygen transmission in an amount sufficient to prevent any clinically significant corneal swelling during a period of extended, continuous contact with ocular tissue and ocular fluids.

50. An ophthalmic lens of claim 1, wherein said lens produces, after wear of about 24 hours, including normal sleep periods, less than about 8% corneal swelling.

51. An ophthalmic lens of claim 50, wherein said lens produces, after wear of about 24 hours, including normal sleep periods, less than about 6% corneal swelling.

52. An ophthalmic lens of claim 51, wherein said lens produces, after wear of about 24 hours, including normal sleep periods, less than about 4% corneal swelling.

53. An ophthalmic lens of claim 1, wherein said period of extended continuous contact is at least 24 hours.

54. An ophthalmic lens of claim 53, wherein said period of extended continuous contact is at least 4 days.
55. An ophthalmic lens of claim 54, wherein said period of extended continuous contact is at least 7 days.
56. An ophthalmic lens of claim 55, wherein said period of extended continuous contact is at least 14 days.
57. An ophthalmic lens of claim 56, wherein said period of extended continuous contact is at least 30 days.
58. An ophthalmic lens of claim 1, wherein said lens has a tensile modulus of 3 MPa or less.
59. An ophthalmic lens of claim 1, wherein said lens has a short relaxation time constant of greater than about 3.5 seconds.
60. An ophthalmic lens of claim 59, wherein said lens has an Ionoton Ion Permeability Coefficient, P, of greater than about $0.2 \times 10^{-6} \text{ cm}^2/\text{sec}$.
61. An ophthalmic lens of claim 59, wherein said lens has an Ionoflux Diffusion Coefficient of greater than about $2.6 \times 10^{-6} \text{ mm}^2/\text{min}$.
62. An ophthalmic lens of claim 59, wherein said lens has a Hydrocell Water Permeability Coefficient of greater than about $0.2 \times 10^{-6} \text{ cm}^2/\text{sec}$.
63. An ophthalmic lens of claim 1, wherein the polymeric material has a $\tan \delta$ above about 0.25 at about 10 Hz.
64. An ophthalmic lens of claim 1, wherein said lens has an Ionoton Ion Permeability Coefficient of greater than about $0.3 \times 10^{-6} \text{ cm}^2/\text{sec}$, a tensile modulus of 3 MPa or less, and a short relaxation time constant of greater than about 3.5 seconds.

65. An ophthalmic lens of claim 1, wherein said lens has an Ionoflux Diffusion Coefficient of greater than about 2.6×10^{-6} mm²/min., a tensile modulus of 3 MPa or less, and a short relaxation time constant of greater than about 3.5 seconds.

66. An ophthalmic lens of claim 1, wherein said lens has a Hydrodell Water Permeability Coefficient of greater than about 0.3×10^{-6} cm²/sec., a tensile modulus of 3 MPa or less, and a short relaxation time constant of greater than about 3.5 seconds.

67. An ophthalmic lens of claim 1, wherein said lens comprises a core polymeric material and an ophthalmically compatible surface which is a hydrophilic surface, wherein:
said surface is more hydrophilic than said core,
said period of extended continuous contact is at least 7 days,
said core material has an Ionoton Ion Permeability Coefficient of greater than about 0.3×10^{-6} cm²/sec, a tensile modulus of 3 MPa or less, and a short relaxation time constant of greater than about 3.5 seconds,
said lens has an equilibrium water content of about 10 to about 30 weight percent when tested in accordance with the Bulk Technique,
said lens has an oxygen permeability of at least 70 barrers/mm, and
said lens is an extended-wear contact lens.

68. An ophthalmic lens of claim 1, wherein said lens comprises a core polymeric material and an ophthalmically compatible surface which is a hydrophilic surface, wherein:
said surface is more hydrophilic than said core,
said period of extended continuous contact is at least 7 days,
said core material has an Ionoflux Diffusion Coefficient of greater than about 2.6×10^{-6} mm²/min., a tensile modulus of 3 MPa or less, and a short relaxation time constant of greater than about 3.5 seconds,
said lens has an equilibrium water content of about 10 to about 30 weight percent when tested in accordance with the Bulk Technique,
said lens has an oxygen permeability of at least 70 barrers/mm, and
said lens is an extended-wear contact lens.

69. An ophthalmic lens of claim 1, wherein said lens comprises a core polymeric material and an ophthalmically compatible surface which is a hydrophilic surface, wherein:
said surface is more hydrophilic than said core,
said period of extended continuous contact is at least 7 days,

said core material has a Hydrodell Water Permeability Coefficient of greater than about $0.2 \times 10^{-6} \text{ cm}^2/\text{sec.}$, a tensile modulus of 3 MPa or less, and a short relaxation time constant of greater than about 3.5 seconds,
said lens has an equilibrium water content of about 10 to about 30 weight percent when tested in accordance with the Bulk Technique,
said lens has an oxygen permeability of at least 70 barrers/mm, and
said lens is an extended-wear contact lens.

70. An ophthalmic lens, comprising an inner and outer surface, wherein said inner surface is adapted to rest immediately adjacent to the human cornea, wherein said lens has the following properties:

- (a) an oxygen permeability from said inner to said outer surface sufficient to prevent substantial corneal swelling during a period of extended wear;
- (b) ophthalmic compatibility during a period of extended, continuous, intimate contact with the ocular environment; and
- (c) ion or water permeability sufficient to allow lens movement on the eye in an amount sufficient to sustain corneal health and wearer comfort.

71. An ophthalmic lens of claim 70, wherein said period of extended wear is at least 24 hours.

72. An ophthalmic lens of claim 71, wherein said lens produces, after wear of about 24 hours, including normal sleep periods, less than about 8% corneal swelling.

73. An ophthalmic lens of claim 72, wherein said lens produces, after wear of about 24 hours, including normal sleep periods, less than about 6% corneal swelling.

74. An ophthalmic lens of claim 73, wherein said lens produces, after wear of about 24 hours, including normal sleep periods, less than about 4% corneal swelling.

75. An ophthalmic lens of claim 71, wherein said extended period of wear is at least 4 days.

76. An ophthalmic lens of claim 75, wherein said extended period of wear is at least 7 days.

77. An ophthalmic lens of claim 76, wherein said lens produces, after wear of about 7 days, including normal sleep periods, less than about 10% corneal swelling.

78. An ophthalmic lens of claim 77, wherein said lens produces, after wear of about 7 days, including normal sleep periods, less than about 7% corneal swelling.

79. An ophthalmic lens of claim 78, wherein said lens produces, after wear of about 7 days, including normal sleep periods, less than about 5% corneal swelling.

80. An ophthalmic lens of claim 70, wherein said period of extended wear is at least 14 days.

81. An ophthalmic lens of claim 80, wherein said extended period of wear is at least 30 days.

82. An ophthalmic lens of claim 70, wherein said oxygen permeability (Dk) is at least 70 barrers/mm.

83. An ophthalmic lens of claim 70, wherein said lens has a tensile modulus of 1.5 MPa or less.

84. An ophthalmic lens of claim 70, wherein said lens has a short relaxation time constant of greater than about 3.5 seconds.

85. An ophthalmic lens of claim 1, wherein the polymeric material has a $\tan \delta$ above about 0.25 at about 10 Hz.

86. An ophthalmic lens of claim 70, wherein said lens has an Ionoton Ion Permeability Coefficient of at least about $0.2 \times 10^{-6} \text{ cm}^2/\text{sec}$.

87. An ophthalmic lens of claim 70, wherein said lens has an Ionoflux Diffusion Coefficient of greater than about $1.5 \times 10^{-5} \text{ mm}^2/\text{min}$.

88. An ophthalmic lens of claim 70, wherein said lens has a Hydrodell Water Permeability Coefficient of greater than about $0.2 \times 10^{-6} \text{ cm}^2/\text{sec}$.

89. An ophthalmic lens of claim 70, wherein said extended period of wear is at least 24 hours and said oxygen transmissibility is at least 80 barrers/mm, and wherein said lens has a tensile modulus of 1.5 MPa or less, a short relaxation time constant of 1.4 to 10 seconds, and an Ionoton Ion Permeability Coefficient of at least $0.2 \times 10^{-6} \text{ cm}^2/\text{sec}$.

90. An ophthalmic lens of claim 70, wherein said extended period of wear is at least 4 days and said oxygen permeability (Dk) is at least 90 barrers/mm, and wherein said lens has a tensile modulus of 1.5 MPa or less, a short relaxation time constant of greater than about 3.5 seconds, and an Ionoton Ion Permeability Coefficient of at least $0.4 \times 10^{-6} \text{ cm}^2/\text{sec}$.

91. An ophthalmic lens of claim 70, wherein said extended period of wear is at least 4 days and said oxygen permeability (Dk) is at least 90 barrers/mm, and wherein said lens has a tensile modulus of 1.5 MPa or less, a short relaxation time constant of greater than about 3.5 seconds, and an Ionoflux Diffusion Coefficient of greater than about $1.5 \times 10^{-6} \text{ mm}^2/\text{min}$.

92. An ophthalmic lens of claim 70, wherein said extended period of wear is at least 4 days and said oxygen permeability (Dk) is at least 90 barrers/mm, and wherein said lens has a tensile modulus of 1.5 MPa or less, a short relaxation time constant of greater than about 3.5 seconds, and a Hydrodell Water Permeability Coefficient of greater than about $0.2 \times 10^{-6} \text{ cm}^2/\text{sec}$.

93. A method of using a contact lens as an extended wear lens, said lens having ophthalmically compatible inner and outer surfaces, said lens being suited to extended periods of wear in continuous, intimate contact with ocular tissue and ocular fluids, said lens comprising a polymeric material which has a high oxygen permeability and a high water permeability, said polymeric material being formed from polymerizable materials including:

(a) at least one oxypem polymerizable; and

(b) at least one ionopem polymerizable,

wherein said lens allows oxygen permeation in an amount sufficient to maintain corneal health and wearer comfort during a period of extended, continuous contact with ocular tissue and ocular fluids, and

wherein said lens allows ion permeation in an amount sufficient to enable the lens to move on the eye such that corneal health is not substantially harmed and wearer comfort is acceptable during a period of extended, continuous contact with ocular tissue and ocular fluids,

said method comprising the steps of:

- (a) applying said lens to the ocular environment; and
- (b) allowing said lens to remain in intimate contact with the ocular environment for a first period of at least 24 hours.

94. A method of claim 93, further including the steps of:

- (c) removing said lens from the ocular environment;
- (d) disinfecting or cleaning said lens;
- (e) re-applying said lens to the ocular environment; and
- (f) allowing said lens to remain in intimate contact with the ocular environment for a second period of at least 24 hours.

95. A method of claim 93, wherein said first intimate contact period is at least 4 days.

96. A method of claim 94, wherein said first and second intimate contact periods are at least 4 days.

97. A method of claim 95, wherein said first intimate contact period is at least 7 days.

98. A method of claim 96, wherein said first and second intimate contact periods are at least 7 days.

99. A method of claim 97, wherein said first intimate contact period is at least 14 days.

100. A method of claim 98, wherein said first and second intimate contact periods are at least 14 days.

101. A method of claim 99, wherein said first intimate contact period is at least 30 days.

102. A method of claim 100, wherein said first and second intimate contact periods are at least 30 days.

103. An ophthalmic lens of claim 93, wherein said lens produces, after wear of about 24 hours, including normal sleep periods, less than about 8% corneal swelling.

104. An ophthalmic lens of claim 103, wherein said lens produces, after wear of about 24 hours, including normal sleep periods, less than about 6% corneal swelling.

105. An ophthalmic lens of claim 104, wherein said lens produces, after wear of about 24 hours, including normal sleep periods, less than about 4% corneal swelling.

106. An ophthalmic lens of claim 93, wherein said lens produces, after wear of about 7 days, including normal sleep periods, less than about 10% corneal swelling.

107. An ophthalmic lens of claim 106, wherein said lens produces, after wear of about 7 days, including normal sleep periods, less than about 7% corneal swelling.

108. An ophthalmic lens of claim 107, wherein said lens produces, after wear of about 7 days, including normal sleep periods, less than about 5% corneal swelling.

109. A method of forming a biocompatible lens having high oxygen permeability and high water permeability, said method comprising the steps of:

(a) forming a core material including:

(1) at least one continuous pathway from front curve to base curve surfaces for oxygen transmission therethrough, and

(2) at least one continuous pathway from front curve to base curve surfaces for water transmission therethrough; and

(b) altering the surface of said core material to produce a surface which is more hydrophilic than said core material,

whereby said lens allows oxygen permeation in an amount sufficient to maintain corneal health and wearer comfort during a period of extended, continuous contact with ocular tissue and ocular fluids, and

whereby said lens allows ion permeation in an amount sufficient to enable the lens to move on the eye such that corneal health is not substantially harmed and wearer comfort is acceptable during a period of extended, continuous contact with ocular tissue and ocular fluids.

110. A method of claim 109, wherein said ophthalmic lens has an oxygen permeability of at least 70 barrers/mm.

111. A method of claim 110, wherein said ophthalmic lens has an oxygen permeability of at least 87 barrers/mm.

112. A method of claim 109, wherein said intimate contact period is at least 24 hours.
113. A method of claim 112, wherein said intimate contact period is at least 7 days.
114. A method of claim 109, wherein said lens has an Ionoton Ion Permeability Coefficient of at least about $0.3 \times 10^{-6} \text{ cm}^2/\text{sec}$.
115. An ophthalmic lens of claim 109, wherein said lens has an Ionoflux Diffusion Coefficient of greater than about $1.5 \times 10^{-6} \text{ mm}^2/\text{min}$.
116. An ophthalmic lens of claim 109, wherein said lens has a Hydrodell Water Permeability Coefficient of greater than about $0.2 \times 10^{-6} \text{ cm}^2/\text{sec}$.
117. A method of claim 111, wherein said intimate contact period is at least 7 days.
118. A method of claim 112, wherein said intimate contact period is at least 14 days.
119. A method of claim 118, wherein said surface altering comprises plasma treating said surface to render said surface more hydrophilic than said core.
120. An ophthalmic lens having ophthalmically compatible inner and outer surfaces, said lens being suited to extended periods of wear in continuous, intimate contact with ocular tissue and ocular fluids, said lens comprising a polymeric material which has a high oxygen permeability and a high ion permeability, said polymeric material being formed from polymerizable materials comprising at least one polymerizable material comprising:
(a) at least one oxypem segment; and
(b) at least one ionopem segment,
wherein said lens allows oxygen permeation in an amount sufficient to maintain corneal health and wearer comfort during a period of extended, continuous contact with ocular tissue and ocular fluids, and
wherein said lens allows ion or water permeation in an amount sufficient to enable the lens to move on the eye such that corneal health is not substantially harmed and wearer comfort is acceptable during a period of extended, continuous contact with ocular tissue and ocular fluids.

121. An ophthalmic lens of claim 120, wherein said ophthalmic lens has an oxygen transmissibility of at least about 70 barrers/mm.

122. An ophthalmic lens of claim 121, wherein said ophthalmic lens has an oxygen transmissibility of at least about 75 barrers/mm.

123. An ophthalmic lens of claim 122, wherein said ophthalmic lens has an oxygen transmissibility of at least about 87 barrers/mm.

124. An ophthalmic lens of claim 120, wherein said lens has an Ionoton Ion Permeability Coefficient of greater than about $0.2 \times 10^{-6} \text{ cm}^2/\text{sec}$.

125. An ophthalmic lens of claim 120, wherein said lens has an Ionoflux Diffusion Coefficient of greater than about $1.5 \times 10^{-6} \text{ mm}^2/\text{min}$.

126. An ophthalmic lens of claim 120, wherein said lens has a Hydrodell Water Permeability Coefficient of greater than about $0.2 \times 10^{-6} \text{ cm}^2/\text{sec}$.

127. A method of screening an ophthalmic lens for utility as an extended-wear lens, said method comprising the steps of:

- (a) allowing said lens to be fully hydrated by allowing said lens to equilibrate in a saline solution;
- (b) testing the lens to determine a factor which is a function of the oxygen transmissibility of said lens;
- (c) testing the lens to determine a factor which is a function of the ion or water permeability of said lens; and
- (d) selecting said lens as an extended-wear lens if said oxygen transmissibility factor and said water or ion permeability factor are both above predetermined limits which are established to ensure good corneal health and wearer comfort when said lens is in intimate contact with a human eye for a period of continuous, extended wear of at least 24 hours.

128. A screening method of claim 127, wherein said ion permeability factor is the Ionoton Ion Permeability Coefficient

129. A screening method of claim 128, wherein said Ionoton Ion Permeability Coefficient is greater than about $0.3 \times 10^{-6} \text{ cm}^2/\text{sec}$.

130. A screening method of claim 127, wherein said ion permeability factor is the Ionoflux Diffusion Coefficient.

131. A screening method of claim 130, wherein said Ionoflux Diffusion Coefficient is greater than about 2.6×10^{-6} mm²/min.

132. A screening method of claim 127, wherein said water permeability factor is the Hydrodell Water Permeability Coefficient.

133. A screening method of claim 132, wherein said Hydrodell Water Permeability Coefficient is greater than about $0.3 \times 10^{-5} \text{ cm}^2/\text{sec}$.


134. A screening method of claim 129, wherein said oxygen transmissibility factor is the Dk and the limit is 70 barrers/mm.

135. A screening method of claim 131, wherein said oxygen transmissibility factor is the Dk and the limit is 70 barrers/mm.

136. A screening method of claim 133, wherein said oxygen transmissibility factor is the Dk and the limit is 70 barrers/mm.

137. A polymer composition having good optical clarity and high oxygen permeability, comprising:

(a) about 5 to about 94 dry weight percent of a macromer having the formula:



wherein:

R_1 and R_2 are selected from C_1 - C_6 alkyl,
 R_3 , R_4 , R_5 , and R_6 are selected from C_1 - C_6 alkylene,
 R_7 and R_8 are selected from linear or branched alkylene and bivalent cycloalkylene,
 R_9 , R_{10} , R_{11} , and R_{12} are selected from C_1 - C_2 alkylene,
 R_{13} and R_{14} are selected from C_1 - C_6 alkylene,
 R_{15} and R_{16} are selected from linear or branched lower alkenylene,
 m and p , independently of one another, are about 3 to about 44, and
 n is about 13 to about 80,
wherein said macromer has a number-average molecular weight of 2000 to 10,000;
(b) about 5 to about 60 weight percent of an acrylated or methacrylated siloxane monomer;
(c) about 1 to about 30 weight percent of an acrylate or methacrylate monomer; and
(d) 0 to 5 weight percent cross-linking agent;
wherein said weight percentages are based upon the dry weight of the polymer components.

138. A polymer of claim 137, wherein said siloxane monomer is 3-methacryloxypropyltris(trimethylsiloxy)silane.

139. A polymer of claim 137, comprising:
(a) 70 to 90 weight percent of said macromer;
(b) 8 to 20 weight percent of said siloxane monomer;
(c) 1 to 5 weight percent hydrophilic monomer; and
(d) 0 to 2 weight percent cross-linking agent.

140. A polymer of claim 137, comprising about 10 to about 50 weight percent water.

141. A polymer of claim 140, wherein said water content is about 10 to about 30 weight percent.

142. A polymer of claim 141, wherein said water content is about 15 to about 22 weight percent.

143. A polymer of claim 139, comprising about 80 to 84 weight percent of said polysiloxane macromer.

144. A polymer of claim 139, comprising about 12 to 15 weight percent methacryloxypropyltris (trimethylsiloxy)silane.

145. A polymer of claim 137, wherein said acrylate or methacrylate component is 2-hydroxyethyl methacrylate.

146. A polymer of claim 140, comprising about 3 to about 4 weight percent of 2-hydroxyethyl methacrylate.

147. A polymer of claim 137, wherein said cross-linking agent is ethylene glycol dimethacrylate.

148. A polymer of claim 147, comprising about 0.7 to 1.2 weight percent ethylene glycol dimethacrylate

149. A polymer of claim 137, comprising:

- (a) about 80 to about 84 weight percent polysiloxane macromer;
- (b) about 12 to about 15 weight percent methacryloxypropyltris(trimethylsiloxy)silane;
- (c) about 3 to about 4 weight percent 2-hydroxyethyl methacrylate; and
- (d) about 0.7 to 1.2 weight percent ethylene glycol dimethacrylate.

150. A polymer of claim 149 having about 15 to about 22 weight percent water, based on total polymer weight.

151. A contact lens, comprising the polymer of claim 137.

152. A contact lens of claim 151, having a D_k greater than 80 barrers and a water content of about 10 to 30 weight percent.

153. A contact lens, comprising the polymer of claim 139.

154. A contact lens, comprising the polymer of claim 150.

155. A contact lens of claim 154, having a D_k greater than 80 barrers and a water content of about 10 to 30 weight percent.

156. A method of forming a molded polymeric article suitable for ophthalmic applications, comprising the steps of:

- (a) contacting a poly(dialkylsiloxane) dialkanol with a diisocyanate compound in the presence of a first catalyst at conditions sufficient to cause reaction of said dialkanol with said diisocyanate, thereby forming a first mixture;
- (b) contacting said first mixture with poly(alkylene glycol), a second catalyst, and sufficient solvent to ensure mixture homogeneity, thereby forming a second mixture;
- (c) evaporating sufficient solvent from said second mixture to generate a third mixture having a solids content of about 40 to 60 weight percent;
- (d) adding isocyanatoalkyl methacrylate to said third mixture, thereby forming a fourth mixture containing a polysiloxane macromer;
- (e) adding to said fourth mixture 3-methacryloxypropyltris(trimethylsiloxy)silane (TRIS), a hydrophilic monomer, a cross-linking agent and a photoinitiator, thereby forming a fifth mixture;
- (f) placing said fifth mixture into a mold; and
- (g) applying sufficient radiation to said fifth mixture to copolymerize the polymerizable material contained therein, thereby forming said polymeric material into a molded polymeric article.

157. A method as recited in claim 156, wherein said molded polymeric article is a contact lens.

158. A method of claim 156, comprising the steps of:

- (a) contacting poly(dimethylsiloxane) dialkanol with isophorone diisocyanate in the presence of dibutyltin dilaurate at conditions sufficient to cause reaction of said dialkanol with said diisocyanate, thereby forming a first mixture;
- (b) contacting said first mixture with poly(ethylene glycol), dibutyltin dilaurate, and sufficient solvent to ensure mixture homogeneity, thereby forming a second mixture;
- (c) evaporating sufficient solvent from said second mixture to generate a third mixture having a solids content of about 40 to 60 weight percent;
- (d) adding isocyanatoethyl methacrylate to said third mixture, thereby forming a fourth mixture containing a polysiloxane macromer;
- (e) adding to said fourth mixture 3-methacryloxypropyltris(trimethylsiloxy)silane, 2-hydroxyethyl methacrylate, ethylene glycol dimethacrylate and a photoinitiator, thereby forming a fifth mixture;
- (f) placing said fifth mixture into a mold; and

(g) applying sufficient radiation to copolymerize said polysiloxane macromer, TRIS, HEMA, and EGDMA, thereby forming said polymeric material into a molded polymeric article.

INTERNATIONAL SEARCH REPORT

International Application No.

PLI/EP 96/01265

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 G02B1/04

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 6 G02B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP,A,0 425 436 (CIBA-GEIGY) 2 May 1991 see claim 1 ---	1-158
X	EP,A,0 295 947 (OCULAR TECH) 21 December 1988 see abstract ---	1-39, 49-136
X	EP,A,0 277 771 (BAUSCH & LOMB) 10 August 1988 see claims ---	1-39, 49-136
X	EP,A,0 114 894 (HOYA LENS) 8 August 1984 see claims 1-4 ---	1-39, 49-136
X	EP,A,0 108 886 (AMERICAN OPT CORP) 23 May 1984 see claim 1 ---	1-39, 49-136
	--- -/-	



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

A document member of the same patent family

Date of the actual completion of the international search

23 July 1996

Date of mailing of the international search report

05.08.96

Name and mailing address of the ISA
European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl.
Fax (+31-70) 340-3016

Authorized officer

Lentz, J

INTERNATIONAL SEARCH REPORT

Int. Patent Application No.
PLI/EP.96/01265

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
----------	--	-----------------------

X	WO,A,93 05085 (BAUSCH & LOMB) 18 March 1993 see claims	1-41, 49-155
X	WO,A,93 09154 (BAUSCH & LOMB) 13 May 1993 see claims	1-41, 49-155
X	WO,A,91 04283 (CHANG ET AL) 4 April 1991 see claim 11	1-39, 49-136

INTERNATIONAL SEARCH REPORT

Information on patent family members

Int. Patent Application No.

PLI/EP 96/01265

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP-A-425436	02-05-91	US-A- 5010141	23-04-91
		AU-B- 4214293	07-10-93
		AU-B- 638066	17-06-93
		AU-B- 6495890	02-05-91
		CA-A- 2028359	26-04-91
		JP-A- 3153726	01-07-91
		US-A- 5079319	07-01-92

EP-A-295947	21-12-88	US-A- 4812598	14-03-89
		AT-T- 115968	15-01-95
		AU-B- 1812588	19-01-89
		DE-D- 3852522	02-02-95
		DE-T- 3852522	04-05-95
		ES-T- 2068200	16-04-95
		JP-A- 1099021	17-04-89
		US-A- 4822864	18-04-89
		US-A- 4820747	11-04-89

EP-A-277771	10-08-88	US-A- 4780515	25-10-88
		AU-B- 606916	21-02-91
		AU-B- 1127388	11-08-88
		CA-A- 1298928	14-04-92
		DE-A- 3880336	27-05-93
		ES-T- 2054795	16-08-94
		IE-B- 62535	08-02-95
		JP-A- 63258917	26-10-88

EP-A-114894	08-08-84	JP-C- 1549520	09-03-90
		JP-A- 59019918	01-02-84
		JP-B- 62061928	24-12-87
		AU-B- 1779483	23-02-84
		CA-A- 1205943	10-06-86
		CH-A- 664837	31-03-88
		DE-C- 3390130	11-08-88
		DE-T- 3390130	09-08-84
		GB-A,B 2135476	30-08-84
		WO-A- 8400619	16-02-84
		NL-T- 8320221	01-06-84
		US-A- 4540761	10-09-85

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PLT/EP 96/01265

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP-A-108886	23-05-84	CA-A- 1205247 JP-A- 59077411	27-05-86 02-05-84
WO-A-9305085	18-03-93	BR-A- 9206601 EP-A- 0603268 JP-T- 7502547 US-A- 5451617	17-10-95 29-06-94 16-03-95 19-09-95
WO-A-9309154	13-05-93	AU-B- 3066392 BR-A- 9206889 CN-A- 1074450 DE-D- 69211152 EP-A- 0611379 JP-T- 7505169 US-A- 5486579	07-06-93 02-05-95 21-07-93 04-07-96 24-08-94 08-06-95 23-01-96
WO-A-9104283	04-04-91	AU-B- 6331890 CA-A- 2040419 EP-A- 0443005 JP-T- 4501882	18-04-91 15-03-91 28-08-91 02-04-92